

FILTER FOAM, FLEXIBLE POLYURETHANE  
Open Pore, Polyvinylchloride Coated

1. SCOPE:

1.1 Form: This specification covers a reticulated, flexible polyurethane foam in the form of sheet coated with polyvinylchloride (PVC).

1.2 Application: Primarily for fresh air intake and exhaust filters requiring hydrolytic stability of the foam sheet resultant from the PVC coating.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications (AMS) shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

2.1 SAE Publications: Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

AMS 2350 - Standard and Test Methods

2.2 ASTM Publications: Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

ASTM D635 - Rate of Burning and/or Extent and Time of Burning of  
Self-Supporting Plastics in a Horizontal Position

ASTM D3574 - Testing Flexible Cellular Materials - Slab, Bonded, and Molded  
Urethane Foam

2.3 U.S. Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

SAE Technical Board rules provide that: "All technical reports, including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade or their use by governmental agencies is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."

## 2.3.1 Military Standards:

MIL-STD-794 - Parts and Equipment, Procedures for Packaging and Packing of  
 MIL-STD-810 - Environmental Test Methods

## 3. TECHNICAL REQUIREMENTS:

3.1 Material: Shall be a polyvinylchloride (PVC) coated, flexible polyurethane foam with controlled pore sizes of 20 and 45 pores per in. (ppi) (0.85 and 1.8 pores/mm).

3.1.1 Color: Shall be green, unless otherwise specified (See 8.1).

3.1.2 Fungus Resistance: The PVC coated foam shall be treated with a fungicide additive to prevent growth of fungus.

3.1.3 Non-Toxicity: The product shall be non-toxic and shall not cause any harmful effects when in prolonged contact with the skin.

3.2 Properties: The product shall conform to the following requirements; tests shall be performed on the product supplied and, except as otherwise specified, in accordance with ASTM D3574 insofar as practicable:

### 3.2.1 As Received:

3.2.1.1 Density 0.8 to 1 lb per cu ft  
 (12.8 to 16 kg/m<sup>3</sup>)

3.2.1.2 Resiliency, time for recovery to 95% original thickness, max 5 sec 4.5.1

3.2.1.3 Tensile Strength, min 10 psi (0.07 MPa)

3.2.1.4 Tear Strength, min 2 lb per in. (350 N/m)

3.2.2 Hydrolytic Stability: ASTM D3574,  
 Procedure J<sub>2</sub>

3.2.2.1 Change in Tensile Strength % max 10

3.2.2.2 Evidence of Surface Deterioration No tackiness, exudation, or cracking

- 3.2.3 Flammability (See 8.2): ASTM D635
- 3.2.3.1 Average Time of Burning, max 5 sec
- 3.2.3.2 Average Extent of Burning, max 0.1 in. (3 mm)
- 3.2.4 Fungus Resistance: Non Nutrient MIL-STD-810,  
Method 508
- 3.2.5 Low-Temperature Compression Set: 4.5.2
- 3.2.5.1 Percent of Original Thickness, max 25
- 3.2.6 Pore Size and Thickness: The foam shall be available in various pore sizes and thicknesses as follows:

Pore Size (4.5.3)		Nominal Thickness	
(ppi)	(pores/mm)	(Inch)	(Millimetres)
20	0.8	1/8 to 1	3.2 to 25
45	1.8	1/8 to 1/2	3.2 to 12

- 3.3 Quality: Foam, as received by purchaser, shall be uniform in quality and condition, homogeneous, and free from foreign materials and from internal and external imperfections detrimental to usage of the foam.
- 3.4 Tolerances: Unless otherwise specified, tolerances shall conform to the following:
- 3.4.1 Thickness: Shall not vary from the nominal by more than  $\pm 1/32$  in. ( $\pm 0.8$  mm).
- 3.4.2 Pore Size: Shall not vary from the nominal by more than  $\pm 5$  ppi (0.2 pores/mm).

4. QUALITY ASSURANCE PROVISIONS:

- 4.1 Responsibility for Inspection: The vendor of foam shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.6. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the foam conforms to the requirements of this specification.

## 4.2 Classification of Tests:

4.2.1 Acceptance Tests: Tests to determine conformance to requirements for flammability (3.2.3) and pore size (3.2.6) are classified as acceptance tests and shall be performed on each lot.

4.2.2 Preproduction Tests: Tests to determine conformance to all technical requirements of this specification are classified as preproduction tests and shall be performed on the initial shipment of foam to a purchaser, when a change in material and/or processing requires reapproval as in 4.4.2, and when purchaser deems confirmatory testing to be required.

4.2.2.1 For direct U.S. Military procurement, substantiating test data and, when requested, preproduction test material shall be submitted to the cognizant agency as directed by procuring activity, the contracting officer, or the request for procurement.

4.3 Sampling: Shall be in accordance with ASTM D3574 and the following; a lot shall be all foam of the same nominal pore size produced from the same batches of raw materials under the same conditions and presented for vendor's inspection at one time:

4.3.1 For Acceptance Tests: Sufficient foam shall be taken from each lot to perform all required tests. The number of specimens for each test shall be as specified in the applicable test procedure or, if not specified therein, not less than three. An inspection lot shall not exceed 200 lb (90 kg) or 2000 board feet (4.7 m<sup>3</sup>) of foam and may be packaged in smaller quantities and delivered under a basic lot approval provided the lot identification is maintained.

4.3.1.1 When a statistical sampling plan and acceptance quality level (AQL) have been agreed upon by purchaser and vendor, sampling shall be in accordance with such plan in lieu of sampling as in 4.3.1 and the report of 4.6.1 shall state that such plan was used.

4.3.2 For Preproduction Tests: As agreed upon by purchaser and vendor.

## 4.4 Approval:

4.4.1 Sample foam shall be approved by purchaser before foam for production use is supplied, unless such approval be waived by purchaser. Results of tests on production foam shall be essentially equivalent to those on the approved sample.

4.4.2 Vendor shall use ingredients, manufacturing procedures, processes, and methods of inspection on production foam which are essentially the same as those used on the approved sample foam. If necessary to make any change in ingredients, in type of equipment for processing, or in manufacturing procedures, vendor shall submit for reapproval a statement of the proposed changes in material and/or processing and, when requested sample foam. Production foam made by the revised procedure shall not be shipped prior to receipt of reapproval.

4.5 Test Methods:

4.5.1 Resiliency: Test specimens having top and bottom surface dimensions greater than the thickness shall be compressed to 25% of original thickness, held in the compressed state for 60 sec  $\pm$  5, and the load removed. The time to recover to 95% of original thickness shall be measured.

4.5.2 Low-Temperature Compression Set:

4.5.2.1 Apparatus and Test Specimens: Shall be as described in ASTM D3574 for Compression Set Test.

4.5.2.2 Procedure: Dry specimens for not less than 16 hr in a desiccator before testing. Place specimens in a cold chamber which is at  $-40^{\circ}\text{C} \pm 1$  ( $-40^{\circ}\text{F} \pm 2$ ) for 5 hr  $\pm$  0.1. At the end of this period and while still in the cold chamber, compress specimens to 75% of original thickness, maintain this compression for 60 sec  $\pm$  5, release the load, and, after 60 sec  $\pm$  5 recovery time, measure the thickness of specimens. Calculate the compression set as a percentage of the original thickness.

4.5.3 Pore Size: Shall be determined by the air pressure drop technique.

4.5.3.1 Test Specimens: Shall be discs, nominally 10 in. (250 mm) in diameter and 1.00 in.  $\pm$  0.02 (25.0 mm  $\pm$  0.5) thick, with the 1-in. (25-mm) dimension being in the thickness direction of the foam.

4.5.3.1.1 For acceptance tests, one specimen from each lot, taken within the top 3 in. (75 mm) of the foam slab, shall be tested.

4.5.3.1.2 For preproduction tests, three specimens, taken from the same location on the foam slab but from the upper, middle, and lower portions of the thickness of the foam slab, shall be tested.

4.5.3.2 Procedure: Pressure drop measurements shall be made using a porosity test jig as shown in Fig. 1, or equivalent (See 8.3).

4.5.3.2.1 Prior to testing, both manometers shall be adjusted to zero with no airflow.

4.5.3.2.2 The specimen shall then be inserted into the specimen holder until it is properly seated into the cutout.

4.5.3.2.3 The blower shall be started and the airflow set to 4 in. (100 mm) on the 8-in. (200 mm) orifice differential manometer.

4.5.3.2.4 The pressure drop through the specimen shall be read on the 4-in. (100-mm) sample differential manometer to the nearest 0.005 in. (0.12 mm) and compared with the calibration curve shown in Fig. 2 to determine the average pore size for the specimen.

4.5.3.2.5 Report, for each specimen, the pressure drop and the average pore size calculated from Fig. 2.

4.5.3.2.6 The porosity values shown in Fig. 2 have been assigned and do not necessarily relate directly to the actual number of pores per lineal inch (millimetre).

## 4.6 Reports:

4.6.1 The vendor of foam shall furnish with each shipment three copies of a report showing the results of tests to determine conformance to the acceptance test requirements and stating that the foam conforms to the other technical requirements of this specification. This report shall include the purchase order number, AMS 3569, vendor's compound number, lot number, and quantity.

4.6.2 The vendor of finished or semi-finished parts shall furnish with each shipment three copies of a report showing the purchase order number, AMS 3569, contractor or other direct supplier of foam, supplier's compound number, part number, and quantity. When foam for making parts is supplied or purchased by the parts vendor, that vendor shall inspect each lot of foam to determine conformance to the requirements of this specification and shall include in the report either a statement that the foam conforms or copies of laboratory reports showing the results of tests to determine conformance.

- 4.7 Resampling and Retesting: If any specimen used in the above tests fails to meet the specified requirements, disposition of the foam may be based on the results of testing three additional specimens for each original nonconforming specimen. Failure of any retest specimen to meet the specified requirements shall be cause for rejection of the foam represented and no additional testing shall be permitted. Results of all tests shall be reported.
5. PREPARATION FOR DELIVERY:
- 5.1 Identification and Packaging:
- 5.1.1 Foam shall be packaged in such a manner as to ensure that the product, during shipment and storage, will not be permanently distorted and will be protected against damage from exposure to weather, direct sunlight, or any other normal hazard.
- 5.1.2 Each package shall be permanently and legibly marked with not less than AMS 3569, size or part number, manufacturer's identification, compound number, purchase order number, quantity, and any applicable precautions or handling instructions for toxic or hazardous materials.
- 5.1.3 Containers of foam shall be prepared for shipment in accordance with commercial practice and in compliance with applicable rules and regulations pertaining to the handling, packaging, and transportation of the foam to ensure carrier acceptance and safe delivery. Packaging shall conform to carrier rules and regulations applicable to the mode of transportation.
- 5.1.4 For direct U.S. Military procurement, packaging shall be in accordance with MIL-STD-794, Level A or Level C as specified in the request for procurement. Commercial packaging as in 5.1.1 and 5.1.3 will be acceptable if it meets the requirements of Level C.
6. ACKNOWLEDGMENT: A vendor shall mention this specification number in all quotations and when acknowledging purchase orders.
7. REJECTIONS: Foam not conforming to this specification or to modifications authorized by purchaser will be subject to rejection.

## 8. NOTES:

- 8.1 The standard color is green. Other colors available on special order are red, blue, orange, and black.
- 8.2 The flammability test is intended only for comparative evaluation of compounds and is not to be construed as an indication of characteristics of the foam under actual fire conditions.
- 8.3 The Porosity Test Jig, manufactured by the Scott Paper Co., Drawing YH102-067x54, has been used satisfactorily in this test.
- 8.4 For direct U.S. Military procurement, purchase documents should specify not less than the following:
- Title, number, and date of this specification
  - Form and size or part number of foam desired
  - Quantity of foam desired
  - Color, if other than green (See 3.1.1 and 8.1)
  - Applicable level of packaging (See 5.1.4)
- 8.5 Product meeting the requirements of this specification has been classified under Federal Supply Classification (FSC) 4140.

This specification is under the jurisdiction of AMS Committee "C".