

AEROSPACE MATERIAL SPECIFICATION



AMS 3571/1B

Issued JUL 1976
Revised APR 1991
Reaffirmed JAN 2001

Superseding AMS 3571/1A

Resin, Polyether Urethane (EU) Casting
Flexible, Solid, Unfilled
45 Durometer "A"

1. SCOPE:

1.1 Form:

This specification covers one type of polyether-type urethane (EU) resin and hardener which, when mixed and cured, produce elastomeric polyurethane products.

1.2 Application:

See AMS 3571.

1.3 Classification:

45 Durometer "A".

2. APPLICABLE DOCUMENTS:

See AMS 3571.

3. TECHNICAL REQUIREMENTS:

3.1 Basic Specification:

The complete requirements for procuring the product described herein shall consist of this document and the latest issue of the basic specification, AMS 3571.

3.2 Material:

See AMS 3571.

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright 2001 Society of Automotive Engineers, Inc.
All rights reserved.

Printed in U.S.A.

QUESTIONS REGARDING THIS DOCUMENT:
TO PLACE A DOCUMENT ORDER:

(724) 772-7161
(724) 776-4970

FAX: (724) 776-0243
FAX: (724) 776-0790

AMS 3571/1B**SAE****AMS 3571/1B****3.3 Properties of Cured Product:**

The product, mixed and cured in accordance with manufacturer's instructions, shall conform to the following requirements, determined in accordance with specified test methods:

3.3.1	Hardness, Durometer "A" or equivalent	45 ± 5	ASTM D 2240
3.3.2	Tensile Strength, minimum	300 psi (2.07 MPa)	ASTM D 412
3.3.3	Elongation, minimum	150%	ASTM D 412
3.3.4	Tensile Stress at 100% Elongation, minimum	150 psi (1.03 MPa)	ASTM D 412
3.3.5	Compression Set, Method B, after 22 hours ± 0.5 at 70°C ± 2 (158°F ± 4), maximum	35%	ASTM D 395
3.3.6	Tear Strength, minimum	25 pounds force per inch (4.4 kN/m)	ASTM D 624 Die C
3.3.7	Bond Strength to Metal, Peel Test, minimum	20 pounds force per inch (3.5 kN/m)	ASTM D 903
3.3.7.1	The use of a primer is optional. Tests shall be run on grit blasted aluminum specimens with the nominal 1/2 inch (12.7 mm) overlap. Grit size shall be 100 - 200 mesh (150 - 75 µm).		
3.3.8	Specific Gravity	1.00 to 1.20	ASTM D 792
3.3.9	Modulus of Rigidity at -55°C (-67°F), maximum	100 ksi (689 MPa)	ASTM D 1053
3.3.10	Electrical Insulation Resistance, minimum		ASTM D 257
	at 25°C (77°F)	100,000 megohms	
	at 120°C (248°F)	750 megohms	
3.3.11	Hydrolytic Stability at 70°C ± 2 (158°F ± 4) and 95% ± 5 RH	30% decrease, in 120 days, of Durometer hardness, maximum	MIL-M-24041