

RESIN, POLYETHER URETHANE (EU) CASTING  
Flexible, Solid, Unfilled  
95 Durometer "A"

1. SCOPE:

1.1 Form: This specification covers one type of polyether-type urethane (EU) resin and hardener which, when mixed and cured, produce elastomeric polyurethane products.

1.2 Application: Primarily for liquid application as electronic encapsulation or for casting parts and shapes.

1.3 Classification: 95 Durometer "A".

2. APPLICABLE DOCUMENTS: See AMS 3571.

3. TECHNICAL REQUIREMENTS:

3.1 Basic Specification: The complete requirements for procuring the product described herein shall consist of this document and the latest issue of the basic specification, AMS 3571.

3.2 Material: See AMS 3571.

3.3 Properties of Cured Product: The material, mixed and cured in accordance with manufacturer's instructions, shall conform to the following requirements, determined in accordance with test methods listed in AMS 3571:

3.3.1	Hardness, Durometer "A" or equiv.	95 ± 5
	Durometer "D" or equiv.	45 ± 5
3.3.2	Tensile Strength, min	2500 psi (17.0 MPa)
3.3.3	Elongation, min	275%
3.3.4	Tensile Stress at 100% Elongation, min	900 psi (6.20 MPa)

SAE Technical Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

AMS documents are protected under United States and international copyright laws. Reproduction of these documents by any means is strictly prohibited without the written consent of the publisher.