

PLASTIC TUBING, ELECTRICAL INSULATION
Irradiated Polyvinylidene Fluoride, Semi-Rigid, Heat-Shrinkable
Marker Sleeving Grade
Low Outgassing

1. SCOPE:

1.1 Form: This specification covers an irradiated, thermally-stabilized, flame-resistant, modified-polyvinylidene-fluoride plastic in the form of semi-rigid, extra-thin-wall, heat-shrinkable tubing.

1.2 Application: Primarily for use as a semi-rigid, electrical insulation tubing and marker sleeves in short lengths whose diameter can be reduced to a predetermined size by heating to temperatures of 175°C (345°F) or higher.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

2.1 SAE Publications: Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

AMS 2350 - Standards and Test Methods
AMS 3032 - Aviation Fuel, Grade 100/130

2.2 ASTM Publications: Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

ASTM D471 - Rubber Property - Effect of Liquids
ASTM D2671 - Testing Heat-Shrinkable Tubing for Electrical Use
ASTM E595 - Total Mass Loss and Collected Volatile Condensable Materials from Outgassing in a Vacuum Environment
ASTM G21 - Determining Resistance of Synthetic Polymeric Materials to Fungi

2.3 U.S. Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

SAE Technical Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

AMS documents are protected under United States and international copyright laws. Reproduction of these documents by any means is strictly prohibited without the written consent of the publisher.

2.3.1 Military Specifications:

- MIL-H-5606 - Hydraulic Fluid, Petroleum Base, Aircraft, Missile, and Ordnance
- MIL-T-5624 - Turbine Fuel, Aviation, Grades JP-4 and JP-5
- MIL-L-7808 - Lubricating Oil, Aircraft Turbine Engine, Synthetic Base
- MIL-A-8243 - Anti-icing and Deicing-Defrosting Fluid

2.3.2 Military Standards:

- MIL-STD-794 - Parts and Equipment, Procedures for Packaging and Packing of

3. TECHNICAL REQUIREMENTS:

3.1 Material: Shall be an irradiated, thermally-stabilized, flame-resistant, modified-polyvinylidene fluoride plastic.

3.2 Color: Shall be opaque white, unless otherwise specified.

3.3 Properties: Tubing shall conform to the following requirements; reported values shall be the average of all specimens tested for each requirement. Except as otherwise specified, tests shall be performed in accordance with ASTM D2671 insofar as practicable.

3.3.1 Recovered Tubing: The following requirements apply to tubing after being shrunk by heating to $200^{\circ}\text{C} \pm 5$ ($390^{\circ}\text{F} \pm 9$) in a convection-current air oven with an air velocity of 100 - 200 ft per min. (0.5 - 1.0 m/sec) past the tubing, holding at heat for not less than 3 min., removing from the oven, and conditioning for not less than 4 hr at $23^{\circ}\text{C} \pm 2$ ($73^{\circ}\text{F} \pm 4$) and 45 - 55% relative humidity.

- | | | | |
|---------|---|---------------------|----------|
| 3.3.1.1 | Tensile Strength, min | 4000 psi | |
| | Jaw separation rate 2.0 in. | (28 MPa) | |
| | per min. (0.85 mm/sec) | | |
| 3.3.1.2 | Elongation, min | 200% | |
| 3.3.1.3 | Dielectric Strength | 600 V/mil | |
| | (short time test), min | (23,600 V/mm) | |
| 3.3.1.4 | Volume Resistivity, min | 10^{12} ohm-cm | |
| 3.3.1.5 | Flammability, Burning Time | 15 sec | |
| | Procedure A, max | | |
| 3.3.1.6 | Fungus Resistance | Rating of 1 or less | ASTM G21 |
| 3.3.1.7 | Heat Aging, 168 hr \pm 2 at | | |
| | $225^{\circ}\text{C} \pm 3$ ($354^{\circ}\text{F} \pm 5$) | | |

3.3.1.7.1	Tensile Strength, min	3000 psi (21 MPa)	
3.3.1.7.2	Elongation, min	150%	
3.3.1.8	Solvent Resistance		4.5.1
3.3.1.8.1	Tensile Strength, min	2000 psi (14 MPa)	
3.3.1.8.2	Dielectric Strength, min	500 V/mil (19,700 V/mm)	
3.3.1.9	Dimensional Change on Heating		
3.3.1.9.1	Diametral	In accordance with Table I	
3.3.1.9.2	Longitudinal, max	$\pm 10\%$	
3.3.1.10	Vacuum Outgassing		ASTM E595
3.3.1.10.1	Total Mass Loss (TML), max	1.0%	
3.3.1.10.2	Volatile Condensable Material (VCM), max	0.1%	
3.3.2	<u>Expanded Tubing</u> : The following requirements apply to tubing in the expanded (as-received) condition. Heating for the tests of 3.3.2.2 and 3.3.2.3 shall be performed in an oven as specified in 3.3.1.		
3.3.2.1	Secant Modulus at 2% Strain, min	80,000 psi (550 MPa)	
3.3.2.2	Heat Shock, 4 hr ± 0.25 at 275°C ± 5 (525°F ± 9)	No dripping, flowing, or cracking	
3.3.2.3	Restricted Shrinkage, Procedure C, after 30 min. ± 1 at 175°C ± 5 (350°F ± 9)	No cracks; withstand 2000 V for 1 min.	
3.3.2.4	Specific Gravity, max	1.80	
3.3.2.5	Low-Temperature Flexibility 4 hr ± 0.25 at -55°C ± 2 (-65°F ± 4)	No cracks	4.5.3
3.3.2.6	Water Absorption, max 24 hr ± 0.25 at 25°C ± 2 (77°F ± 4)	2.0%	

AMS 3593

- 3.4 Marking: Tubing, prior to and after shrinkage, shall be suitable for having numbers or characters printed on it with conventional tubing marking techniques. Marking applied prior to shrinkage shall not be distorted by non-concentric shrinkage.
- 3.5 Quality: Tubing, as received by purchaser, shall be uniform in quality and condition, smooth, and free from foreign materials and from imperfections detrimental to usage of the tubing.
- 3.6 Standard Sizes and Tolerances: Tubing shall be supplied in lengths of 48 in., $+1, -0$ (1200 mm, $+25, -0$), and in the standard sizes and to the tolerances shown in Table I, unless otherwise specified. Tolerances apply at $23^{\circ} - 30^{\circ}\text{C}$ ($73^{\circ} - 86^{\circ}\text{F}$). Measurements shall be made in accordance with ASTM D2671.
- 3.6.1 Dimensional requirements (lengths, inside diameters, wall thicknesses, tolerances and longitudinal change) of short lengths of tubing used specifically for identification purposes shall be as agreed upon by purchaser and vendor.

TABLE I

Size	Expanded (As Supplied)		Recovered Dimensions (After Heating)		
	ID, Inches min	ID, Inches max	Nominal ID, Inch	Nominal Wall Thickness Inch	Wall Thickness Tolerance, Inch plus and minus
3/64	0.046	0.023	0.010	0.010	0.002
1/16	0.063	0.031	0.010	0.010	0.002
3/32	0.093	0.046	0.010	0.010	0.002
1/8	0.125	0.062	0.010	0.010	0.002
3/16	0.187	0.093	0.010	0.010	0.002
1/4	0.250	0.125	0.012	0.012	0.003
3/8	0.375	0.187	0.012	0.012	0.003
1/2	0.500	0.250	0.012	0.012	0.003
3/4	0.750	0.375	0.017	0.017	0.003
1	1.000	0.500	0.019	0.019	0.003
1-1/2	1.500	0.750	0.019	0.019	0.003
2	2.000	1.000	0.020	0.020	0.003

TABLE I (SI)

Size	Expanded (As Supplied)		Recovered Dimensions (After Heating)	
	ID Millimetres min	ID Millimetres max	Nominal Wall Thickness Millimetre	Wall Thickness Tolerance Millimetre plus and minus
3/64	1.17	0.58	0.25	0.05
1/16	1.60	0.79	0.25	0.05
3/32	2.36	1.17	0.25	0.05
1/8	3.18	1.57	0.25	0.05
3/16	4.75	2.36	0.25	0.05
1/4	6.35	3.18	0.30	0.08
3/8	9.52	4.75	0.30	0.08
1/2	12.70	6.35	0.30	0.08
3/4	19.05	9.52	0.43	0.08
1	25.40	12.70	0.48	0.08
1-1/2	38.10	19.05	0.48	0.08
2	50.80	25.40	0.51	0.08

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection: The vendor of tubing shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.6. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the tubing conforms to the requirements of this specification.

4.2 Classification of Tests:

4.2.1 Acceptance Tests: Tests to determine conformance to requirements for tensile strength (3.3.1.1), elongation (3.3.1.2), dimensional change on heating (3.3.1.9), heat shock (3.3.2.2), and sizes and tolerances (3.6) are classified as acceptance tests and shall be performed on each lot.

4.2.2 Periodic Tests: Tests to determine conformance to requirements for dielectric strength (3.3.1.3), volume resistivity (3.3.1.4), flammability (3.3.1.5), fungus resistance (3.3.1.6), heat aging (3.3.1.7), solvent resistance (3.3.1.8), vacuum outgassing (3.3.1.10), secant modulus (3.3.2.1), restricted shrinkage (3.3.2.3), specific gravity (3.3.2.4), low-temperature flexibility (3.3.2.5), water absorption (3.3.2.6), and marking (3.4) are classified as periodic tests and shall be performed at a frequency selected by the vendor unless frequency of testing is specified by purchaser.

AMS 3593

4.2.3 Preproduction Tests: Tests to determine conformance to all technical requirements of this specification are classified as preproduction tests and shall be performed prior to or on the initial shipment of tubing to a purchaser, when a change in material or processing, or both, requires reapproval as in 4.4.2, and when purchaser deems confirmatory testing to be required.

4.2.3.1 For direct U.S. Military procurement, substantiating test data and, when requested, preproduction test material shall be submitted to the cognizant agency as directed by the procuring activity, the contracting officer, or the request for procurement.

4.3 Sampling: Shall be in accordance with AMS D2671 and as follows:

4.3.1 For Acceptance Tests: Not less than 16 ft (5 m) of tubing taken at random from each lot. The number of determinations for each requirements shall be as specified in the applicable test procedure or, if not specified therein, not less than three.

4.3.1.1 A lot shall be not more than 250,000 ft (76,200 m) of the same size tubing from one production run presented for vendor's inspection at one time. An inspection lot shall not exceed the quantities specified below and may be packaged in small quantities under the basic lot approval provided lot identification is maintained.

Tubing Size	Inspection Lot Size
3/64 - 1/4, incl	100,000 ft (30,000 m)
3/8 - 1/2, incl	30,000 ft (9,000 m)
3/4 - 2, incl	10,000 ft (3,000 m)

4.3.1.2 When a statistical sampling plan and acceptance quality level (AQL) have been agreed upon by purchaser and vendor, sampling shall be in accordance with such plan in lieu of sampling as in 4.3.1 and the report of 4.6.1 shall state that such plan was used.

4.3.2 For Periodic Tests: Not less than 48 ft (15 m) of tubing of each size or size range. Certain representative sizes may be used to demonstrate conformance of a range of sizes as follows:

Representative Size	Range of Sizes
3/16	3/64 - 3/16, incl
1	1/4 - 2, incl

4.3.3 For Preproduction Tests: As agreed upon by purchaser and vendor.

4.4 Approval:

- 4.4.1 Sample tubing shall be approved by purchaser before tubing for production use is supplied, unless such approval be waived by purchaser. Results of tests on production tubing shall be essentially equivalent to those on the approved sample tubing.
- 4.4.2 Vendor shall use ingredients, manufacturing procedures, processes, and methods of inspection on production tubing which are essentially the same as those used on the approved sample tubing. If necessary to make any change in ingredients, in type of equipment for processing, or in manufacturing procedures, vendor shall submit for reapproval a statement of the proposed changes in material or processing, or both, and, when requested, sample tubing. Tubing made by the revised procedure shall not be shipped prior to receipt of reapproval.

4.5 Test Methods:

- 4.5.1 Solvent Resistance: Shall be determined in accordance with ASTM D2671 on specimens immersed for 24 hr \pm 2 at 23°C \pm 3 (73°F \pm 5) in MIL-T-5624 JP-4 fuel, SAE phosphate ester test fluid No. 1A (See 8.1), MIL-L-7808 lubricating oil, MIL-H-5606 hydraulic oil, ASTM service fluid No. 101 (See ASTM D471), AMS 3032 aviation gasoline 100/130, MIL-A-8243 anti-icing fluid, and salt water (5% salt), using separate specimens for each fluid.
- 4.5.2 Bending After Heat Shock: Specimens from the heat shock test of 3.3.2.2 shall be bent 180 deg around the applicable mandrel of Table II. Any side-cracking, caused by flattening of the specimens on the mandrel shall be disregarded.

TABLE II

MANDREL DIMENSIONS

Tubing Size	<u>Diameter of Mandrel</u>	
	Inches	Millimetres
3/64 through 3/16	5/16	7.9
1/4 through 2	3/4	19.0

- 4.5.3 Low-Temperature Flexibility: For tubing of expanded size of 1/4 in. or greater, three strip specimens 0.250 in. \pm 0.010 (6.35 mm \pm 0.25) wide and 12 in. (300 mm) long shall be cut from the expanded tubing. For tubing of expanded diameter less than 1/4 in. (6.35 mm), three tubular specimens 12 in. (300 mm) long shall be cut from the expanded tubing. The specimens shall be recovered in accordance with 3.3.1 and conditioned in accordance with 3.3.2.5. Mandrel diameter shall be 10 times specimen thickness, \pm 10%. For tubular specimens, the specimen thickness shall be taken as the outside diameter, determined in accordance with ASTM D2671. After the conditioning period and while at the specified low temperature, and without removing the specimens from the chamber, bend the specimens around

AMS 3593

4.5.3 (Continued):

the mandrel for not less than one complete wrap (360 deg) at a uniform speed of about 4 sec per wrap. Any side cracking, caused by flattening of the specimens on the mandrel, shall be disregarded.

4.6 Reports:

4.6.1 The vendor of tubing shall furnish with each shipment a report showing the results of tests to determine conformance to the acceptance tests requirements and, when performed, to the periodic test requirements and stating that the tubing conforms to the other technical requirements of this specification. This report shall include the purchase order number, AMS 3593, vendor's compound number, lot number, size, and quantity.

4.6.2 The vendor of finished or semi-finished parts shall furnish with each shipment a report showing the purchase order number, AMS 3593, contractor or other direct supplier of tubing, supplier's compound number, part number, and quantity. When tubing for making parts is produced or purchased by the parts vendor, that vendor shall inspect each lot of tubing to determine conformance to the requirements of this specification and shall include in the report either a statement that the tubing conforms or copies of laboratory reports showing the results of tests to determine conformance.

4.7 Resampling and Retesting: If the average of the results of the specimens tested for any requirement fails to meet the specified value, disposition of the tubing may be based on the results of testing three additional specimens for each original specimen failing to meet the specified average requirement. Failure of the average of the original specimens plus the retest specimens to meet any specified requirement shall be cause for rejection of the tubing represented and no additional testing shall be permitted. Results of all tests shall be reported.

5. PREPARATION FOR DELIVERY:

5.1 Identification: Each package shall be permanently and legibly marked with not less than AMS 3593, size, quantity, purchase order number, manufacturer's identification, and date of manufacture.