



AEROSPACE MATERIAL SPECIFICATIONS

SOCIETY OF AUTOMOTIVE ENGINEERS, Inc.

485 Lexington Ave., New York, N. Y. 10017

AMS 3636B

Superseding AMS 3636A

Issued 2-15-65

Revised 11-1-67

PLASTIC TUBING, ELECTRICAL INSULATION Irradiated Polyolefin, Pigmented, Flexible, Heat Shrinkable 2 to 1 Shrink Ratio

- 1. ACKNOWLEDGMENT:** A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.
- 2. FORM:** Thin wall flexible tubing.
- 3. APPLICATION:** Primarily for use as a flexible, electrical insulation tubing whose diameter can be reduced to a predetermined size by heating to temperatures higher than 121 C (250 F). This material is stable under the following conditions:

-55 C (-67 F) to 135 C (275 F)	Continuous
-55 C (-67 F) to 150 C (302 F)	2000 hr
-55 C (-67 F) to 175 C (347 F)	336 hr
-55 C (-67 F) to 200 C (392 F)	48 hr
-55 C (-67 F) to 250 C (482 F)	8 hr
-55 C (-67 F) to 300 C (572 F)	2 hr

- 4. COMPOSITION:** The material shall be an irradiated, thermally stabilized, flame-resistant, modified polyolefin.

5. TECHNICAL REQUIREMENTS:

- 5.1 Color:** The tubing shall be furnished in black, white, red, yellow, or blue, as ordered. Unless otherwise specified, the colors shall be in accordance with MIL-STD-104.
- 5.2 Properties:** The product shall conform to the requirements of 5.2.1 through 5.2.5 and shall be capable of meeting the requirements of 5.2.6 through 5.2.17. Tests shall be performed in accordance with the issue of specified ASTM methods listed in the latest issue of AMS 2350, insofar as practicable. Unless otherwise specified, tubing shall be tested after being shrunk by heating for 3 min. in a mechanical convection oven which is at $200\text{ C} \pm 5$ ($392\text{ F} \pm 9$), with an air velocity of 100 - 200 ft per min. past the tubing, removed from the oven, and cooled to room temperature.
 - 5.2.1 Tensile Strength, psi, min.**

Sizes 3/64 to 1/4, incl	2000	ASTM D638, Speed D (See Note 1)
Sizes 3/8 to 4, incl	1500	
 - 5.2.2 Elongation, %, min** 200 ASTM D638, Speed D (See Note 1)
 - 5.2.3. Secant Modulus at 2% Strain, psi, max** 2.5×10^4 ASTM D882 (See Note 2)
 - 5.2.4 Heat Shock** Pass Note 3
 - 5.2.5 Flammability** Self-Extinguishing Note 4
 - 5.2.6 Low Temperature Flexibility** Pass Note 5

SAE Technical Board rules provide that: "All technical reports, including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."

5.2.7	Heat Aging	Pass	Note 6
∅ 5.2.8	Copper Stability	Pass	Note 7
5.2.9	Corrosion	Pass	Note 8
5.2.10	Color Stability	Pass	Note 9
5.2.11	Solvent Resistance	Pass	Note 10
5.2.12	Fungus Resistance	Pass	Note 11
∅ 5.2.13	Restricted Shrinkage	Pass	Note 12
5.2.14	Specific Gravity, max	1.35	ASTM D792, Method A
5.2.15	Water Absorption in 24 hr, %, max	0.50	ASTM D570
5.2.16	Dielectric Strength, short time test, v per mil, min	500	ASTM D876
5.2.17	Volume Resistivity, ohm-cm, min	10 ¹⁴	ASTM D257

- Note 1.** Five specimens, each 4 in. long, shall be tested, using 1 in. bench marks and 1 in. initial jaw separation. The specimens shall be full sections of tubing for sizes 1/4 and smaller and strip specimens not less than 1/4 in. wide cut longitudinally from sizes 3/8 and larger. No metal plugs are necessary when testing full sections of tubing. A specimen break at a bench mark or outside the gage length shall be cause for retest.
- Note 2.** Five specimens in the expanded form (as supplied), each 12 in. long, shall be tested. The specimens shall be full sections of tubing for sizes 1/4 and smaller and strip specimens not less than 1/2 in. wide cut longitudinally from sizes 3/8 and larger. No metal plugs are necessary when testing full sections of tubing. Initial strain rate shall be 0.1 in. per in. per minute.
- Note 3.** Three specimens in the expanded form (as supplied), each 6 in. in length, shall be conditioned for 4 hr in a mechanical convection oven which is at 250 C ± 5 (482 F ± 9), with an air velocity of 100 - 200 ft per min. past the specimens. After conditioning, the specimens shall be removed from the oven, cooled to room temperature, and visually examined. Tubing shall not drip, flow, or crack. Also, tubing shall be bent through 180 deg over a steel mandrel of the diameter shown in Table 1. The tubing shall remain free from cracks except that any side cracking caused by flattening of the specimen on the mandrel shall be disregarded.

TABLE I

Size	Diameter of Mandrel, Inch
3/64 to 1/4, incl	5/16
3/8 to 1/2, incl	3/8
3/4 to 2, incl	7/16
3 to 4, incl	7/8

- Note 4.** A specimen of tubing 18 in. in length shall be shrunk over a metal rod, 21 in. in length, with a diameter equivalent to the applicable maximum recovered diameter specified in Table II. The specimen then shall be subjected to vertical test in accordance with Federal specification J-C-98, Method 5221. The tubing shall extinguish within 1 min. after final removal of the gas flame, shall not drip or flow, and not more than 25% of the indicator flag shall be burned or charred. Brown scorching or soot on the indicator flag shall not be cause for rejection.

- Note 5. Three specimens, each 6 in. in length (x 1/4 in. wide strips cut from sizes 3/4 and larger), shall be conditioned at $-55\text{ C} \pm 2$ ($-67\text{ F} \pm 3.6$) for 4 hours. A fixed steel mandrel, selected in accordance with Table 1 above, shall be conditioned at this temperature. Upon completion of this conditioning and at this same temperature, the specimens shall be wrapped not less than 360 deg about the mandrel in approximately 2 seconds. The specimens shall be free from cracks.
- Note 6. Specimens shall be prepared as in Note 1 and shall be conditioned for 336 hr in a mechanical convection oven which is at $175\text{ C} \pm 3$ ($347\text{ F} \pm 5.4$), with an air velocity of 100 - 200 ft per min. past the specimens. After conditioning, the specimens shall be removed from the oven, cooled to room temperature, and tested for elongation. Specimens shall have elongation of not less than 150%.
- Note 7. A specimen of each color of tubing, 6 in. in length, shall be slid over a straight, clean, unplated, un-insulated, solid copper conductor. For sizes 1/4 and smaller, a single copper conductor shall be used; for sizes 3/8 and larger, several copper conductors shall be used, each conductor AWG 18 or smaller. The specimens on horizontally suspended conductors shall be conditioned for not less than 24 hr in a humidity chamber at 90 - 95% relative humidity and $25\text{ C} \pm 3$ ($77\text{ F} \pm 5.4$). The specimens on horizontally suspended conductors then shall be conditioned for 168 hr in an oven which is at $160\text{ C} \pm 3$ ($320\text{ F} \pm 5.4$), in accordance with ASTM D573, cooled to room temperature, and examined. The tubing shall not be brittle, glazed, cracked, severely discolored, or otherwise deteriorated by direct contact with copper. The elongation of the tubing shall be not lower than 200%. The copper shall not be pitted or blackened. Darkening of the copper due to normal air oxidation shall be disregarded.
- Note 8. A specimen 1 in. in length (a 1/4 in. wide strip cut from sizes 1 and larger), shall be placed in the bottom of each of two clean 1/2 in. x 12 in. test tubes. A third test tube shall be used for control. A copper-glass mirror about 1/4 in. wide x 1 in. long shall be suspended 6 - 7 in. above the bottom of each tube by fine copper wire attached to a silicone rubber stopper wrapped in aluminum foil. The mirrors shall be vacuum-deposited copper, on one side only, with a thickness equal to $10\% \pm 5$ transmission of normal incident light of 5000 Angstroms. The coated mirrors shall be stored in vacuum and may be used for test only if no oxide film is present and the copper is not visibly damaged. The three test tubes shall be tightly sealed. The lower 2 in. of each tube shall be placed in an oven or oil bath at $175\text{ C} \pm 3$ ($347\text{ F} \pm 5.4$) for 16 hours. After cooling, the mirrors shall be examined in a good light against a white background. The copper shall not have been removed from a mirror leaving an area of transparency greater than 5% of the total area. Discoloration of the copper film shall not be considered corrosion.
- Note 9. Three specimens, in the expanded form (as supplied), each 4 in. in length, of each color shall be conditioned for 48 hr in a mechanical convection oven which is at $175\text{ C} \pm 3$ ($347\text{ F} \pm 5.4$), with an air velocity of 100 - 200 ft per min. past the specimens. After conditioning, the specimens shall be removed from the oven, cooled to room temperature, and determined to be within the limits of MIL-STD-104.
- Note 10. Tubing shall have tensile strength not lower than 1000 psi and dielectric strength not lower than 400 v per mil after being immersed for $24\text{ hr} \pm 2$ at $23\text{ C} \pm 3$ ($73.4\text{ F} \pm 5.4$) in JP-4 Fuel, SAE phosphate ester test fluid No. 1, hydraulic oil, aviation gasoline 100/130, and water. Six specimens (a total of 30), each 6 in. in length, shall be immersed in each of the fluids. The volume of the fluid shall be not less than 20 times that of the specimens. After immersion, the specimens shall be lightly wiped, air dried for 30 - 60 min. at room temperature, and subjected to the tensile strength and dielectric strength tests; three of each group of six specimens shall be tested for tensile strength and the other three for dielectric strength.
- Note 11. Fungus resistance shall be determined in accordance with ASTM D1924 except that the incubation period shall be 28 days and the test organisms shall be *Aspergillus niger*, *Aspergillus flavus*, *Penicillium luteum*, and *Trichoderma T-1*. At the end of the incubation period, not more than traces of growth on the specimens are permissible. Three specimens, each 3 in. long, shall be used for each organism.

Note 12. A specimen in the expanded form (as supplied) shall be shrunk onto a clean metallic mandrel of the configuration and size shown in Fig. 1. The tubing on the mandrel then shall be conditioned for 30 min. in an oven which is at $175\text{ C} \pm 5$ ($347\text{ F} \pm 9$), in accordance with ASTM D573. When cooled to room temperature, the tubing shall be visually examined and then shall be subjected to the following voltage withstand test. The tubing shall snugly fit the mandrel and shall not be cracked. The test potential shall be applied between the mandrel and a metal foil electrode wrapped around the largest diameter of the tubing in accordance with ASTM D876. The test potential then shall be applied in accordance with the short-time test of ASTM D149 using a 500 v per sec rate of rise. The specimen shall withstand 2000 v for 1 minute.

5.3 Dimensions After Shrinkage:

5.3.1 Diametral: Three specimens in the expanded form (as supplied), each 6 in. in length, shall be measured for length and inside diameter. The specimens shall be conditioned for 3 min. in a mechanical convection oven which is at $200\text{ C} \pm 5$ ($392\text{ F} \pm 9$), with an air velocity of 100 - 200 ft per min. past the specimens. After conditioning, the specimens shall be removed from the oven, cooled to room temperature, and then remeasured. Longer heating at such temperature shall cause no additional shrinkage. Prior to and after conditioning, the dimensions of the tubing shall be in accordance with Table II. Measurements shall be made in accordance with ASTM D876.

5.3.2 Longitudinal: In reaching its recovered dimensions, the tubing shall not exhibit a longitudinal change greater than +1%, -5%, computed as follows:

$$\% \text{ change} = \frac{\text{Length after heating} - \text{Length before heating}}{\text{Length before heating}} \times 100$$

5.4 Marking: Prior to or after shrinkage, tubing shall be capable of having numbers or characters printed on it with conventional tubing marking techniques.

6. QUALITY: The product shall be uniform in quality and condition, clean, smooth, and free from foreign materials and from imperfections detrimental to fabrication, appearance, or performance of parts.

7. STANDARD SIZES AND TOLERANCES: Unless otherwise specified, tubing shall be supplied in lengths of 48 in., +1, -0, and in the standard sizes and tolerances shown in Table II. Tolerances apply at 23 - 30 C ($73.4 - 86\text{ F}$).

TABLE II

Expanded (As Supplied) Size	ID, Inches min	Recovered Dimensions (After Heating)		
		ID, Inches max	Nominal Wall Thickness, Inch	Wall Thickness Tolerance, Inch Plus and minus
3/64	0.046	0.023	0.016	0.003
1/16	0.063	0.031	0.017	0.003
3/32	0.093	0.046	0.020	0.003
1/8	0.125	0.062	0.020	0.003
3/16	0.187	0.093	0.020	0.003
1/4	0.250	0.125	0.025	0.003
3/8	0.375	0.187	0.025	0.003
1/2	0.500	0.250	0.025	0.003
3/4	0.750	0.375	0.030	0.003
1	1.000	0.500	0.035	0.005
1-1/2	1.500	0.750	0.040	0.006
2	2.000	1.000	0.045	0.007
3	3.000	1.500	0.050	0.008
4	4.000	2.000	0.055	0.009