

**AEROSPACE
MATERIAL
SPECIFICATION**

AMS 3644/1A

Issued 7-16-79
Revised 1-1-87

Superseding AMS 3644/1

**PLASTIC ROD AND BAR, POLYIMIDE
Unfilled, Molded**

1. SCOPE:

1.1 Form: This specification covers an unfilled polyimide plastic in the form of molded rod and bar.

1.2 Application: Primarily for parts requiring low coefficient of friction, thermal resistance, and toughness up to 260°C (500°F).

2. APPLICABLE DOCUMENTS: See AMS 3644.

3. TECHNICAL REQUIREMENTS:

3.1 Basic Specification: The complete requirements for procuring the product described herein shall consist of this document and the latest issue of the basic specification, AMS 3644.

3.2 Material: Shall be an unfilled molded polyimide polymer.

3.3 Properties: Shall conform to the following requirements, determined on the product supplied and in accordance with test methods specified in AMS 3644. Specimens for elevated temperature tests shall be held at the test temperature for not less than 30 min. prior to testing. Values for tensile strength, elongation, flexural strength, and compressive strength shall be the average of three specimens for each test; no individual value shall be less than 90% of the minimum average value specified.

3.3.1 Color Brown, essentially as approved on preproduction sample

3.3.2 Tensile Strength, min avg
At 23°C + 1 (73°F + 2) 11,000 psi (75 MPa)
At 260°C + 5 (500°F + 10) 5,000 psi (35 MPa)

SAE Technical Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

AMS documents are protected under United States and international copyright laws. Reproduction of these documents by any means is strictly prohibited without the written consent of the publisher.