

Issued 1960-01
Reaffirmed 1998-11
Revised 2010-07

Superseding AMS3656F

Polytetrafluoroethylene (PTFE) Extrusions
Normal Strength, As Sintered

RATIONALE

This revision now includes the requirement for pre-production acceptance tests and recommends the use of AMS3678/1 for applications such as bearings, seals and backup rings that do not require radiographic or dielectric testing, therefore the options for Types 1 through 4 have been removed. The document has been re-formatted to a template.

1. SCOPE

1.1 Form

This specification covers a virgin, unfilled polytetrafluoroethylene (PTFE) in the form of extruded and sintered rods, tubes, and profiles.

1.2 Application

These products have been used typically for parts such as insulators and bushings requiring chemical inertness up to 500 °F (260 °C), but usage is not limited to such applications. For applications such as bearings, seals, and back-up rings that do not require dielectric properties and radiographic inspection it is recommended to use AMS3678/1 Grade B.

1.3 Safety - Hazardous Materials

While the materials, methods, applications, and processes described or referenced in this specification may involve the use of hazardous materials, this specification does not address the hazards which may be involved in such use. It is the sole responsibility of the user to ensure familiarity with the safe and proper use of any hazardous materials and to take necessary precautionary measures to ensure the health and safety of all personnel involved.

1.4 Types 1 through 4, which were defined in previous revisions of this specification, have been combined. For documentation which specifies Type 1 through Type 4 of this specification, all of the requirements of this specification now apply.

2. APPLICABLE DOCUMENTS

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2010 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
http://www.sae.org

SAE WEB ADDRESS:

**SAE values your input. To provide feedback
on this Technical Report, please visit
<http://www.sae.org/technical/standards/AMS3656G>**

2.1 SAE Publications

Available from SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001, Tel: 877-606-7323 (inside USA and Canada) or 724-776-4970 (outside USA), www.sae.org.

AMS3678 Polytetrafluoroethylene (PTFE) Moldings and Extrusions, Unfilled, Pigmented and Filled Compounds

2.2 ASTM Publications

Available from ASTM International, 100 Barr Harbor Drive, P.O. Box C700, West Conshohocken, PA 19428-2959, Tel: 610-832-9585, www.astm.org.

ASTM D 149 Dielectric Breakdown Voltage and Dielectric Strength of Solid Electrical Insulating Materials at Commercial Power Frequencies

ASTM D 4894 Polytetrafluoroethylene (PTFE) Granular Molding and Ram Extrusion Materials

ASTM D 792 Specific Gravity (Relative Density) and Density of Plastics by Displacement

3. TECHNICAL REQUIREMENTS

3.1 Material

The product shall be extruded from virgin PTFE powder conforming to ASTM D 4894 Type IV or Type V without admixture of fillers, pigments, or adulterants and shall be sintered. "Virgin" shall mean no previous heat or pressure history.

3.1.1 Color

Shall be predominantly white. Surface discoloration from sintering and/or annealing may vary from white to mottled gray or brown. Small gray, brown, or black spots are acceptable provided they do not have a detrimental effect on the finished product.

3.2 Properties

Extrusions shall conform to requirements shown in Table 1, Table 2, Table 3, and Table 4; tests shall be performed on production extrusions and in accordance with specified test methods, insofar as practicable.

3.2.1 Tensile Strength at $73\text{ }^{\circ}\text{F} \pm 2$ ($23\text{ }^{\circ}\text{C} \pm 1$)

Shall be shown in Table 1, determined in accordance with 4.3.1.

TABLE 1 - MINIMUM TENSILE STRENGTH

Form	Nominal Diameter or Distance	Nominal Diameter or Distance	Tensile Strength psi (MPa)
	Between Parallel Sides Inches	Between Parallel Sides Millimeters	
Rods, Profiles	Up to 0.500, excl	Up to 12.70, excl	1600 (11.0)
Rods, Profiles	0.500 to 1.500, incl	12.70 to 38.10, incl	1700 (11.7)
Rods, Profiles	Over 1.500	Over 38.10	1800 (12.4)
Tubes	All sizes	All sizes	1600 (11.0)

3.2.2 Elongation at 73 °F ± 2 (23 °C ± 1)

Shall be as shown in Table 2, determined in accordance with 4.3.1.

Form	Nominal Diameter or Distance	Nominal Diameter or Distance	Elongation %
	Between Parallel Sides	Between Parallel Sides	
	Inches	Millimeters	
Rods, Profiles	Up to 0.500, excl	Up to 12.70, excl	100
Rods, Profiles	0.500 to 1.500, incl	12.70 to 38.10, incl	125
Rods, Profiles	Over 1.500	Over 38.10	150
Tubes	All sizes	All sizes	100

3.2.3 Specific Gravity at 73 °F ± 2 (23 °C ± 1)

Shall be as shown in Table 3.

Form	Nominal Diameter or Distance	Nominal Diameter or Distance	Specific Gravity
	Between Parallel Sides	Between Parallel Sides	
	Inches	Millimeters	
Rods, Profiles	Up to 0.500, excl	Up to 12.70, excl	2.12 - 2.17
Rods, Profiles	0.500 to 1.500, incl	12.70 to 38.10, incl	2.13 - 2.18
Rods, Profiles	Over 1.500	Over 38.10	2.14 - 2.19
Tubes	All sizes	All sizes	2.12 - 2.17

3.2.4 Dielectric Strength, Short Time Test

Shall be as shown in Table 4, determined in accordance with 4.3.2.

Form	Nominal Diameter or Distance	Nominal Diameter or Distance	Dielectric Strength Volts/mil
	Between Parallel Sides	Between Parallel Sides	
	Inches	Millimeters	
Rods, Profiles	Up to 0.500, excl	Up to 12.70, excl	600 (23.6)
Rods, Profiles	0.500 to 1.500, incl	12.70 to 38.10, incl	650 (25.6)
Rods, Profiles	Over 1.500	Over 38.10	700 (27.6)
Tubes	All sizes	All sizes	600 (23.6)

3.3 Quality

Extrusions, as received by purchaser, shall be uniform in quality and condition, smooth, and free from foreign materials and from imperfections detrimental to usage of the extrusions.

3.3.1 Extrusions shall be radiographically inspected. Radiographic procedures and standards for acceptance shall be as agreed upon by purchaser and vendor.

3.4 Tolerances

Unless otherwise agreed between vendor and purchaser, dimensional tolerances of extrusions shown in Table 5, Table 6, and Table 7 apply at 73 to 86 °F (23 to 30 °C):

3.4.1 Rods and shapes shall be in accordance with Table 5.

TABLE 5 - DIAMETER TOLERANCES

Nominal Diameter or Distance Between Parallel Sides Inches (Millimeters)		Tolerance, plus only Inch (Millimeter)
Up to	0.250 (6.35) incl	0.008 (0.20)
Over	0.250 (6.35) to 0.500 (12.70) incl	0.016 (0.41)
Over	0.500 (12.70) to 0.750 (19.05) incl	0.020 (0.51)
Over	0.750 (19.05) to 1.000 (25.40) incl	0.024 (0.61)
Over	1.000 (25.40) to 1.250 (31.75) incl	0.030 (0.76)
Over	1.250 (31.75) to 1.500 (38.10) incl	0.038 (0.96)
Over	1.500 (38.10) to 1.750 (44.45) incl	0.046 (1.17)
Over	1.750 (44.45) to 2.000 (50.80) incl	0.052 (1.32)
Over	2.000 (50.80) to 2.250 (57.15) incl	0.068 (1.73)
Over	2.250 (57.15) to 2.500 (63.50) incl	0.076 (1.93)

3.4.2 Tubes shall be in accordance with Tables 6 and 7.

TABLE 6 - DIAMETER TOLERANCE

Nominal OD or ID Inches (Millimeters)	ID Tolerance Inch (Millimeter), minus only	OD Tolerance Inch (Millimeter), plus only
Over 0.187 (4.75) to 2.000 (50.80), incl	0.062 (1.57)	0.062 (1.57)

TABLE 7 - CONCENTRICITY TOLERANCES

Nominal ID Inches	Nominal ID Millimeters	Variation from Concentricity Inch (Millimeter), maximum (See 3.5.2.1)
Up to 0.500, incl	Up to 12.70, incl	0.020 (0.51)
Over 0.500 to 1.000, incl	Over 12.70 to 25.40, incl	0.031 (0.79)
Over 1.000 to 1.750, incl	Over 25.40 to 44.45, incl	0.045 (1.14)
Over 1.750 to 2.500, incl	Over 44.45 to 63.50, incl	0.062 (1.57)

With a zeroed dial indicator on the OD of a tube segment mounted on a tight-fitting mandrel, rotate the tube about the centerline of the ID. Alternatively, with zeroed dial indicator on the ID of a tube, rotate the tube in a V-block. In either case, note the highest positive and negative dial indicator readings; the sum of these numerical values is the maximum variation from concentricity.

Example: Highest positive reading: 0.005 inch (0.13 mm)
 Highest negative reading: 0.003 inch (0.08 mm)
 Maximum variation from concentricity: 0.008 inch (0.20 mm)

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for Inspection

The manufacturer of extrusions shall supply all test coupons and shall be responsible for the performance of all required tests for each lot of extrusions. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the extrusions conform to the specified requirements. Manufacturer of machined parts shall furnish substantiating test data acquired by the manufacturer of extrusions. Purchaser of parts machined from extrusions also reserves the right to perform confirmatory testing provided the parts will yield test coupons that conform to the testing procedure(s) listed in 4.5.

4.2 Classification of Tests

4.2.1 Acceptance Tests

All technical requirements are acceptance tests and shall be performed on each lot of extrusions (See 4.3.1).

4.3 Sampling and Testing

Shall be as follows

- 4.3.1 Sufficient test coupons shall be taken at random from each production extrusion lot to perform all required tests. Otherwise test samples shall be machined from a test or other suitable extrusion from the same resin lot. The number of determinations for each requirement shall be as specified in the applicable test procedure or, if not specified therein, not less than three.
- 4.3.2 A lot of extrusions shall be all the rods, tubes or profiles of the same configuration made from the same batch of PTFE resin in one continuous run and presented for manufacturer's inspection at one time. Where multiple shipments are made from one lot of extrusions, lot traceability shall be maintained.
- 4.3.3 A statistical sampling plan, acceptable to purchaser, may be used in lieu of sampling as in 4.3.1 and the report of 4.6 shall state that such plan was used.

4.4 Approval

- 4.4.1 Test results from sample product shall be approved by purchaser before production extrusions are supplied, unless such approval is waived by purchaser. Results of the tests on samples from the production lot shall be essentially equivalent to those on the approved sample. Production product made by a revised procedure shall not be shipped prior to receipt of reapproval. If necessary to make any change in parameters for the process control factors, manufacturer shall submit for reapproval a statement of the proposed changes in ingredients and/or processing and, when requested, sample product or test coupons shall be provided.
- 4.4.2 Manufacturer of the product shall make no significant change in material, processes, or control factors from those on which the approval was based, unless the change is approved by the purchaser's engineering department. A significant change is one which, in the judgment of the purchaser's engineering department, could affect the properties or performance of the product.

4.5 Test Methods

Shall be as follows

- 4.5.1 Tensile strength and elongation shall be determined in accordance with ASTM D 4894 and the test specimens shall be prepared from either a production extrusion as specified or from a sample extrusion of sufficient size from the same resin lot. Test specimens for rods, tubes and profiles, where size permits, shall conform to ASTM D 4894, Figure 11. For smaller sizes the test specimen for rod and for shapes shall conform to Figure 1 of this specification except that rods 0.250 inch (6.35 mm) and under in diameter may be tested in full cross-section. The initial jaw separation shall be 0.875 inch \pm 0.005 (22.2 mm \pm 0.13) and the speed of testing shall be 2 inches (50 mm) per minute. All results shall be reported.
- 4.5.2 The tensile strength coupon shall be pulled in the direction of molding (axial direction). The values shown are the minimum values required.
- 4.5.3 Specific Gravity shall be determined in accordance with ASTM D 792, Method A, with two drops of wetting agent added to the water.

4.5.4 Dielectric Strength shall be determined in accordance with ASTM D 149 on specimens 0.040 inch \pm 0.001 (1.02 mm \pm 0.03) thick. The test shall be conducted under oil using 0.062-inch (1.57-mm) diameter corrosion-resistant steel electrodes with rounded edges. If flash-over is a problem on small diameter rod or on shapes, specimens shall be prepared by drilling holes from opposite ends of a piece of product, leaving a web, 0.040 inch \pm 0.001 (1.02 mm \pm 0.03) thick, in the middle of the specimen. Electrodes shall be the same as used for the wafer specimen and shall be inserted in the holes in the specimen.

4.6 Reports

The supplier of extrusions shall furnish with each shipment a report from the manufacturer showing the results of tests on each lot to determine conformance to tensile strength, elongation, specific gravity, and dielectric strength and stating that the extrusions conform to the other technical requirements. This report shall include the purchase order number, lot number, AMS3656G and its applicable type or detail specification number, vendors compound number, form and size or part number, and quantity.

4.7 Resampling and Retesting

If any specimen used in the above tests fails to meet the specified requirements, disposition of the extrusions may be based on the results of testing three additional specimens for each original nonconforming specimen. Failure of any retest specimen to meet the specified requirements shall be cause for rejection of the extrusions represented. Results of all tests shall be reported.

5. PREPARATION FOR DELIVERY

5.1 Packaging and Identification

5.1.1 Packaging shall be accomplished to ensure that the extrusions, during shipment and storage, will not be permanently distorted and will be protected against damage from exposure to weather or any other normal hazard.

5.1.1.1 A lot of extrusions may be packaged in small quantities and delivered under the basic lot approval provided lot identification is maintained.

5.1.2 Each package shall be permanently and legibly marked with not less than the following information:

POLYTETRAFLUOROETHYLENE (PTFE) EXTRUSIONS

Normal Strength, As Sintered

AMS3656G

SIZE OR PART NUMBER _____

LOT NUMBER _____

PURCHASE ORDER NUMBER _____

QUANTITY _____

MANUFACTURER'S IDENTIFICATION _____

5.1.3 Packages of extrusions shall be prepared for shipment in accordance with commercial practice and in compliance with applicable rules and regulations pertaining to the handling, packaging, and transportation of the extrusions to ensure acceptance and safe delivery.

6. ACKNOWLEDGMENT

A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.