

Submitted for recognition as an American National Standard

**CLOTH, GLASS, VINYL COATED**

**THIS REVISION CONTAINS ONLY EDITORIAL CHANGES.**

**1. SCOPE:**

**1.1 Form** This specification covers four types of glass cloth (See 3.1) coated on both sides with a flexible, vinyl-copolymer resin, the type of glass cloth varying with nominal thickness of the product.

**1.2 Application:** Primarily for use as a nonporous, abrasion and flame resistant, trim cloth or as a covering for thermal and acoustic insulation blankets for use up to 80°C (180°F).

**2. APPLICABLE DOCUMENTS:** The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

**2.1 SAE Publications:** Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.

**2.1.1 Aerospace Material Specifications:**

AMS 2350 - Standards and Test Methods

Am 2810 - Identification and Packaging, Elastomeric Products

**2.2 ASTM Publications:** Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103

ASTM D471 - Rubber Property - Effect of Liquids

ASTM D573 - Rubber-Deterioration in An Air Oven

ASTM D751 - Testing Coated Fabrics

ASTM D3389 - Testing Coated Fabrics - Abrasion Resistance (Rotary Platform Double-Head Abrader)

SAETechnical Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

AMS documents are protected under United States and international copyright laws. Reproduction of these documents by any means is strictly prohibited without the written consent of the publisher.

**2.3 U.S. Government Publications:** Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120, except as specified in 2.3.2.

**2.3.1 Federal Specifications:**

TT-L-32 - Lacquer, Cellulose Nitrate, Glass, for Aircraft Use

**2.3.2 Federal Aviation Administration Regulations:** Available from Superintendent of Documents, U.S. Government Printing Office, Washington, DC 20402.

FAR Part 25 - Airworthiness Standards: Transport Category Airplanes

**3. TECHNICAL REQUIREMENTS:**

**3.1 Material:** Shall be glass cloth coated with a flexible, vinyl-copolymer resin of uniform thickness on both faces to produce products conforming to the requirements of Table I and 3.2.

**TABLE I**

Glass Cloth Type	Nominal Thickness		Coated Weight	
	Inch	Millimetre	Oz per sq yd	g/m <sup>2</sup>
108	0.0045	0.114	4.5 ± 0.5	152 ± 17
119	0.005	0.13	5.0 ± 0.5	170 ± 17
118	0.007	0.18	8.0 ± 0.5	271 ± 17
126	0.011	0.28	11.0 ± 1.0	373 ± 34

**3.1.1 Color:** Shall be at the option of the vendor unless aluminum or other specific color is ordered.

**3.1.2 Finish:** Shall be nonglossy.

**3.2 Properties:** The product shall conform to the following requirements; tests shall be performed on the product supplied and in accordance with specified test methods, insofar as practicable.

**3.2.1 As Received:**

**3.2.1.1 Breaking Strength:** Shall be as specified in Table II, determined in accordance with ASTM D751, Grab Method.

**TABLE II**

Nominal Thickness Inch	Breaking Strength, minimum lbf per in. width	
	Warp	Fill
0.0045	70	40
0.005	125	100
0.007	190	140
0.011	225	195

**TABLE II (SI)**

Nominal Thickness Millimetre	Breaking Strength, minimum kN/m width	
	Warp	Fill
0.114	12.2	7.0
0.13	21.9	17.5
0.18	33.3	24.5
0.28	39.4	34.1

- 3.2.1.2 **Flammability:** The time to cease burning shall be not more than 15 seconds, determined in accordance with FAR 25.853(a) and Appendix F.
- 3.2.1.3 **Flexibility:** The product shall withstand, without cracking or peeling of the coating from the cloth, bending rapidly at 20° - 30°C (68° - 86°F) flat on itself.
- 3.2.1.4 **Water Permeability:** The product shall not leak more than 10 mL of water in 100 minutes under an 8-inch (203-mm) head of water when clamped over a 4-1/2-inch (114-mm) diameter hole in a reservoir.
- 3.2.1.5 **Abrasion Resistance:** The product neither shall decrease in thickness by more than 0.0005 inch (0.013 mm) nor shall the glass cloth be exposed in 1000 cycles, determined in accordance with 4.5.1; if aluminum colored coatings are ordered, the loss in thickness shall be as agreed upon by purchaser and vendor.
- 3.2.1.6 **Solvent Resistance:** The product shall withstand, without developing surface tackiness, decomposition, delamination, or excessive curling or cracking of the coating, immersion at 20° - 30°C (68° - 86°F) in the fluids and for the times shown in Table III; separate specimens shall be immersed in each fluid.

**TABLE III**

Fluid	Immersion Time
ASTM Fuel B (ASTM D471)	10 minutes ± 0.5
ASTM Oil No. 3 (ASTM D471)	15 minutes ± 0.5
Tap Water	8 hours ± 0.25

- 3.2.2 **Heat Resistance:** The product, aged in accordance with ASTM D573 for 24 hours ± 0.25 at 100°C ± 1 (212°F ± 2), shall show neither undue surface tackiness nor loss of adhesion of the coating to the cloth and shall pass the flexibility (3.2.1.3) and water permeability (3.2.1.4) tests.
- 3.2.3 **Low-Temperature Resistance:** The product, maintained at -55°C ± 1 (-65°F ± 2) for 5 hours ± 0.25, shall withstand, without cracking, peeling, or delamination: bending rapidly at -55°C ± 1 (-65°F ± 2) through an angle of 180 degrees around a 1/4-inch (6-mm) diameter mandrel.

- 3.2.4 **Cleanability:** The product shall not be adversely affected when cleaned by rubbing lightly with soap solution or Stoddard's solvent to remove exhaust soot, oil, and grease.
- 3.2.5 **Weathering:** When specified, the product shall have weather resistance acceptable to the purchaser, determined by a procedure agreed upon by purchaser and vendor.
- 3.2.6 **Corrosion:** The product shall not have a corrosive effect on other materials when exposed to conditions normally encountered in service, determined by a procedure agreed upon by purchaser and vendor. Discoloration of metal shall not be considered objectionable.
- 3.2.7 **Plasticizer Migration:** When in contact with TT-L-32 lacquer, the product shall not cause tackiness of the finish.
- 3.3 **Quality:** The product, as received by purchaser, shall be uniform in quality and condition, clean, free from blisters, tears, cracks, and uncoated areas, as free from foreign materials as commercially practicable, and free from other imperfections detrimental to its use.
- 3.4 **Tolerances:** Shall be as specified in Table IV.

TABLE IV

Nominal Thickness Inch	Tolerance, Inch plus and minus
0.0045	0.0010
0.005	0.001
0.007	0.001
0.011	0.002

TABLE IV (SI)

Nominal Thickness Millimetre	Tolerance, Millimetre plus and minus
0.114	0.025
0.13	0.02
0.18	0.02
0.28	0.05

#### 4. QUALITY ASSURANCE PROVISIONS:

- 4.1 **Responsibility for Inspection:** The vendor of the product shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.6. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to the requirements of this specification.

#### 4.2 Classification of Tests:

**4.2.1 Acceptance Tests:** Tests to determine conformance to the following requirements are classified as acceptance tests and shall be performed on each lot:

Requirement	Paragraph
Material	3.1
Breaking Strength	3.2.1.1
Flammability	3.2.1.1
Heat Resistance	3.2.2
Quality	3.3

**4.2.2 Preproduction Tests:** Tests to determine conformance to all technical requirements of this specification are classified as preproduction tests and shall be performed prior to or on the initial shipment of cloth to a purchaser, when a change in material, processing, or both requires reapproval as in 4.4.2, and when producer deems confirmatory testing to be required.

**4.2.2.1** For direct U.S. Military procurement, substantiating test data and, when requested, preproduction test material shall be submitted to the cognizant agency as directed by the procuring activity, contracting officer, or request for procurement.

**4.3 Sampling:** Sufficient product shall be taken at random from each lot to perform all required tests. The number of determinations for each requirement shall be as specified in the applicable test procedure or, if not specified therein, not less than three.

**4.3.1** A lot shall be all product from the same batch of compound and same roll of cloth processed in one continuous run and presented for vendor's inspection at one time. A lot may be packaged in small quantities and delivered under the basic lot approval provided lot identification is maintained.

**4.3.2** A batch shall be the quantity of compound run through a mill or mixer at one time.

**4.3.3** When a statistical sampling plan and acceptance quality level (AQL) have been agreed upon by purchaser and vendor, sampling shall be in accordance with such plan in lieu of sampling as in 4.3.1 and the report of 4.6.1 shall state that such plan was used.

**4.4 Approval:**

**4.4.1** Sample cloth shall be approved by purchaser before cloth for production use is supplied, unless such approval be waived by purchaser. Results of tests on production cloth shall be essentially equivalent to those on the approved sample.