



<b>AEROSPACE MATERIAL SPECIFICATION</b>	<b>AMS3670™/5</b>	<b>REV. D</b>
	Issued 1984-07 Reaffirmed 2000-12 Revised 2021-05	
Superseding AMS3670/5C		
(R) Bars, Rods, and Shapes Produced from 30% Carbon Fiber Filled Polyamide-Imide (PAI) Material		

### RATIONALE

This standard has been updated to include technical and editorial changes.

#### 1. SCOPE

##### 1.1 Form

This specification covers molded or extruded bar, rod, and shapes produced from a polyamide-imide polymer filled with 30% carbon fiber. This is designated as Grade 5 material per AMS3670.

##### 1.2 Application

These products have been used typically for parts requiring high strength, high modulus, thermal resistance, and toughness up to 446 °F (230 °C), but usage is not limited to such applications. Each application should be considered individually.

##### 1.3 Type

The type shall designate the process used to produce the bar, rod, or shapes.

Type I Bar, rod, or shapes produced via the injection molded process or raw material used to produce the shapes.

Type II Bar, rod, or shapes produced via the extrusion process.

Type III Bar, rod, or shapes produced via the compression molding process.

When no type is specified, Type I shall be supplied.

#### 2. APPLICABLE DOCUMENTS

Refer to AMS3670.

SAE Executive Standards Committee Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2021 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

**TO PLACE A DOCUMENT ORDER:** Tel: 877-606-7323 (inside USA and Canada)  
Tel: +1 724-776-4970 (outside USA)  
Fax: 724-776-0790  
Email: CustomerService@sae.org  
http://www.sae.org

SAE WEB ADDRESS:

For more information on this standard, visit  
<https://www.sae.org/standards/content/AMS3670/5D/>

### 3. TECHNICAL REQUIREMENTS

#### 3.1 Basic Specification

The complete requirements for procuring the product described herein shall consist of this document and the latest issue of the basic specification, AMS3670.

#### 3.2 Material

Shall be a a bar, rod, or shape produced from polyamide-imide polymer filled with 30% ± 3% by weight carbon fiber.

#### 3.3 Properties

The bar, rod, shapes shall conform to the requirements shown in Table 1. Physical properties shall be determined on test specimens specified in the parts standard, drawing, or purchase document. If not specified, determined on post-cured test specimens produced by the indicated process and in accordance with specified test methods. Specimens for elevated temperature tests shall be held at the test temperature for not less than 30 minutes prior to testing. Values for tensile strength, elongation, flexural strength, and compressive strength shall be reported as the average of three determinations for each test; no individual value shall be less than 90% of the minimum value specified.

**Table 1 - Properties**

	Property	Type I	Type II	Type III	Test Method
3.3.1	Color	Black, or as approved on preproduction sample	Black, or as approved on preproduction sample	Black, or as approved on preproduction sample	
3.3.2	Tensile strength, min avg At 73 °F ± 2 °F (23 °C ± 1 °C) At 446 °F ± 9 °F (230 °C ± 5 °C)	23.0 ksi (158 MPa) 13.0 ksi (89.6 MPa)	20.0 ksi (137.8 MPa)	10.0 ksi (68.9 MPa)	ASTM D1708, Speed B, 1/8 inch specimen
3.3.3	Elongation, min avg At 73 °F ± 2 °F (23 °C ± 1 °C)	4%	1.5%	1.5%	ASTM D1708, Speed B, 1/8 inch specimen
3.3.4	Tensile modulus, min At 73 °F ± 2 °F (23 °C ± 1 °C)	2.8 Msi (19.3 GPa)	1.0 Msi (6.8 GPa)	0.5 Msi (3.4 GP)	ASTM D1708, Speed B, 1/8 inch specimen
3.3.5	Flexural strength, min avg At 73 °F ± 2 °F (23 °C ± 1 °C) At 446 °F ± 9 °F (230 °C ± 5 °C)	43.0 ksi (296 MPa) 21.0 ksi (145 MPa)	N/A	15.0 ksi (103.4 MPa)	ASTM D790 or ASTM D790M
3.3.6	Compressive strength, min avg At 73 °F ± 2 °F (23 °C ± 1 °C)	29.5 ksi (203 MPa)	30.0 ksi (206.8 MPa)	40.0 ksi (275.7 MPa)	ASTM D695 or ASTM D695M
3.3.7	Specific gravity at 73/73 °F ± 2 °F (23/23 °C ± 1 °C)	1.46 to 1.51	1.46 to 1.51	1.46 to 1.53	ASTM D792 Method A
3.3.8	Water absorption, max 24.0 to 24.5 hours At 73 °F ± 2 °F (23 °C ± 1 °C)	0.4%	0.4%	0.4%	ASTM D570
3.3.9	Heat deflection temp, min 1/8 inch (3.2 mm) specimen 264 psi (1820 kPa) fiber stress	500 °F (260 °C)	500 °F (260 °C)	500 °F (260 °C)	ASTM D648

### 4. QUALITY ASSURANCE PROVISIONS

Refer to AMS3670.

### 5. PREPARATION FOR DELIVERY

Refer to AMS3670.