

SAE The Engineering Society
For Advancing Mobility
Land Sea Air and Space®
INTERNATIONAL

400 Commonwealth Drive, Warrendale, PA 15096-0001

AEROSPACE MATERIAL SPECIFICATION

SAE

AMS 3671B

Issued 15 OCT 1980
Revised 1 OCT 1992

Superseding AMS 3671A

Submitted for recognition as an American National Standard

PLASTIC MOLDING COMPOUND, NOVOLAC EPOXY RESIN,
SHORT GLASS FIBER REINFORCED, STRUCTURAL

This specification has been declared "NONCURRENT" by the Aerospace Materials Division, SAE, as of July, 1992. It is recommended, therefore, that this specification not be specified for new designs.

This cover sheet should be attached to revision "A" of the subject specification.

"NONCURRENT" refers to those materials which have previously been widely used and which may be required on some existing designs in the future. The Aerospace Materials Division, however, does not recommend these as standard materials for future use in new designs. Each of these "NONCURRENT" specifications is available from SAE upon request.

PREPARED UNDER THE JURISDICTION OF AMS COMMITTEE "CP".

SAE Technical Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

H-63-08

SAE The Engineering Society
For Advancing Mobility
Land Sea Air and Space

400 COMMONWEALTH DRIVE, WARRENDALE, PA 15096

AEROSPACE MATERIAL SPECIFICATION

Submitted for recognition as an American National Standard

AMS 3671A

Issued 10-15-80
Revised 4-1-87

Superseding AMS 3671

PLASTIC MOLDING COMPOUND, NOVOLAC EPOXY RESIN,
SHORT GLASS FIBER REINFORCED, STRUCTURAL

1. SCOPE:

1.1 Form: This specification covers a modified novolac epoxy resin in the form of a chopped-glass-fiber filled molding compound processed to a dry "B" stage condition.

1.2 Application: Primarily for high-pressure compression molding, useful in fabrication of parts with good properties up to 135°C (275°F).

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

2.1 SAE Publications: Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

AMS 2350 - Standards and Test Methods
AMS 2825 - Material Safety Data Sheets

SAE Technical Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

AMS documents are protected under United States and international copyright laws. Reproduction of these documents by any means is strictly prohibited without the written consent of the publisher.

2.2 ASTM Publications: Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

- ASTM D651 - Tensile Strength of Molded Electrical Insulating Materials
- ASTM D696 - Coefficient of Linear Thermal Expansion of Plastics
- ASTM D731 - Molding Index of Thermosetting Molding Powder
- ASTM D790 - Flexural Properties of Unreinforced and Reinforced Plastics and Electrical Insulating Materials
- ASTM D792 - Specific Gravity and Density of Plastics by Displacement
- ASTM D2584 - Ignition Loss of Cured Reinforced Resins
- ASTM D3530 - Volatiles Content of Carbon Fiber-Epoxy Prepreg
- ASTM F501 - Aerospace Materials Response to Flame, with Vertical Test Specimen (for Aerospace Vehicles Standard Conditions)

2.3 U.S. Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

2.3.1 Military Specifications:

MIL-R-60346 - Roving, Glass, Fibrous (for Filament Winding Applications)

2.3.1 Military Standards:

MIL-STD-794 - Parts and Equipment, Procedures for Packaging and Packing of

3. TECHNICAL REQUIREMENTS:

3.1 Product: The molding compound shall be manufactured from a modified epoxy resin filled with chopped glass roving and processed to a dry "B" stage without tack.

3.1.1 Resin: Shall be a novolac epoxy resin modified as necessary to meet the requirements of 3.2.

3.1.2 Roving: Shall be chopped "E" glass fiber capable of producing the properties specified in Table I. When specified by purchaser, the roving shall meet the requirements of MIL-R-60346, Type I, Class 1.

3.1.3 Storage Life: The product shall meet the requirements of this specification when tested at any time up to 12 months from date of receipt by purchaser, provided it has been stored in the original sealed container at not higher than 5°C (40°F).

3.1.4 Shelf Life: The product shall meet the requirements of this specification when tested after continuous exposure to a relative humidity not higher than 70% and a temperature not higher than 30°C (85°F) for not less than three months.

3.2 Properties: The product shall conform to the following requirements:

3.2.1 **Uncured Product:** Shall be as follows; tests shall be performed on the as-received product, after warming to above the dew point prior to sampling, in accordance with test methods specified herein:

3.2.1.1	Resin Content	36% \pm 3	ASTM D2584
3.2.1.2	Roving Length	0.5 in. \pm 0.01 (12.5 mm \pm 0.25)	Visual
3.2.1.3	Cup Flow, Cup Closing Time	18 - 24 sec	ASTM D731
3.2.1.4	Volatile Content, max	0.5%	ASTM D3530

3.2.2 **Cured Product:** Shall be as specified in Table I; tests shall be performed in accordance with specified test methods on molded specimens prepared in accordance with 4.5.1. Specimens for elevated temperature tests shall be held at the test temperature for not less than 30 min. prior to testing. Values for tensile strength, flexural strength, and flexural modulus shall be the average of five specimens for each test; no individual value shall be less than 90% of the minimum average value specified.

TABLE I

Test Number	Property	Test Temperature		Test Method
		77°F \pm 9	275°F \pm 9	
1	Tensile Strength, min avg	25,000 psi	18,000 psi	ASTM D651
2	Flexural Strength, min avg	60,000 psi	45,000 psi	ASTM D790
3	Flexural Modulus, min avg	3,500,000 psi	2,800,000 psi	ASTM D790
4	Coefficient of Linear Thermal Expansion, in. per in. per °F, max	20 x 10 ⁻⁶	--	ASTM D696
5	Specific Gravity	1.85 to 1.95	--	ASTM D792

TABLE I(SI)

Test Number	Property	Test Temperature		Test Method
		25°C \pm 5	135°C \pm 5	
1	Tensile Strength, min avg	170 MPa	125 MPa	ASTM D651
2	Flexural Strength, min avg	415 MPa	310 MPa	ASTM D790
3	Flexural Modulus, min avg	25 GPa	20 GPa	ASTM D790
4	Coefficient of Linear Thermal Expansion, (mm/mm)/°C, max	36 x 10 ⁻⁶	--	ASTM D696
5	Specific Gravity	1.85 to 1.95	--	ASTM D792

3.2.2.1 Flame Resistance: Time to extinguish, defined as the total of flame time and glow time, shall not exceed 5.0 sec average or 6.0 sec individual. Burn length shall not exceed 6.0 in. (150 mm) average or 7.2 in. (180 mm) individual. Specimens shall be tested in the vertical position with 60 sec \pm 1 flame exposure in accordance with 4.5.2.

3.3 Quality: The molding compound, as received by purchaser, shall be uniform in quality and condition, clean, and free from foreign materials and other contaminants detrimental to usage of the compound.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection: The vendor of the product shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.6. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to the requirements of this specification.

4.2 Classification of Tests:

4.2.1 Acceptance Tests: Tests to determine conformance to requirements for resin content (3.2.1.1), roving length (3.2.1.2), cup flow (3.2.1.3), volatile content (3.2.1.4), flexural strength at 77°F (25°C) (Table I, Test No. 2), specific gravity cured (Table I, Test No. 5), and quality (3.3) are classified as acceptance tests and shall be performed on each lot.

- 4.2.2 Preproduction Tests: Tests to determine conformance to all technical requirements of this specification are classified as preproduction tests and shall be performed prior to or on the initial shipment of the product to a purchaser, when a change in material, processing, or both requires reapproval as in 4.4.2, and when purchaser deems confirmatory testing to be required.
- 4.2.2.1 For direct U.S. Military procurement, substantiating test data and, when requested, preproduction test material shall be submitted to the cognizant agency as directed by the procuring activity, the contracting officer, or the request for procurement.
- 4.3 Sampling: Shall be as follows:
- 4.3.1 For Acceptance Tests: A sufficient quantity of compound shall be selected at random from each lot to perform all required tests. The number of determinations for each requirement shall be as specified in the applicable test procedure or, if not specified therein, not less than three except that for tensile strength, flexural strength, and flexural modulus shall be not less than five.
- 4.3.1.1 A lot shall be all compound produced in a single production run from the same batches of polymer and chopped roving and presented for vendor's inspection at one time. A lot shall not exceed 1000 lb (450 kg) and may be packaged and delivered in smaller quantities under a basic lot approval provided lot identification is maintained.
- 4.3.1.2 When a statistical sampling plan and acceptance quality level (AQL) have been agreed upon by purchaser and vendor, sampling shall be in accordance with such plan in lieu of sampling as in 4.3.1 and the report of 4.6.1 shall state that such plan was used.
- 4.3.2 For Preproduction Tests: As agreed upon by purchaser and vendor.
- 4.4 Approval:
- 4.4.1 Sample compound shall be approved by purchaser before compound for production use is supplied, unless such approval be waived by purchaser. Results of tests on production compound shall be essentially equivalent to those on the approved sample.
- 4.4.2 Vendor shall use ingredients, manufacturing procedures, processes, and methods of inspection on production compound which are essentially the same as those used on the approved sample. If necessary to make any change in ingredients, in type of equipment for processing, or in manufacturing procedures, vendor shall submit for reapproval a statement of the proposed changes in material, processing, or both and, when requested, sample compound. Production compound made by the revised procedure shall not be shipped prior to receipt of reapproval.

4.5 Test Methods:

4.5.1 Specimen Preparation: Each container of compound to be sampled shall be allowed to warm above the dew point before opening the sealed package for sampling. Immediately after sampling, the container shall be resealed and returned to proper storage.

4.5.1.1 Test of Uncured Product: Shall be performed on room temperature compound immediately after sampling.

4.5.1.2 Tests of Cured Product: Shall be performed on molded specimens 0.125 in. \pm 0.010 (3.00 mm \pm 0.25) thick using the manufacturer's recommended cure time, temperature, and pressure.

4.5.1.2.1 Tensile Specimens: Shall be in accordance with ASTM D651.

4.5.1.2.2 Flexural Specimens: Shall be 0.125 x 1.000 x 4.00 in. (3.00 x 25 x 100 mm).

4.5.2 Flame Resistance: Shall be determined in accordance with ASTM F501, using three specimens, 0.060 in. \pm 0.010 (1.5 mm \pm 0.25) thick x 3.0 x 12.0 in. (75 x 300 mm), with the 12-in. (300-mm) dimension vertical.

4.6 Reports:

4.6.1 The vendor of the product shall furnish with each shipment a report showing the results of tests to determine conformance to the acceptance test requirements and stating that the product conforms to the other technical requirements of this specification. This report shall include the purchase order number, AMS 3671A, vendor's product identification, lot number, and quantity.

4.6.1.1 A material safety data sheet conforming to AMS 2825, or equivalent, shall be supplied to each purchaser prior to, or concurrent with, the report of preproduction test results or, if preproduction testing be waived by purchaser, concurrent with the first shipment of compound for production use. Each request for modification of compound formulation shall be accompanied by a revised data sheet for the proposed formulation.

4.7 Resampling and Retesting: If any specimen used in the above tests fails to meet the specified requirements, disposition of the compound may be based on the results of testing three additional specimens cut from the same test panels, or newly prepared test panels cured to the same parameters, for each original nonconforming specimen. Failure of any retest specimen to meet the specified requirements shall be cause for rejection of the compound represented and no additional testing shall be permitted. Results of all tests shall be reported.

5. PREPARATION FOR DELIVERY:

5.1 Packaging and Identification: