

Issued 1999-03
Reaffirmed 2006-06
Revised 2010-11
Supersedes AMS3678/6

**Type 6
60% Bronze Filled Virgin Polytetrafluoroethylene (PTFE) Moldings or Extrusions**

RATIONALE

This document is being revised to clear up some editorial issues and to maintain the same revision date for AMS3678 and all the accompanying slash sheets.

1. SCOPE

1.1 Form

This specification covers a polytetrafluoroethylene (PTFE) resin filled with 60% bronze powder in the form of extruded or molded rods or tubes which are sintered after molding or, in the case of extrusions, sintered during the extrusion process.

1.2 Application

These products have been used typically for bearing and wear ring applications in a lubricated environment against steel, stainless steel, and chromium plate, and requiring dimensional stability up to 450 °F (232 °C), but usage is not limited to such applications. Each application should be considered individually.

2. APPLICABLE DOCUMENTS

See AMS3678.

3. TECHNICAL REQUIREMENTS

3.1 Basic Specification

The complete requirements for procuring the products described herein shall consist of this document and the latest issue of the basic specification, AMS3678.

3.2 Material

All products shall be molded or extruded from virgin polytetrafluoroethylene (PTFE) powder conforming to ASTM D 4894, Type II or Type IV, uniformly blended with the specified filler. The blended powder shall consist of 60% ± 4 bronze powder and the remainder virgin PTFE powder, filler percentage measured by weight.

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising there from, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2010 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
http://www.sae.org

SAE WEB ADDRESS:

**SAE values your input. To provide feedback
on this Technical Report, please visit
<http://www.sae.org/technical/standards/AMS3678/6A>**