

Type 9
Virgin Polytetrafluoroethylene (PTFE) Moldings with Pigment for AS4716 and AS5857 Backup
Rings

RATIONALE

This document is being revised to add the materials required for back-up rings for use in AS5857 glands.

1. SCOPE

1.1 Form

This specification covers a polytetrafluoroethylene (PTFE) resin filled with inorganic pigment in the form of molded rods or tubes which are sintered after molding. The blue colored material is designated for use in rod glands only and the yellow colored material is designated for use in piston glands only. The brown colored material is designated for use in AS 5857 rod glands only and the green colored material is designated for use in AS 5857 piston glands only.

1.2 Application

These products are to be used as backup rings in AS 4716 Glands for both static and dynamic applications and in AS 5857 Glands for static applications where dimensional stability up to 450 °F (232 °C) with good mechanical properties is required, but usage is need not be limited to such applications. Each application should be considered individually.

2. APPLICABLE DOCUMENTS

See AMS 3678.

3. TECHNICAL REQUIREMENTS

3.1 Basic Specification

The complete requirements for procuring the products described herein shall consist of this document and the latest issue of the basic specification, AMS 3678.

3.2 Material

All products shall be molded from virgin polytetrafluoroethylene (PTFE) powder conforming to ASTM D 4894, Type II or Type IV, and should contain 2% or less of inorganic pigment to provide a uniform color throughout the material.

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2006 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
SAE WEB ADDRESS: <http://www.sae.org>