

**Polytetrafluoroethylene (PTFE) Moldings and Extrusions  
Unfilled, Pigmented, and Filled**

**RATIONALE**

This document has been revised to better define product and express the test requirements more succinctly. Additional materials have also been added.

**1. SCOPE**

**1.1 Form**

This specification covers several grades of virgin polytetrafluoroethylene (PTFE) resin which may be compounded with pigment and fillers in the form of extruded or molded rods or tubes which are sintered after molding or, in the case of extrusions, sintered during the extrusion process.

**1.2 Application**

These products have been used typically for the production of mechanical parts such as back-up rings, seals, and bearings requiring dimensional stability up to 450 °F (232 °C) with good mechanical properties, but usage is not limited to such applications. Each application should be considered individually.

**1.3 Safety - Hazardous Materials**

While the materials, methods, applications, and processes described or referenced in this specification may involve the use of hazardous materials, this specification does not address the hazards which may be involved in such use. It is the sole responsibility of the user to ensure familiarity with the safe and proper use of any hazardous materials and to take necessary precautionary measures to ensure the health and safety of all personnel involved.

**2. APPLICABLE DOCUMENTS**

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent supplied herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising there from, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2010 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

**TO PLACE A DOCUMENT ORDER:** Tel: 877-606-7323 (inside USA and Canada)  
Tel: +1 724-776-4970 (outside USA)  
Fax: 724-776-0790  
Email: CustomerService@sae.org  
http://www.sae.org

**SAE WEB ADDRESS:**

**SAE values your input. To provide feedback  
on this Technical Report, please visit  
<http://www.sae.org/technical/standards/AMS3678C>**

## 2.1 SAE Publications

Available from SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001, Tel: 877-606-7323 (inside USA and Canada) or 724-776-4970 (outside USA), [www.sae.org](http://www.sae.org).

AS4716 Gland Design, O-Ring and Other Elastomeric Seals

AS5857 Gland Design, O-Ring and Other Elastomeric Seals, Static Applications

## 2.2 ASTM Publications

Available from ASTM International, 100 Barr Harbor Drive, P.O. Box C700, West Conshohocken, PA 19428-2959, Tel: 610-832-9585, [www.astm.org](http://www.astm.org).

ASTM D 792 Density and Specific Gravity (Relative Density) of Plastics by Displacement

ASTM D 4745 Filled Compounds of Polytetrafluoroethylene (PTFE) Molding and Extrusion Materials

ASTM D 4894 Polytetrafluoroethylene (PTFE) Granular Molding and Ram Extrusion Materials

## 2.3 U.S. Government Publications

Available from the Document Automation and Production Service (DAPS), Building 4/D, 700 Robbins Avenue, Philadelphia, PA 19111-5094, Tel: 215-697-6257, <http://assist.daps.mil/quicksearch/>.

FED-STD-595 Colors Used in Government Procurement

## 3. TECHNICAL REQUIREMENTS

### 3.1 Detail Specifications

The requirements for a specific product shall consist of all requirements specified herein in addition to requirements specified in the applicable detail specification. In case of conflict between requirements of this specification and an applicable detail specification, requirements of the detail specification shall govern.

### 3.2 Material

All products shall be molded or extruded from fresh virgin or filled polytetrafluoroethylene (PTFE) powder. The virgin PTFE powder used in both unfilled and filled compounds to this specification shall conform to ASTM D 4894, Type II or Type IV. Type III PTFE powder is allowed for Type 12 and Type 13 materials. The blending of fillers with the virgin PTFE for each type shall be as shown in Table 1.

TABLE 1 - MATERIAL TYPES

Type	Description	Detail Specification
1	Virgin PTFE, Grades A and B	AMS3678/1A
2	PTFE filled with 15% graphite	AMS3678/2
3	PTFE filled with 15% glass fiber and 5% molybdenum disulfide	AMS3678/3
4	PTFE filled with 25% glass fiber	AMS3678/4
5	PTFE filled with inorganic pigment	AMS3678/5
6	PTFE filled with 60% bronze powder	AMS3678/6
7	PTFE filled with 23% carbon and 2% graphite	AMS3678/7
8	PTFE filled with 10% carbon fiber	AMS3678/8
9	PTFE filled with inorganic pigment (AS4716 & AS5857)	AMS3678/9
10	PTFE filled with 15% carbon fiber	AMS3678/10
11	PTFE filled with 10% aromatic polymer	AMS3678/11
12	PTFE filled with 10% mineral and 2.5% molybdenum disulfide	AMS3678/12
13	PTFE filled with 10% polyimide	AMS3678/13
14	PTFE filled with 40% bronze powder	AMS3678/14
15	PTFE filled with 15% aromatic polymer	AMS3678/15
16	PTFE filled with 15% polyimide	AMS3678/16

- 3.2.1 Virgin polytetrafluoroethylene shall mean resin that has no pigment or filler added and the resin has not experienced any previous pressure or heat history.
- 3.2.2 Filled material shall mean that at least one pigment or filler has been uniformly blended with the virgin PTFE polymer prior to any pressure or heat process. The percentage(s) of pigment(s) or filler(s) added shall be measured by weight.
- 3.2.3 Pigmented material shall mean that a small percentage of inorganic pigment which may also include a color enhancing agent, total additive(s) usually less than 2% by weight, has been added to color the material and uniformly blended.
- 3.2.4 Type 1 material is used typically for backup rings and seal components for static and light duty dynamic applications. Type 1 materials can be used to seal against steel, stainless steel, chromium plating, bronze, bare or anodized aluminum and aluminum alloys, and ceramic coatings. Type 1 materials have the highest wear rate and lowest coefficients of friction. Type 1 materials are classified as Grade A and Grade B. Unless Grade A is ordered, Type 1, Grade B shall be supplied.
- 3.2.5 Type 2 material is used typically in seal components for dynamic reciprocating and rotary applications. Type 2 materials have better extrusion resistance than Type 1 materials. Type 2 materials can be used to seal against the same materials as Type 1 materials. Type 2 materials have much better wear resistance than Type 1 materials with slightly higher coefficients of friction.
- 3.2.6 Type 3 material is used typically in seal components where resistance to high temperature and pressure is required along with very good wear resistance. Type 3 materials are used to seal against steel, stainless steel, and chromium plate in a lubricated environment.
- 3.2.7 Type 4 material is used typically for dynamic seals. Type 4 materials have better extrusion resistance but slightly higher coefficients of friction than Type 3 materials. Type 4 materials are used to seal against the same materials as Type 3 materials in a lubricated environment.
- 3.2.8 Type 5 material is used typically for backup rings and seal elements in both static and dynamic applications. Type 5 materials have essentially the same physical properties as Type 1 materials with better wear resistance as a result of the presence of the inorganic pigment. Type 5 material is used to seal against steel (with the exception of nitrided steel), stainless steel, chromium plate, and anodized aluminum and aluminum alloys in both dry and lubricated environments. As opposed to Type 1 and Type 2 materials, Type 5 materials should not be used against bare aluminum or aluminum alloy.

- 3.2.9 Type 6 material is used typically for bearing and wear ring applications in a lubricated environment against steel, stainless steel, and chromium plate. Type 6 material has very good compressive strength and abrasion resistance.
- 3.2.10 Type 7 material is used in seal components for dynamic and static applications. Type 7 materials have excellent extrusion resistance and good wear resistance. Type 7 material will function well in lubricated and non-lubricated environments. Type 7 materials are used against chromium plate and steel.
- 3.2.11 Type 8 material is used in seal components for dynamic and static applications. Type 8 materials have excellent extrusion resistance and long wear life. Type 8 materials are used against chromium plate and steel.
- 3.2.12 Type 9 material is used typically for backup rings for AS4716 and AS5857 glands. For the AS4716 glands the bright blue is designated for rod glands and the bright yellow for piston glands in both static and dynamic applications. For AS5857 glands the medium brown color is designated for piston glands and the medium green color for rod glands in static applications. Type 9 materials are supplied in Grades A and B. Type 9 material is used to seal against steel (with the exception of nitrided steel), stainless steel, chromium plate, and anodized aluminum and aluminum alloys in both dry and lubricated environments. As opposed to Type 1 and Type 2 materials, Type 9 materials should not be used against bare aluminum or aluminum alloy.
- 3.2.13 Type 10 material is used in seal components for dynamic and static applications. Type 10 materials have excellent extrusion resistance and long wear life. Type 10 materials are used against chromium plate and steel.
- 3.2.14 Type 11 material is used in seal components for dynamic and static applications. Type 11 materials have excellent wear resistance and their non abrasive nature prevents galling of softer mating surfaces. They should not be used in a water environment.
- 3.2.15 Type 12 material is used typically in seal components where resistance to high temperature and pressure is required along with very good wear resistance against softer stainless steels and aluminum. Type 12 materials are similar to glass filled materials with less abrasiveness.
- 3.2.16 Type 13 material is used in seal components for dynamic and static applications where resistance to high temperature and pressure is required. They will not abrade mating surfaces and have low coefficients of friction.
- 3.2.17 Type 14 is used typically for bearing and wear ring applications in a lubricated environment against steel, stainless steel, and chromium plate. Type 14 material has very good compressive strength and abrasion resistance.
- 3.2.18 Type 15 material is used in compressor rings and seal components for dynamic and static applications. Type 15 materials have excellent wear resistance and their non abrasive nature prevents galling of softer mating surfaces. They should not be used in a water environment.
- 3.2.19 Type 16 material is used typically for bearing and seal components for dynamic and static applications. Type 16 materials have low coefficients of friction. They will not abrade mating surfaces and have low wear rates even in dry environments. They are excellent materials for dry running compressor rings.
- 3.2.20 Unless a specific type is ordered, Type 1, Grade B shall be supplied.

### 3.3 Properties

The product shall conform to the requirements of this specification and those shown for each type in the applicable detail specification; tests shall be performed on production product in accordance with specified test methods, insofar as practicable. The tests shall be performed on test specimens removed from the extruded or molded rods and tubes used to produce parts machined from this material.

3.3.1 Color shall be as described for each type with no discoloration or inclusions detrimental to the performance requirements of the final components. For Type 5, color is solely dependent upon pigment chosen by the supplier.

### 3.4 Quality

Moldings or extrusions as received by purchaser shall be uniform in quality and color, smooth, as free from foreign material as commercially practicable, and free from internal imperfections detrimental to usage of the material.

### 3.5 Sizes and Tolerances

Dimensions and tolerances of moldings or extrusions shall be as agreed upon by purchaser and supplier or as stated on purchase order.

## 4. QUALITY ASSURANCE PROVISIONS

### 4.1 Responsibility for Inspection

The manufacturer of moldings or extrusions shall supply all test coupons and shall be responsible for the performance of all required tests for each lot of moldings or extrusions. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the moldings or extrusions conform to the specified requirements. Manufacturer of machined parts shall furnish substantiating test data acquired by the manufacturer of moldings or extrusions. Purchaser of parts machined from moldings or extrusions also reserves the right to perform confirmatory testing provided the parts will yield test coupons that conform to the testing procedure(s) listed in 4.5.

### 4.2 Classification of Tests

#### 4.2.1 Acceptance Tests

All technical requirements are acceptance tests and shall be performed on each lot of moldings or extrusions (See 4.3.1.2).

### 4.3 Sampling and Testing

Shall be as follows:

#### 4.3.1 Acceptance Tests

Sufficient test coupons shall be taken at random from each molding or extrusion lot to perform required tests. The number of determinations for each requirement shall be as specified in the applicable test procedure or, if not specified, not less than three.

4.3.1.1 A batch of either virgin PTFE polymer or filled or pigmented PTFE polymer shall not exceed 4400 pounds (2000 kg).

4.3.1.2 A lot of moldings or extrusions shall be all the rods or tubes made from the same batch of compound in one continuous run and presented for manufacturer's inspection at one time.

4.3.1.3 A statistical sampling plan, acceptable to purchaser, may be used in lieu of sampling as in 4.3.1 and the report of 4.6 shall state that such plan was used.

#### 4.4 Approval

4.4.1 Test results from sample product shall be approved by purchaser before production moldings or extrusions are supplied, unless such approval is waived by purchaser. Results of the tests on samples from the production lot shall be essentially equivalent to those on the approved sample. Production product made by a revised procedure shall not be shipped prior to receipt of reapproval. If necessary to make any change in parameters for the process control factors, manufacturer shall submit for reapproval a statement of the proposed changes in ingredients and/or processing and, when requested, sample product.

4.4.2 Manufacturer of the product shall make no significant change in material, processes, or control factors from those on which the approval was based, unless the change is approved by the cognizant engineering organization. A significant change is one which, in the judgment of the cognizant engineering organization, could affect the properties or performance of the product.

#### 4.5 Test Methods

Shall be as follows:

4.5.1 Tensile strength and elongation shall be determined in accordance with ASTM D 4894 and the test specimens shall be prepared from either a production molding or extrusion as specified or from a sample molding or extrusion of sufficient size. Test specimens for rods and tubes, where size permits, shall conform to ASTM D 4894, Figure 11, except that rods 0.250 inch (6.35 mm) and under in diameter may be tested in full cross-section. The initial jaw separation shall be 0.875 inch  $\pm$  0.005 (22.2 mm  $\pm$  0.13) and the speed of testing shall be as specified for each type per ASTM D 4745 or ASTM D 4894. Type 5 material should be tested in accordance with the requirements of Type 1 material.

4.5.1.1 For compression molded material, the sample should be pulled in the direction of molding (axial direction) where physical dimensions permit. Where this is not possible, the sample should be perpendicular to the direction of molding (circumferential direction). For isostatically molded rods or tubes, the sample may be taken from either the axial or circumferential direction. For extrusions, the sample should be pulled in the direction of extrusion (axial direction). The values shown for each type are the minimum values required.

4.5.2 Specific gravity shall be determined in accordance with ASTM D 792, Method A with two drops of wetting agent added to the water.

#### 4.5.3 Dimensional Stability

The dimensional stability test shall be carried out on sample rings.

##### 4.5.3.1 Dimensional Stability Test

Sample rings cut from the moldings or extrusions shall be subjected to air aging for a minimum of 1 hour at 350 °F  $\pm$  10 (177 °C  $\pm$  6) and allowed to cool to room temperature in free air at ambient temperature. The samples shall not exhibit a change in circumferential length of more than 0.2% (i.e., 0.002 inch per inch).

#### 4.6 Reports

The supplier of moldings or extrusions shall furnish with each shipment a report from the manufacturer showing the results of tests on each lot to determine conformance to the tensile strength, elongation, specific gravity, and stability testing requirements and stating that the moldings or extrusions conform to the other technical requirements. This report shall include the purchase order number, lot number, AMS3678C and its applicable type or detail specification number, manufacturer's identification number, form and size or part number, and quantity.