

AERONAUTICAL MATERIAL SPECIFICATIONS

AMS 3690

SOCIETY OF AUTOMOTIVE ENGINEERS, Inc. 485 Lexington Ave., New York 17, N.Y.

Issued 1-15-60
Revised

ADHESIVE COMPOUND, EPOXY Room Temperature Curing

1. ACKNOWLEDGMENT: A vendor shall mention this specification number in all quotations and when acknowledging purchase orders.
2. FORM: The adhesive shall contain an epoxy resin as the basic ingredient. It shall consist of two components: an epoxy resin base and a hardener. Fillers and modifiers may be included in either component.
3. APPLICATION: A general purpose adhesive for non-structural bonding of aluminum, corrosion resistant steel, brass, and many thermosetting plastics to themselves and to each other. It is primarily intended as an adhesive for electrical components and devices operating at temperatures not higher than 185 F.
4. TECHNICAL REQUIREMENTS:
 - 4.1 General:
 - 4.1.1 Curing: When mixed and cured at room temperature in accordance with manufacturer's recommendations, formulation shall polymerize to a uniform material exhibiting 90% of its ultimate strength within 24 hours. It shall reach its ultimate adhesive strength when cured at 75 F for not more than 7 days or at 150 F for not more than 4 hours.
 - 4.1.2 Pot Life: Material in 100 g batches, when mixed in accordance with manufacturer's recommendations, shall have a useful pot life of not less than 40 min. when maintained at not higher than 75 F.
 - 4.1.3 Corrosion: The product shall not have a corrosive effect on other materials when exposed to conditions normally encountered in service. Discoloration of metal shall not be considered objectionable.
 - 4.2 Properties: The product, when cured to obtain maximum properties, shall conform to the following requirements; tests shall be performed in accordance with listed ASTM methods or as noted. Test specimens may be furnished by the vendor or fabricated by the user. The results shall be taken as the average value of not less than 5 samples, except as otherwise specified.
 - 4.2.1 Adhesive Strength:
 - 4.2.1.1 Tensile Shear at 70 - 85 F, psi, min
Cured 24 hr at 70 - 85 F 1800 Note 1
Ultimate cure 2000
After thermal cycling (See Note 2) 1500
After thermal aging (See Note 3) 1800
 - 4.2.1.2 Tensile Shear at Temperature extremes, psi, min Note 1
At -65 F \pm 2 1500 Time: 1 hr
At 185 F \pm 2 1800

Section 7C of the SAE Technical Board rules provides that: "All technical reports use by anyone engaged in industry or trade is entirely voluntary. There is no obligation to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."

Note 1. Tests shall be conducted in accordance with ASTM D1002-53T with the following modifications. Individual test pieces 1 x 5 x 1/8 in. may be used in sample preparation. The metal shall be AMS 5044 or equivalent steel. The tensile holding fixture shall allow sufficient offset to account for the metal thickness, and through-pin holding arrangement shall be allowable when 1/8 in. thick test pieces are used. The test piece width shall be 1 in. and the overlap area 0.5 sq inch. Bonding fixtures used shall give identical pressure on the adhesive joint from batch to batch. Bonding surface shall be freshly sandblasted to obtain a uniformly roughened surface and shall be thoroughly washed with a suitable solvent.

Note 2. Samples shall be subjected to 10 thermal cycles in air as described below and then tested at room temperature. Time at the temperature extremes shall be regulated to ± 5 minutes. One cycle shall consist of 1/2 hr at $-65\text{ F} \pm 2$, 1/2 hr at $75\text{ F} \pm 2$, 1/2 hr at $158\text{ F} \pm 2$, and 1/2 hr at $75\text{ F} \pm 2$. The cycle may be extended during any 75 F conditioning period.

Note 3. Samples shall be maintained at $185\text{ F} \pm 2$ in a circulating air oven for 200 hr ± 12 , removed from the oven, and allowed to stabilize at test temperature for not less than 2 hr before testing.

4.2.2 Fluid Resistance: The material shall be subjected to di-2-ethylhexyl sebacate +0.5% phenothiazine, ASTM Oil No. 3, and ASTM Reference Fuel B.

Weight change, %, max

2.0

Note 4

Note 4. Seventeen samples shall be prepared by dip, spray, or brush coating both sides and all edges of one half of a tared standard glass microscope slide with a uniform, bubble-free film of adhesive 0.005 - 0.020 in. thick. Thin sections on corners shall be acceptable. Samples shall be cured according to manufacturer's recommendations, weighed accurately to ± 0.0001 g, and the adhesive film weight calculated. Five samples shall be subjected to each test fluid for 96 hr at $212\text{ F} \pm 2$. Two samples shall be aged for 96 hr at $212\text{ F} \pm 2$ in a circulating air oven. Thermal aged samples shall be cooled, allowed to stabilize at 75 F in a desiccator, and weighed. Samples subjected to volatile solvents shall be cooled to 75 F in the solvent, removed from the solvent, wiped dry, and weighed immediately. Samples subjected to non-volatile fluids shall be cooled to 75 F, washed free of excess material with a suitable solvent, allowed to stabilize to a constant weight, and weighed immediately. The initial and final average weights of samples exposed to each fluid and to hot air shall be determined and the difference expressed as percent weight change. Results shall be recorded as the difference between the percent weight change of the air aged samples and the fluid aged samples.

5. QUALITY: The product shall be uniform in quality and condition, clean, and free from foreign materials and from imperfections detrimental to fabrication, appearance, or performance of parts.

6. REPORTS: Unless otherwise specified, the vendor of the product shall furnish with each shipment three copies of a report stating that the product conforms to the requirements of this specification. This report shall include the purchase order number, material specification number, form or part number, and quantity.