



<b>AEROSPACE MATERIAL SPECIFICATION</b>	<b>AMS3692™</b>	<b>REV. C</b>
	Issued 1960-06 Revised 1995-02 Reaffirmed 2022-01	
Superseding AMS3692		
Adhesive Compound, Epoxy Resin High Temperature Application		

### RATIONALE

AMS3692C has been reaffirmed to comply with the SAE five year review policy.

#### 1. SCOPE:

##### 1.1 Form:

This specification covers a two-component adhesive compound, an epoxy resin base and a hardener, in the form of a paste.

##### 1.2 Application:

This compound has been used typically for non-structural bonding of metals and thermosetting plastics, to themselves and to each other, and as an adhesive for electrical components and devices operating at not higher than 260 °C (500 °F), but usage is not limited to such applications.

##### 1.3 Safety-Hazardous Materials:

While the materials, methods, applications, and processes described or referenced in this specification may involve the use of hazardous materials, this specification does not address the hazards which may be involved in such use. It is the sole responsibility of the user to ensure familiarity with the safe and proper use of any hazardous materials and to take necessary precautionary measures to ensure the health and safety of all personnel involved.

#### 2. APPLICABLE DOCUMENTS:

The following publications form a part of this specification to the extent specified herein. The latest issue of SAE publications shall apply. The applicable issue of other publications shall be the issue in effect on the date of the purchase order.

##### 2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

AMS 2825 Material Safety Data Sheets

AMS 5044 Steel Sheet and Strip, 0.15 Carbon, Maximum, Half Hard Temper

SAE Executive Standards Committee Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2022 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

**TO PLACE A DOCUMENT ORDER:** Tel: 877-606-7323 (inside USA and Canada)  
Tel: +1 724-776-4970 (outside USA)  
Fax: 724-776-0790  
Email: CustomerService@sae.org  
http://www.sae.org

**SAE WEB ADDRESS:**

**For more information on this standard, visit**  
<https://www.sae.org/standards/content/AMS3692C/>

## 2.2 ASTM Publications:

Available from ASTM, 1916 Race Street, Philadelphia, PA 19103-1187.

ASTM D 471 Rubber Property - Effect of Liquids

ASTM D 1002 Strength Properties of Adhesives in Shear by Tension Loading (Metal-to-Metal)

## 2.3 U.S. Government Publications:

Available from DODSSP, Subscription Services Desk, Building 4D, 700 Robbins Avenue, Philadelphia, PA 19111-5094.

MIL-STD-2073-1 DOD Materiel, Procedures for Development and Application of Packaging Requirements

## 3. TECHNICAL REQUIREMENTS:

### 3.1 Material:

Shall consist of two components; an epoxy resin base and a hardener. Fillers and modifiers may be included in either component.

3.1.1 Curing: When mixed and cured at room temperature in accordance with manufacturer's recommendations, resin system shall polymerize to a uniform adhesive. The adhesive shall require less than 10 psi (70 kPa) pressure on the bond surface to achieve bond strength conforming to specified requirements.

3.1.2 Shelf Life: Resin base and hardener, stored in unopened containers at not higher than 27 °C (80 °F) for up to one year, shall meet the requirements of 3.2 after being mixed and cured as in 3.1.1.

3.1.3 Pot Life: Adhesive in 100-gram batches, mixed in accordance with manufacturer's recommendations, shall have a useful pot life of not less than 40 minutes when maintained at not higher than 24 °C (75 °F).

### 3.2 Properties:

The product, when cured to obtain maximum properties in accordance with manufacturer's recommendations, shall conform to the requirements in Table 1, 3.2.3, 3.2.4, and 3.2.5; tests shall be performed on the product supplied and in accordance with specified methods, insofar as practicable. Reported values shall be the average of five or more specimens.

TABLE 1 - Properties

Paragraph	Property	Requirement	Test Method
3.2.1	Tensile shear as cured 24 °C ± 1 (75 °F ± 2), min		4.5.1
3.2.1.1	As cured	2000 psi (13.8 MPa)	
3.2.1.2	After thermal cycling	2000 psi (13.8 MPa)	4.5.2
3.2.1.3	After thermal aging	1000 psi (6.90 MPa)	4.5.3
3.2.2	Tensile shear at temperature extremes, min		4.5.1
3.2.2.1	At -55 °C ± 1 (-65 °F ± 2)	1500 psi (10.3 MPa)	
3.2.2.2	At 260 °C ± 3 (500 °F ± 5)	1000 psi (6.90 MPa)	
3.2.2.3	At 260 °C ± 3 (500 °F ± 5) after thermal aging	1000 psi (6.90 MPa)	4.5.3

3.2.3 Fluid Resistance: The adhesive, subjected to ASTM D 471 Service Fluid No. 1, Oil No. 3, and Reference Fuel B, shall not show a weight change greater than 2.0%, determined in accordance with 4.5.4.

3.2.4 Volatile Content: Volatiles evolved during drying (if required) and curing, shall not exceed R) 20 grams per liter when tested as in 4.5.5.

3.2.5 Corrosion: The product shall not have a corrosive effect on adherent surfaces when exposed to conditions normally encountered in service, determined by a procedure acceptable to purchaser. Discoloration of metals shall not be considered objectionable.

### 3.3 Quality:

The product, as received by purchaser, shall be uniform in quality and condition and free from foreign materials and from imperfections detrimental to usage of the product.

## 4. QUALITY ASSURANCE PROVISIONS:

### 4.1 Responsibility for Inspection:

(R)

The manufacturer of the product shall supply all samples and shall be responsible for all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to the requirements of this specification.

### 4.2 Classification of Tests:

4.2.1 Acceptance Tests: Tests for tensile shear as cured 24 hours at 24 °C ± 1 (75 °F ± 2) (3.2.1.1) and quality (3.3) are acceptance tests and shall be performed on each lot.

4.2.2 Preproduction Tests: Tests for all technical requirements are preproduction tests and shall be performed prior to or on the initial shipment of the product to a purchaser, when a change in ingredients and/or processing requires reapproval as in 4.4.2, and when purchaser deems confirmatory testing to be required.

4.2.2.1 For direct U.S. Military procurement, substantiating test data and, when requested, preproduction test material shall be submitted to the cognizant agency as directed by the procuring activity, contracting officer, or request for procurement.

4.3 Sampling and Testing:

(R)

Shall be as follows:

4.3.1 For Acceptance Tests: Sufficient product shall be taken at random from each lot to perform all required tests. The number of determinations for each requirement shall be as specified in the applicable test procedure or, if not specified therein, not less than five.

4.3.1.1 A lot shall be all adhesive produced in a single production run from the same batches of raw materials and presented for purchaser's inspection at one time. A lot shall not exceed 500 pounds (227 kg).

4.3.1.2 A statistical sampling plan, acceptable to purchaser, may be used in lieu of sampling as in (R) 4.3.1.

4.3.2 For Preproduction Tests: Shall be acceptable to purchaser.

(R)

4.4 Approval:

4.4.1 Sample adhesive shall be approved by purchaser before adhesive for production use is supplied, unless such approval be waived by purchaser. Results of tests on production adhesive shall be essentially equivalent to those on the approved sample.

4.4.2 Manufacturer shall use ingredients, manufacturing procedures, processes, and methods of inspection on production adhesive which are essentially the same as those used on the approved sample. If necessary to make any change in ingredients, in type of equipment for processing, or in manufacturing procedures, manufacturer shall submit for reapproval a statement of the proposed changes in ingredients and/or processing and, when requested, sample adhesive. Production adhesive made by the revised procedure shall not be shipped prior to receipt of reapproval.

4.5 Test Methods:

4.5.1 Tensile Shear: Shall be determined in accordance with ASTM D 1002 with the following modifications. Individual test pieces shall be made of AMS 5044 steel, or equivalent, nominally 1/8 x 1 x 5 inches (3.2 x 25 x 127 mm) in size. Tensile holding fixture shall allow sufficient offset to account for the metal thickness, and through-pin holding arrangement shall be allowable when 1/8 inch (3.2 mm) thick test pieces are used. The test piece width shall be 1.0 inch  $\pm$  0.1 (25 mm  $\pm$  0.3) and the overlap area 0.5 square inches (323 mm<sup>2</sup>). Bonding fixtures used shall provide identical pressure on the adhesive joint from batch to batch. Bonding surface shall be freshly sand blasted to obtain a uniformly roughened surface and shall be thoroughly washed with a suitable solvent.

- 4.5.2 Thermal Cycling: Samples shall be subjected to 10 thermal cycles in air as follows and tested at room temperature. One cycle shall consist of 30 minutes  $\pm 5$  at  $-55\text{ }^{\circ}\text{C} \pm 1$  ( $-67\text{ }^{\circ}\text{F} \pm 2$ ), 30 minutes  $\pm 5$  at  $24\text{ }^{\circ}\text{C} \pm 1$  ( $75\text{ }^{\circ}\text{F} \pm 2$ ), 30 minutes  $\pm 5$  at  $100\text{ }^{\circ}\text{C} \pm 1$  ( $212\text{ }^{\circ}\text{F} \pm 2$ ), and 30 minutes  $\pm 5$  at  $24\text{ }^{\circ}\text{C} \pm 1$  ( $75\text{ }^{\circ}\text{F} \pm 2$ ). The cycle may be extended during any  $24\text{ }^{\circ}\text{C}$  ( $75\text{ }^{\circ}\text{F}$ ) conditioning period.
- 4.5.3 Thermal Aging: Samples shall be maintained at  $260\text{ }^{\circ}\text{C} \pm 3$  ( $500\text{ }^{\circ}\text{F} \pm 5$ ) in a circulating-air oven for 200 hours  $\pm 12$ , removed from the oven, and allowed to stabilize at test temperature for not less than 2 hours before testing.
- 4.5.4 Fluid Resistance: Seventeen samples shall be prepared by dip, spray, or brush coating both sides and all edges of one half of a tared standard glass microscope slide with a uniform, bubble-free film of adhesive 0.005 to 0.020 inches (0.13 to 0.51 mm) thick. Thin sections on corners are acceptable. Samples shall be cured according to manufacturer's recommendations, weighed to  $\pm 0.0001$  gram, and the adhesive film weight calculated. Five samples shall be subjected to each test fluid for 96 hours  $\pm 1$  at  $100\text{ }^{\circ}\text{C} \pm 1$  ( $212\text{ }^{\circ}\text{F} \pm 2$ ). Two samples shall be aged for 96 hours  $\pm 1$  at  $100\text{ }^{\circ}\text{C} \pm 1$  ( $212\text{ }^{\circ}\text{F} \pm 2$ ) in a circulating-air oven. Thermal aged samples shall be cooled, allowed to stabilize at  $24\text{ }^{\circ}\text{C} \pm 1$  ( $75\text{ }^{\circ}\text{F} \pm 2$ ) in a desiccator, and weighed. Samples subjected to volatile solvents shall be cooled to  $24\text{ }^{\circ}\text{C} \pm 1$  ( $75\text{ }^{\circ}\text{F} \pm 2$ ) in the solvent, removed from the solvent, wiped dry, and weighed immediately. Samples subjected to non-volatile fluids shall be cooled to  $24\text{ }^{\circ}\text{C} \pm 1$  ( $75\text{ }^{\circ}\text{F} \pm 2$ ), washed free of excess material with a suitable solvent, allowed to stabilize to constant weight, and weighed immediately. The initial and final average weights of samples exposed to each fluid and to hot air shall be determined and the difference expressed as percent weight change. Results shall be recorded as the difference between the percent weight change of the air aged samples and the fluid aged samples.
- 4.5.5 Volatile Content: Shall be determined by weighing, to the nearest 0.001 gram, into a tared (R) weighing dish approximately three grams of adhesive ( $W_1$ ) mixed for application in accordance with manufacturer's instructions. Cure the adhesive in accordance with manufacturer's instructions, heat the cured adhesive for 60 minutes  $\pm 5$  at  $110\text{ }^{\circ}\text{C} \pm 5$  ( $230\text{ }^{\circ}\text{F} \pm 9$ ), cool to room temperature in a desiccator, and weigh to the nearest 0.001 gram ( $W_2$ ). Calculate the volatiles in accordance with Equation 1.

$$\text{Volatile Content} = \frac{(w_1 - W_2)}{W_1 / p} \quad (\text{Eq.1})$$

Where:

$p$  = density of adhesive as applied, grams/L

#### 4.6 Reports:

The supplier of adhesive shall furnish with each shipment a report showing the results of tests to determine conformance to the acceptance test requirements and stating that the adhesive conforms to the other technical requirements. This report shall include the purchase order number, lot number, AMS 3692C, manufacturer's identification, and quantity.