

EPOXY RESIN, CYCLOALIPHATIC LIQUID

1. SCOPE:

1.1 Form: This specification covers an alicyclic diepoxy carboxylate prepolymer in the form of a low viscosity liquid.

1.2 Application: Primarily for use in manufacture of high temperature composite matrices and adhesives where a low viscosity resin is required.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

2.1 SAE Publications: Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

AMS 2350 - Standards and Test Methods

AMS 2825 - Material Safety Data Sheets

2.2 ASTM Publications: Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

ASTM D1652 - Epoxy Content of Epoxy Resins

ASTM D1963 - Specific Gravity of Drying Oils, Varnishes, Resins, and Related Materials at 25/25°C

ASTM D2393 - Viscosity of Epoxy Resins and Related Components

2.3 U.S. Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

SAE Technical Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

AMS documents are protected under United States and international copyright laws. Reproduction of these documents by any means is strictly prohibited without the written consent of the publisher.

AMS 3705

2.3.1 Military Standards:

MIL-STD-794 - Parts and Equipment, Procedures for Packaging and Packing of

3. TECHNICAL REQUIREMENTS:

3.1 Materials: Shall be 3, 4 - epoxy cyclohexylmethyl - 3, 4 - epoxy cyclohexane carboxylate.

3.2 Impurities: Resin shall be substantially free of suspended matter.

3.3 Properties: Resin shall conform to the following requirements determined in accordance with specified ASTM methods; both individual results and the arithmetic means shall be reported:

3.3.1 Epoxy Content (equiv. per 100 g)	0.70 - 0.76	ASTM D1652
3.3.2 Viscosity at 25°C (77°F), cps	350 - 450	ASTM D2393
3.3.3 Specific Gravity at 25/25°C (77/77°F)	1.16 - 1.18	ASTM D1963

3.4 Quality: The resin, as received by purchaser, shall be uniform in quality and condition, clean, and free from foreign materials and contaminants detrimental to usage of the resin.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection: The vendor of the resin shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.6. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the resin conforms to the requirements of this specification.

4.2 Classification of Tests: Tests to determine conformance to all technical requirements of this specification are classified as acceptance tests and as preproduction tests and shall be performed prior to or on the initial shipment of resin to a purchaser, on each lot, when a change in material, processing, or both requires reapproval as in 4.4.2, and when purchaser deems confirmatory testing to be required.

4.2.1 For direct U.S. Military procurement, substantiating test data and, when requested, preproduction test material shall be submitted to the cognizant agency as directed by the procuring activity, the contracting officer, or the request for procurement.

4.3 Sampling: Shall be as follows:

4.3.1 For Acceptance Tests: Each lot of resin shall be sampled at random to provide sufficient material to perform all required tests. The number of determinations for each requirement shall be as specified in the applicable test procedure, or, if not specified therein, not less than three.

4.3.1.1 A lot shall be all resin produced in a continuous production run from the same batches of raw materials under the same fixed conditions and presented for vendor's inspection at one time. A lot may be packaged in smaller quantities under the basic lot approval provided lot identification is maintained.

4.3.1.2 A batch shall be the quantity of material run in a reactor or mixer at one time.

4.3.1.3 When a statistical sampling plan and acceptance quality level (AQL) have been agreed upon by purchaser and vendor, sampling shall be in accordance with such plan in lieu of sampling as in 4.3.1 and the report of 4.1 shall state that such plan was used.

4.3.2 For Preproduction Tests: As agreed upon by purchaser and vendor.

4.4 Approval:

4.4.1 Sample resin shall be approved by purchaser before resin for production use is supplied, unless such approval be waived by purchaser. Results of tests on production resin shall be essentially equivalent to those on the approved sample.

4.4.2 Vendor shall use ingredients, manufacturing procedures, processes, and methods of inspection on production resin which are essentially the same as those used on the approved sample resin. If necessary to make any change in ingredients, in type of equipment for processing, or in manufacturing procedures, vendor shall submit for reapproval a statement of the proposed changes in material, processing, or both and, when requested, sample resin. Production resin made by the revised procedure shall not be shipped prior to receipt of reapproval.

4.5 Reports:

4.5.1 The vendor of resin shall furnish with each shipment a report showing the results of tests on each lot to determine conformance to the technical requirements of this specification. This report shall include the purchase order number, AMS 3705, vendor's product designation, lot number, date of manufacture, and quantity.

AMS 3705

4.5.1.1 A material safety data sheet conforming to AMS 2825, or equivalent shall be supplied to each purchaser prior to, or concurrent with, the report of preproduction test results or, if preproduction testing be waived by purchaser, concurrent with the first shipment of resin for production use. Each request for modification of resin formulation shall be accompanied by a revised data sheet for the proposed formulation.

4.5.2 The vendor of finished or semi-finished parts shall furnish with each shipment a report showing the purchase order number, AMS 3705, contractor or other direct supplier of resin, vendor's product designation, part number, and quantity. When resin for making parts is produced or purchased by the parts vendor, that vendor shall inspect each lot of resin to determine conformance to the requirements of this specification and shall include in the report either a statement that the resin conforms or copies of laboratory reports showing the results of tests to determine conformance.

4.6 Resampling and Retesting: If any specimen used in the above tests fails to meet the specified requirements, disposition of the resin may be based on the results of testing three additional specimens for each original nonconforming specimen. Failure of any retest specimen to meet the specified requirements shall be cause for rejection of the resin represented and no additional testing shall be permitted. Results of all tests shall be reported.

5. PREPARATION FOR DELIVERY:

5.1 Packaging and Identification:

5.1.1 The resin shall be packaged in air-tight containers and stored away, or otherwise protected, from excessive heat and humidity.

5.1.2 Each container of resin shall be identified with an attached label using characters of such size as to be legible and which will not be obliterated by normal handling. Each label shall show not less than the following information:

EPOXY RESIN, CYCLOALIPHATIC LIQUID

AMS 3705

MANUFACTURER'S MATERIAL DESIGNATION _____

PURCHASE ORDER NUMBER _____

DATE OF MANUFACTURE _____

LOT NUMBER _____

QUANTITY _____

STORE AWAY FROM EXCESSIVE HEAT AND HUMIDITY