

**AEROSPACE
MATERIAL
SPECIFICATION**

Issued OCT 1983
Revised JAN 1993
Noncurrent JUL 1992
Cancelled MAY 2003
Superseding AMS 3726/1B

Shims, Filled Resin Compound
Liquid

CANCELLATION NOTICE

This specification has been "CANCELLED" by the Aerospace Materials Division, SAE, as of May, 2003. By this action, this document will remain listed in the Numerical Section of the Index of Aerospace Material Specifications.

Cancelled specifications are available from SAE.

SAENORM.COM : Click to view the full PDF of AMS 3726-1C

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright 2003 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
 Tel: 724-776-4970 (outside USA)
 Fax: 724-776-0790
 Email: custsvc@sae.org
SAE WEB ADDRESS: http://www.sae.org

1. SCOPE:

1.1 Form:

This specification covers a filled, resinous, thermosetting, two-part, liquid compound capable of being applied and cured in place between the surfaces of mechanically fastened (joined) structures.

1.2 Application:

This product has been used typically as a molded shim during assembly of aircraft components and parts, but usage is not limited to such applications. The compound covered by this detail specification can be stored as two separate components for up to one year from date of receipt by purchaser.

2. APPLICABLE DOCUMENTS:

See AMS 3726.

3. TECHNICAL REQUIREMENTS:

3.1 Basic Specification:

The complete requirements for procuring the product described herein shall consist of this document and the latest Issue of the basic specification, AMS 3726.

3.2 Material:

Shall be an epoxy or modified epoxy-base polymer supplied with a separate hardener or curing agent.

3.3 Cured Properties:

Shall be as shown in Table 1.

TABLE 1

Paragraph	Property	Requirement	Method of Testing
3.3.1	Hardness, Durometer D or equivalent, minimum average	92	ASTM D 2240
3.3.2	Specific Gravity, maximum	1.60	ASTM D 792
3.3.3	Coefficient of Linear Thermal Expansion, maximum average -62° to +93°C (-80° to +199°F)	5.4 x 10 ⁻⁵ mm/mm per °C (3.0 x 10 ⁻⁵ inch/inch per °F)	ASTM D 696
3.3.4	Lap Shear Strength, minimum average	2000 psi (13.8 MPa)	ASTM D 1002
3.3.5	Lap Shear Residual Strength, Exposed, minimum average		
3.3.5.1	Salt Spray, 30 days at 50°C ± 1 (122°F ± 2)	1500 psi (10.3 MPa)	ASTM B 117
3.3.5.2	Condensing Humidity, 30 days at 60°C ± 1 (140°F ± 2)	1700 psi (11.7 MPa)	ASTM D1151
3.3.5.3	JP-4 Fuel, 7 days at 60°C ± 1 (140°F ± 2)	1800 psi (12.4 MPa)	ASTM D 3165
3.3.6	Strain Compatibility, Tensile, Constant Amplitude Cycling		
3.3.6.1	Aluminum alloy	20 cycles without failure at -55°C ± 1 (-67°F ± 2)	4.5.2
3.3.6.2	Graphite-epoxy laminate	20 cycles without failure at -55°C + 1 (-67°F ± 2)	4.5.3
3.3.7	Flatwise Compressive Strength, minimum	30.0 ksi (207 MPa) stress without failure	4.5.4
3.3.8	Shim-Torque Test, breakaway torque, individual bolt, minimum	50% of initial applied torque	4.5.5