



400 Commonwealth Drive, Warrendale, PA 15096-0001

AEROSPACE MATERIAL SPECIFICATION



AMS 3726/2B

Issued	OCT 1983
Revised	OCT 1991
Reaffirmed	APR 2001
Cancelled	JUN 2002

Superseding AMS 3726/2A

Shims, Filled Resin Compound
Precatalyzed Sheet

CANCELLATION NOTICE

This specification has been "CANCELLED" by the Aerospace Materials Division, SAE, as of June, 2002. By this action, this document will remain listed in the Numerical Section of the Index of Aerospace Material Specifications.

Cancelled specifications are available from SAE.

SAENORM.COM : Click to view the full PDF of AMS 3726_2B

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright 2002 Society of Automotive Engineers, Inc.
All rights reserved.

Printed in U.S.A.

QUESTIONS REGARDING THIS DOCUMENT:
TO PLACE A DOCUMENT ORDER:
SAE WEB ADDRESS:

(724) 772-7161
(724) 776-4970
<http://www.sae.org>

FAX: (724) 776-0243
FAX: (724) 776-0790

1. SCOPE:**1.1 Form:**

This specification covers a filled, resinous, thermosetting, precatyzed compound in the form of sheet capable of being applied and cured in place between the surfaces of mechanically fastened (joined) structures.

1.2 Application:

This product has been used typically as a molded shim during assembly of aircraft components and parts, but usage is not limited to such applications. The compound covered by this detail specification requires storage in the frozen condition until just prior to installation.

2. APPLICABLE DOCUMENTS:

See AMS 3726.

3. TECHNICAL REQUIREMENTS:**3.1 Basic Specification:**

The complete requirements for procuring the product described herein shall consist of this document and the latest issue of the basic specification, AMS 3726.

3.2 Material:

Shall be a precatyzed epoxy or modified epoxy-base polymer supplied in sheet form. The thickness, width, and length of the sheets shall be as specified.

3.2.1 Storage Life: The product shall meet the requirements of this specification at any time up to six months from date of receipt by purchaser when stored below -37 °C (-35 °F) in the original unopened containers.

3.3 Cured Properties:

Shall be as shown in Table 1.

TABLE 1

Paragraph	Property	Requirement	Method of Testing
3.3.1	Hardness, Durometer D or equivalent, minimum average	92	ASTM D 2240
3.3.2	Specific Gravity, maximum	1.60	ASTM D 792
3.3.3	Coefficient of Linear Thermal Expansion, maximum average -62 to +93 °C (-80 to +199 °F)	5.4 x 10 ⁻⁵ mm/mm per °C (3.0 x 10 ⁻⁵ inch/inch per °F)	ASTM D 696
3.3.4	Lap Shear Strength, minimum average	2000 psi (13.8 MPa)	ASTM D 1002
3.3.5	Lap Shear Residual Strength, Exposed, minimum average		
3.3.5.1	Salt Spray, 30 days at 50 °C ± 1 (122 °F ± 2)	1500 psi (10.3 MPa)	ASTM B 117
3.3.5.2	Condensing Humidity, 30 days at 60 °C + 1 (140 °F ± 2)	1700 psi (11.7 MPa)	ASTM D 1151
3.3.5.3	JP-4 Fuel, 7 days at 60 °C ± 1 (140 °F ± 2)	1800 psi (12.4 MPa)	ASTM D 3165
3.3.6	Strain Compatibility, Tensile, Constant Amplitude Cycling		
3.3.6.1	Aluminum alloy	20 cycles without failure at -55 °C ± 1 (-67 °F ± 2)	4.5.2
3.3.6.2	Graphite-epoxy laminate	20 cycles without failure at -55 °C ± 1 (-67 °F ± 2)	4.5.3
3.3.7	Flatwise Compressive Strength, minimum	30.0 ksi (207 MPa) stress without failure	4.5.4
3.3.8	Shim-Torque Test, breakaway torque, individual bolt, minimum	50% of initial applied torque	4.5.5