

POTTING COMPOUND, EPOXY  
Bisphenol A-Type  
Unfilled, Room Temperature Cure

1. SCOPE:

- 1.1 Form: This specification covers an unfilled, room-temperature-polymerizing epoxy resin formulation, supplied as a two-component system.
- 1.2 Application: Primarily for use as a casting or sealing material where fairly high thermal expansion can be tolerated and where flammability resistance is not required.

2. APPLICABLE DOCUMENTS: Shall be as shown in AMS 3731.

3. TECHNICAL REQUIREMENTS:

- 3.1 Basic Specification: The complete requirements for procuring the product described herein shall consist of this document and the latest issue of the basic specification, AMS 3731.
- 3.2 Material: Shall be an epoxy-based polymer with a curing agent.
- 3.3 Properties: The compound shall conform to the following requirements:
- 3.3.1 Mixed Uncured Compound: The compound, mixed in accordance with manufacturer's instructions, shall exhibit the following properties:
- 3.3.1.1 Viscosity: Shall be not greater than 1500 centipoise (1.5 Pa s) at 23°C (73°F), determined within 5 min. after mixing, using a Brookfield Model LVF viscometer and No. 2 spindle at 12 revolutions per minute.

SAE Technical Board rules provide that: "All technical reports, including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade or their use by governmental agencies is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."

# AMS3731/1

- 3.3.1.2 Pot Life: Usable life of the compound, defined as the time to attain double the initial viscosity determined in 3.3.1.1, shall be not less than 30 min. at 23°C (73°F).
- 3.3.1.3 Curing Time: The time required to develop the cured product properties specified in 3.3.2 shall be not more than 5 days at 23°C (73°F) or not more than 2 hr at 93°C (200°F).
- 3.3.1.4 Demold Time: The time required before the part can be removed from the mold and retain its integrity shall be not more than 24 hr at 23°C (73°F).
- 3.3.2 Cured Product: The compound, mixed and cured in accordance with manufacturer's instructions, shall exhibit the following properties, determined in accordance with test methods listed in AMS 3731:
- |           |   |  |
|-----------|---|--|
| 3.3.2.1   | Flexural Strength, min                                | 13,500 psi (93 MPa)  |
| 3.3.2.2   | Izod Impact Strength, per unit of notch, min          | 0.23 ft-lb per in. (12.3 J/m)  |
| 3.3.2.3   | Compressive Strength, min                             | 12,500 psi (86 MPa)  |
| 3.3.2.4   | Insulation Resistance                                 |  |
| 3.3.2.4.1 | At 23°C (73°F), min                                   | 1x10 <sup>6</sup> megohms  |
| 3.3.2.4.2 | After hydrolytic stability conditioning, min          | 1x10 <sup>4</sup> megohms  |
| 3.3.2.5   | Dielectric Constant at 1 KHz, max                     | 5.5  |
| 3.3.2.6   | Dissipation Factor at 1 KHz, max                      | 0.04   |
| 3.3.2.7   | Heat Deflection Temperature at 264 psi (1.8 MPa), min | 70°C (160°F)   |
| 3.3.2.8   | Coefficient of Linear Thermal Expansion, max          |  |
| 3.3.2.8.1 | From -54°C to +23°C (-65°F to + 73°F)                 | 50x10 <sup>-6</sup> (mm/mm)/deg C<br>(28x10 <sup>-6</sup> in. per in. per deg F) |