

POTTING COMPOUND, EPOXY
Bisphenol A-Type
Filled, Heat Cure, Low CTE
Thermal Shock Resistant

1. SCOPE:

- 1.1 Form: This specification covers a filled epoxy resin formulation, supplied as a two-component system, requiring an oven cure for attainment of maximum properties.
- 1.2 Application: Primarily for use as a potting or sealing material where a low coefficient of thermal expansion (CTE) is desired.

2. APPLICABLE DOCUMENTS: Shall be as shown in AMS 3731.

3. TECHNICAL REQUIREMENTS:

- 3.1 Basic Specifications: The complete requirements for procuring the product described herein shall consist of this document and the latest issue of the basic specification, AMS 3731.
- 3.2 Material: Shall be an epoxy-based polymer with a filler and a curing agent:
- 3.3 Properties: The compound shall conform to the following requirements:
- 3.3.1 Mixed Uncured Compound: The compound, mixed in accordance with manufacturer's instructions, shall exhibit the following properties:
- 3.3.1.1 Viscosity: Shall be not greater than 8000 centipoise (8.0 Pa s) at 65°C (150°F), determined within 5 min. after mixing, using a Brookfield Model LVF viscometer and No. 3 spindle at 6 revolutions per minute.

SAE Technical Board rules provide that: "All technical reports, including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade or their use by governmental agencies is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."

AMS 3731/2

3.3.1.2 Pot Life: Usable life of the compound, defined as the time to attain double the initial viscosity determined in 3.3.1.1, shall be not less than 60 min. at 65°C (150°F).

3.3.1.3 Curing Time: The time required to develop the cured product properties specified in 3.2 shall be not more than 16 hr at 65°C (150°F) or not more than 8 hr at 95°C (200°F).

3.3.2 Cured Product: The compound, mixed and cured in accordance with manufacturer's instructions, shall exhibit the following properties, determined in accordance with test methods listed in AMS 3731:

3.3.2.1	Flexural Strength, min	10,000 psi (70 MPa)
3.3.2.2	Izod Impact Strength, per unit of notch, min	0.30 ft-lb per in. (16 J/M)
3.3.2.3	Compressive Strength, min	20,000 psi (140 MPa)
3.3.2.4	Insulation Resistance	
3.3.2.4.1	At 23°C (73°F), min	1x10 ⁶ megohms
3.3.2.4.2	At 121°C (250°F), min	1x10 ⁵ megohms
3.3.2.4.3	After hydrolytic stability conditioning, min	1x10 ⁴ megohms
3.3.2.5	Dielectric Constant at 1 KHz, max	5.5
3.3.2.6	Dissipation Factor at 1 KHz, max	0.04
3.3.2.7	Heat Deflection Temperature at 264 psi (1.8 MPa), min	88°C (190°F)
3.3.2.8	Coefficient of Linear Thermal Expansion, max	
3.3.2.8.1	From -54°C to +23°C (-65°F to +73°F)	25x10 ⁻⁶ (mm/mm)/deg C (14x10 ⁻⁶ in. per in. per deg F)
3.3.2.8.2	From 23°C to 74°C (73°F to 165°F)	30x10 ⁻⁶ (mm/mm)/deg C (17x10 ⁻⁶ (in. per in. per deg F)