

AEROSPACE MATERIAL SPECIFICATION

SAE

AMS 3731/7B

Issued 1 OCT 1981

Revised 1 JAN 1993

Superseding AMS 3731/7A

Submitted for recognition as an American National Standard

POTTING COMPOUND, EPOXY
Bisphenol A-Type
Filled, Room Temperature Cure, Low Shrinkage

This specification has been declared "NONCURRENT" by the Aerospace Materials Division, SAE, as of July, 1992. It is recommended, therefore, that this specification not be specified for new designs.

This cover sheet should be attached to revision "A" of the subject specification.

"NONCURRENT" refers to those materials which have previously been widely used and which may be required on some existing designs in the future. The Aerospace Materials Division, however, does not recommend these as standard materials for future use in new designs. Each of these "NONCURRENT" specifications is available from SAE upon request.

PREPARED UNDER THE JURISDICTION OF AMS COMMITTEE "CP".

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

AN AMERICAN NATIONAL STANDARD

SAE The Engineering Society
For Advancing Mobility
Land Sea Air and Space

400 COMMONWEALTH DRIVE, WARRENDALE, PA 15096

AEROSPACE MATERIAL SPECIFICATION

Submitted for recognition as an American National Standard

AMS 3731/7A

Issued 10-1-81
Revised 10-1-87

Superseding AMS 3731/7

POTTING COMPOUND, EPOXY Bisphenol A-Type Filled, Room Temperature Cure, Low Shrinkage

1. SCOPE:

1.1 Form: This specification covers a filled, room-temperature-polymerizing epoxy resin formulation, supplied as a two-component system.

1.2 Application: Primarily for use as a potting or sealing material where low shrinkage is desired.

2. APPLICABLE DOCUMENTS: See AMS 3731.

3. TECHNICAL REQUIREMENTS:

3.1 Basic Specification: The complete requirements for procuring the product described herein shall consist of this document and the latest issue of the basic specification, AMS 3731.

3.2 Material: Shall be an epoxy-based polymer with a curing agent.

3.3 Properties: The compound shall conform to the following requirements:

3.3.1 Mixed Uncured Compound: The compound, mixed in accordance with manufacturer's instructions, shall exhibit the following properties:

3.3.1.1 Viscosity: Shall be not greater than 10,000 centipoise (10.0 Pa·s) at 23°C (73°F), determined within 5 min. after mixing, using a Brookfield Model LVF viscometer and No. 3 spindle at 6 revolutions per minute.

3.3.1.2 Pot Life: Usable life of the compound, defined as the time to attain double the initial viscosity determined in 3.3.1.1, shall be not less than 30 min. at 23°C (73°F).

SAE Technical Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

AMS documents are protected under United States and international copyright laws. Reproduction of these documents by any means is strictly prohibited without the written consent of the publisher.

3.3.1.3 Curing Time: The time required to develop the cured product properties specified in 3.3.2 shall be not more than 5 days at 23°C (73°F) or not more than 2 hr at 95°C (200°F).

3.3.1.4 Demold Time: The time required before the part can be removed from the mold and retain its integrity shall be not more than 24 hr at 23°C (73°F).

3.3.2 Cured Product: The compound, mixed and cured in accordance with manufacturer's instructions, shall exhibit the following properties, determined in accordance with test methods listed in AMS 3731:

| | | |
|-----------|---|---|
| 3.3.2.1 | Flexural Strength, min | 9600 psi (52.5 MPa) |
| 3.3.2.2 | Izod Impact Strength, per unit of notch, min | 0.27 ft-lb per in. (14.5 J/m) |
| 3.3.2.3 | Compressive Strength, min | 14,000 psi (97 MPa) |
| 3.3.2.4 | Insulation Resistance | |
| 3.3.2.4.1 | At 23°C (73°F), min | 1x10 ⁶ megohms |
| 3.3.2.4.2 | At 120°C (250°F), min | 1x10 ³ megohms |
| 3.3.2.4.3 | After hydrolytic stability conditioning, min | 1x10 ⁴ megohms |
| 3.3.2.5 | Dielectric Constant at 1 KHz, max | 5.5 |
| 3.3.2.6 | Dissipation Factor at 1 KHz, max | 0.04 |
| 3.3.2.7 | Heat Deflection Temperature at 264 psi (1.8 MPa), min | 77°C (170°F) |
| 3.3.2.8 | Coefficient of Linear Thermal Expansion, max | |
| 3.3.2.8.1 | From -54°C to +23°C (-65°F to +73°F) | 35x10 ⁻⁶ mm/mm per deg C (20x10 ⁻⁶ in./in. per deg F) |
| 3.3.2.8.2 | From 23°C to 75°C (73°F to 165°F) | 50x10 ⁻⁶ mm/mm per deg C (27x10 ⁻⁶ in./in. per deg F) |
| 3.3.2.9 | Water Absorption after 24 hr immersion, max | 0.1% |
| 3.3.2.10 | Specific Gravity, max | 1.8 |