

Submitted for recognition as an American National Standard

Issued 1985-07-01
Revised 1990-10-01
Superseding AMS-3782/3

WEBBING, TEXTILE, TUBULAR, PARA-ARAMID
Intermediate Modulus
0.35 ounce per linear yard (14 g/linear m)

1. SCOPE:

1.1 Form: This specification covers one weight and type of para-aramid webbing.

1.2 Application: Primarily for use in the manufacture of parachutes and their accessories.

1.3 Classification: The webbing shall be a para-aramid tube with weight not more than 0.35 ounce per linear yard (14 g/linear m) and breaking strength not lower than 2000 pounds force (8896 N).

2. APPLICABLE DOCUMENTS: See AMS-3782.

3. TECHNICAL REQUIREMENTS:

3.1 Basic Specification: The complete requirements for procuring the webbing described herein shall consist of this document and the latest issue of the basic specification, AMS-3782.

3.2 Material: Shall conform to the following:

3.2.1 Yarn Twist: The warp yarns shall be twisted so as to have not less than 4 and 3 turns, respectively, for the 1000 and 1500 denier yarn. Filling yarns shall have the producer's twist only.

3.2.2 Weave: The webbing shall be tubular, plain weave, 1 up and 1 down.

3.3 Properties: Webbing shall conform to the following requirements, determined in accordance with test methods listed in the basic specification, AMS-3782:

SAE Technical Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.