

**AEROSPACE  
MATERIAL  
SPECIFICATION**

**SAE** AMS3792/1

**REV. B**

Issued 1983-10

Revised 1989-01

Stabilized 2012-02

Superseding AMS3792/1A

Tape, Low Modulus Aramid  
2 (51), 300 (1334) Breaking Strength

**RATIONALE**

This document has been determined to contain basic and stable technology which is not dynamic in nature.

**STABILIZED NOTICE**

This document has been declared "Stabilized" by SAE AMS P, Polymeric Materials Committee, and will no longer be subjected to periodic reviews for currency. Users are responsible for verifying references and continued suitability of technical requirements. Newer technology may exist.

SAENORM.COM : Click to view the full PDF of ams3792-1b

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2012 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

**TO PLACE A DOCUMENT ORDER:** Tel: 877-606-7323 (inside USA and Canada)  
Tel: +1 724-776-4970 (outside USA)  
Fax: 724-776-0790  
Email: CustomerService@sae.org  
http://www.sae.org

**SAE WEB ADDRESS:**

**SAE values your input. To provide feedback  
on this Technical Report, please visit  
<http://www.sae.org/technical/standards/AMS3792/1B>**

1. SCOPE:

1.1 Form: This specification covers one weight of low-modulus aramid tape.

1.2 Application: Primarily for use in construction of parachutes.

1.3 Classification: Low-modulus aramid tape having width of 2.0 inches (51 mm) and 300-pounds force (1334-N) breaking strength.

2. APPLICABLE DOCUMENTS: See AMS 3792.

3. TECHNICAL REQUIREMENTS:

3.1 Basic Specification: The complete requirements for procuring the tape described herein shall consist of this document and the latest issue of the basic specification, AMS 3792.

3.2 Construction and Properties:

3.2.1 Yarn:

3.2.1.1 Denier and Filament Count: The warp yarn shall be 200 denier  $\pm$  15 and shall consist of 100 filaments  $\pm$  15. The filling yarn shall be 100 denier  $\pm$  10 and shall consist of 50 filaments  $\pm$  10.

3.2.1.2 Ply: The warp and filling yarns shall be 1 ply.

SAENORM.COM : Click to view the full PDF of ams3792-1B