

**AEROSPACE  
MATERIAL  
SPECIFICATION**

**SAE** AMS3793/12

REV. A

Issued 1996-03

Stabilized 2013-09

Superseding AMS3793/12

Tape and Webbing, Textile, Para-Aramid  
Intermediate Modulus  
5/8 Inch (15.9 mm), 0.25 Ounces per Yard (7.75 g/m)

RATIONALE

This document has been determined to contain basic and stable technology which is not dynamic in nature.

STABILIZED NOTICE

This document has been declared "Stabilized" by SAE AMS P, Polymeric Materials Committee, and will no longer be subjected to periodic reviews for currency. Users are responsible for verifying references and continued suitability of technical requirements. Newer technology may exist.

SAENORM.COM : Click to view the full PDF of ams3793-12a

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2011 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)  
Tel: +1 724-776-4970 (outside USA)  
Fax: 724-776-0790  
Email: CustomerService@sae.org  
http://www.sae.org

SAE WEB ADDRESS:

**SAE values your input. To provide feedback  
on this Technical Report, please visit  
<http://www.sae.org/technical/standards/AMS3793/12A>**

## 1. SCOPE:

### 1.1 Form:

This specification covers one class of para-aramid tape and webbing of a single width and with varying weights.

### 1.2 Application:

See AMS 3793.

### 1.3 Classification:

Width of 5/8 inch  $\pm$  1/16 (15.9 mm  $\pm$  1.6) and weight classes as shown in Table 1.

TABLE 1 - Weight of Products

Class	Weight Ounces per Yard	Maximum g/m
1	0.25	7.75

## 2. APPLICABLE DOCUMENTS:

See AMS 3793.

SAENORM.COM : Click to view the full PDF of AMS3793-12A