

AEROSPACE MATERIAL SPECIFICATION



AMS 3793/4A

Issued APR 1986
 Revised MAR 1996

Superseding AMS 3793/4

Submitted for recognition as an American National Standard

TAPE AND WEBBING, TEXTILE, PARA-ARAMID
 Intermediate Modulus
 1 Inch (25 mm), 0.08 to 1.65 Ounces per Yard (2.5 to 51.2 g/m)

1. SCOPE:

1.1 Form:

This specification covers twelve classes of para-aramid tape and webbing of a single width and with varying weights.

1.2 Application:

See AMS 3793.

1.3 Classification:

Width of 1 inch \pm 1/16 (25.0 mm \pm 1.6) and weight classes as shown in Table 1.

TABLE 1 - Weight of Products

Class	Weight	Maximum
	Ounces per Yard	g/m
1	0.08	2.5
2	0.12	3.7
3	0.12	3.7
5	0.23	7.1
6	0.36	11.2
6a	0.36	11.2
7	0.52	16.1
8	0.55	17.1
9	1.00	31.0
9a	1.09	33.8
10	1.50	46.5
11	1.65	51.2
12	1.45	45.0

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

2. APPLICABLE DOCUMENTS:

See AMS 3793.

3. TECHNICAL REQUIREMENTS:**3.1 Basic Specification:**

The complete requirements for procuring the tape and webbing described herein shall consist of this document and the latest of the basic specification, AMS 3793.

3.2 Properties:

Tape and webbing shall conform to the requirements of Table 2 and the following:

3.2.1 Width: Shall be 1 inch \pm 1/16 (25 mm \pm 1.6).

3.2.2 Weight: Shall be as specified in 1.3 for the class ordered.

4. QUALITY ASSURANCE PROVISIONS:

See AMS 3793.

5. PREPARATION FOR DELIVERY:

See AMS 3793.

6. ACKNOWLEDGMENT:

See AMS 3793.

7. REJECTIONS:

See AMS 3793.

8. NOTES:

See AMS 3793.