

**AEROSPACE
MATERIAL
SPECIFICATION**

SAE AMS3798/12

REV. C

Issued 1983-10
Revised 1993-07
Reaffirmed 1998-08
Stabilized 2015-04

Superseding AMS3798/12B

Webbing, Low Modulus Aramid
1 (25) Wide, 9000 (40,034) Breaking Strength
Special Weave

RATIONALE

This document has been determined to contain basic and stable technology which is not dynamic in nature.

STABILIZED NOTICE

This document has been declared "Stabilized" by SAE AMS P, Polymeric Materials Committee, and will no longer be subjected to periodic reviews for currency. Users are responsible for verifying references and continued suitability of technical requirements. Newer technology may exist.

SAENORM.COM : Click to view the full PDF of AMS3798-12C

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2015 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
http://www.sae.org

SAE WEB ADDRESS:

**SAE values your input. To provide feedback
on this Technical Report, please visit
<http://www.sae.org/technical/standards/AMS3798/12C>**

1. SCOPE:

1.1 Form:

This specification covers one width and one breaking strength of low-modulus aramid webbing.

1.2 Application:

See AMS 3798.

1.3 Classification:

1 inch (25.4 mm) wide low-modulus aramid webbing having 9000 pounds force (40,034 N) breaking strength.

2. APPLICABLE DOCUMENTS:

The following publications form a part of this specification to the extent specified herein. The latest issue of SAE publications shall apply. The applicable issue of other publications shall be the issue in effect on the date of the purchase order.

2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

See AMS 3798.

SAENORM.COM : Click to view the full PDF of AMS3798-12C

3. TECHNICAL REQUIREMENTS:

3.1 Basic Specification:

The complete requirements for procuring the webbing described herein shall consist of this document and the latest issue of the basic specification, AMS 3798.

3.2 Construction and Properties:

3.2.1 Yarn: Yarn used in weaving the webbing shall be low-modulus aramid with a carbonization (char) temperature not lower than 355 °C (671 °F).

3.2.1.1 Denier and Filament Count: The yarn shall be 1200 denier \pm 15 and shall consist of 600 filaments \pm 15.

3.2.1.2 Ply: Final warp yarn shall be not less than four ply; binder warp shall be singles. Filling yarn shall be not less than two ply.

3.2.1.3 Twist: The final ply of yarn shall have not less than 2.5 turns per inch (25.4 mm) twist. The required denier and number of single yarns shall be twisted together (plied) in one operation.

3.2.2 Webbing: Shall conform to the following requirements:

3.2.2.1 Weave: Shall be as shown in Figure 1.

3.2.2.2 Color: Shall be FED-STD-595, Olive Green 106 solution dyed.

3.2.2.3 Width: Shall be 1.00 inch \pm 0.06 (25.4 mm \pm 1.5), determined in accordance with ASTM D 3774.

3.2.2.4 Thickness: Shall be 0.220 to 0.260 inch (5.59 to 6.60 mm), determined in accordance with ASTM D 1777.

3.2.2.5 Weight: Shall not exceed 4.10 ounces/yard (127.1 g/m), determined in accordance with ASTM D 3776.

3.2.2.6 Breaking Strength: Shall be not less than 9000 pounds force (40,034 N) unaged and not less than 85% of the unaged strength after aging, determined in accordance with FED-STD-191, Method 4108.

3.2.2.7 Thread Count: Total warp ends (face and back) shall be not less than 184 and binder warp ends shall be not less than 15, for a total of not less than 199 warp ends. Filling picks shall be not less than 18 per inch (25.4 mm).

3.3 Length and Put-up:

Webbing shall be furnished in rolls containing 90 to 110 yards (82 to 101 m). No roll shall contain more than three pieces and no piece shall be less than 10 yards (9 m) in length.

4. QUALITY ASSURANCE PROVISIONS:

See AMS 3798.

5. PREPARATION FOR DELIVERY:

See AMS 3798.

6. ACKNOWLEDGMENT:

See AMS 3798.

7. REJECTIONS:

See AMS 3798.

8. NOTES:

See AMS 3798.

- 8.1 The change bar (I) located in the left margin is for the convenience of the user in locating areas where technical revisions, not editorial changes, have been made to the previous issue of this specification. An (R) symbol to the left of the document title indicates a complete revision of the specification.

SAENORM.COM : Click to view the full PDF of ams3798_12C