

WEBBING, LOW MODULUS ARAMID  
1-23/32 (44) Wide, 7,300 (32,500) Breaking Strength  
Twill, Resin Treated

1. SCOPE:

- 1.1 Form: This specification covers one width and one strength of low-modulus aramid webbing.
- 1.2 Application: Primarily for use in construction of parachutes.
- 1.3 Classification: 1-23/32 in. (44 mm) wide low-modulus aramid webbing having 7,300 lb (32,500 N) breaking strength.

2. APPLICABLE DOCUMENTS: Shall be as shown in AMS 3798.

3. TECHNICAL REQUIREMENTS:

- 3.1 Basic Specification: The complete requirements for procuring the webbing described herein shall consist of this document and the latest issue of the basic specification, AMS 3798.
- 3.2 Construction and Properties:
- 3.2.1 Yarn: Yarn used in weaving the webbing shall be low-modulus aramid with a carbonization (char) temperature not lower than 355°C (670°F).
- 3.2.1.1 Denier and Filament Count: The yarn shall be 1,200 denier  $\pm$  15 and shall consist of 600 filaments  $\pm$  15.
- 3.2.1.2 Ply: Final warp yarn shall be not less than 2 ply and filling yarn shall be not less than 2 ply.
- 3.2.1.3 Twist: The final ply of yarn shall have not less than 2.5 turns per in. (25 mm) twist. The required denier and number of single yarns shall be twisted together (plied) in one operation.
- 3.2.2 Webbing: Shall conform to the following requirements:

SAE Technical Board rules provide that: "All technical reports, including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade or their use by governmental agencies is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."

- 3.2.2.1 Weave: Shall be as shown in Fig. 1.
- 3.2.2.2 Color: Shall be FED-STD-595, Olive Green 106 solution dyed, unless otherwise specified.
- 3.2.2.3 Width: Shall be 1.72 in.  $\pm$  0.06 (44.0 mm  $\pm$  1.5).
- 3.2.2.4 Thickness: Shall be 0.090 to 0.120 in. (2.25 to 3.00 mm).
- 3.2.2.5 Weight: Shall not exceed 2.40 oz per yd (74.4 g/m).
- 3.2.2.6 Breaking Strength: Shall be not less than 7,300 lb (32,500 N) unaged and not less than 85% of the unaged strength after aging (See 4.1).
- 3.2.2.7 Thread Count: Total warp ends (face and back) shall be not less than 305. Filling picks shall be not less than 17.
- 3.2.2.8 Resin Treatment: The webbing shall have an abrasion protective resin treatment. Treatment shall be polyvinyl butyral plasticized with butyl ricinoleate applied by water dispersion, dried, and cured to form a firmly adherent and evenly distributed deposit or coating on the yarns of the webbing. The curing of the resin shall be conducted within the range 115° - 180°C (240° - 360°F).
- 3.2.2.9 Extractable Matter: After resin treatment, the webbing shall contain not more than 8.5% by weight of matter extractable in methyl ethyl ketone.
- 3.3 Length and Put-up: Unless otherwise specified, webbing shall be furnished in rolls containing 90 - 110 yd (82 - 100 m). No roll shall contain more than 3 pieces and no piece shall be less than 10 yd (9 m) in length.
4. QUALITY ASSURANCE PROVISIONS: Shall be as in AMS 3798 and as follows:
- 4.1 Except for breaking strength, the physical and chemical values specified apply to the average of the determinations made on a sample unit for test purposes as specified in the applicable test methods. For breaking strength, the lot shall be rejected if the value of any individual determination is lower than the required minimum. The sample unit shall be as specified in the basic specification.
5. PREPARATION FOR DELIVERY: See AMS 3798.
6. ACKNOWLEDGMENT: See AMS 3798.
7. REJECTIONS: See AMS 3798.
8. NOTES: See AMS 3798.

This specification is under the jurisdiction of AMS Committee "C" (NOMETCOM).