

**AEROSPACE
MATERIAL
SPECIFICATION**

SAE AMS3798/16

REV. C

Issued 1983-11
Revised 1992-07
Reaffirmed 1997-10
Stabilized 2015-04

Superseding AMS3798/16B

Webbing, Low Modulus Aramid
1-1/2 (38) Wide, 1700 (7562) Breaking Strength
Special Weave

RATIONALE

This document has been determined to contain basic and stable technology which is not dynamic in nature.

STABILIZED NOTICE

This document has been declared "Stabilized" by SAE AMS P, Polymeric Materials Committee, and will no longer be subjected to periodic reviews for currency. Users are responsible for verifying references and continued suitability of technical requirements. Newer technology may exist.

SAENORM.COM : Click to view the full PDF of AMS3798-16C

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2015 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
http://www.sae.org

SAE WEB ADDRESS:

**SAE values your input. To provide feedback
on this Technical Report, please visit
<http://www.sae.org/technical/standards/AMS3798/16C>**

1. SCOPE:

1.1 Form:

This detail specification covers 1-1/2 inch (38.1 mm) wide aramid webbing having 1700 pounds force (7562 N) breaking strength.

1.2 Application:

See AMS 3798.

2. APPLICABLE DOCUMENTS:

See AMS 3798.

3. TECHNICAL REQUIREMENTS:

3.1 Basic Specification:

The complete requirements for procuring the webbing described herein shall consist of this document and the latest issue of the basic specification, AMS 3798.

3.2 Construction and Properties:

3.2.1 Yarn: Yarn used in weaving the webbing shall be low-modulus aramid with a carbonization (char) temperature not lower than 355 °C (671 °F).

3.2.1.1 Denier and Filament Count: The yarn shall be 1200 denier \pm 15 and shall consist of 600 filaments \pm 15.


3.2.1.2 Ply: Final warp yarn shall be one ply or more and filling yarn shall be one ply or more.

SAENORM.COM · Click to view the full PDF of ams3798_16C

3.2.1.3 Twist: The final ply of yarn shall have not less than 2.5 turns per inch (25.4 mm) twist. The required denier and number of single yarns shall be twisted together (plied) in one operation.

3.2.2 Webbing: Shall conform to the following requirements:

3.2.2.1 Weave: Shall be as shown in Figure 1.



- Face warp yarn
- ⊗ Back warp yarn
- ⊙ Binder warp yarn

FIGURE 1 - Weave Diagram

3.2.2.2 Color: Shall be FED-STD-595, Green No. 34088 solution dyed.

3.2.2.3 Width: Shall be 1.50 inches \pm 0.06 (38.1 mm \pm 1.5).

3.2.2.4 Thickness: Shall be 0.045 to 0.065 inch (1.14 to 1.65 mm).

3.2.2.5 Weight: Shall not exceed 1.35 ounces/yards (41.9 g/m).

3.2.2.6 Breaking Strength: Shall be not less than 1700 pounds force (7562 N) unaged and not less than 85% of the unaged strength after aging (See 4.1).

3.2.2.7 Thread Count: There shall be not less than 143 warp ends in the face and back, and not less than 34 binder ends, for a total of not less than 177 warp ends. There shall be not less than 47 filling picks per inch (25.4 mm).

3.3 Length and Put-up:

Webbing shall be furnished in rolls containing 90 to 110 yards (82 to 101 m). No roll shall contain more than three pieces and no piece shall be less than 10 yards (9 m) in length.