

CLOTH, PARACHUTE, META-ARAMID, LOW MODULUS
4.7(160) Weight, Twill

1. SCOPE:

- 1.1 Form: This specification covers one weight and one weave of low modulus meta-aramid cloth.
- 1.2 Application: Primarily for use in construction of parachutes.
- 1.3 Classification: 4.7 oz per sq yd (160 g/m²) low modulus meta-aramid cloth with twill weave.

2. APPLICABLE DOCUMENTS: See AMS 3801.

3. TECHNICAL REQUIREMENTS:

- 3.1 Basic Specification: The complete requirements for procuring the low modulus meta-aramid cloth described herein shall consist of this document and the latest issue of the basic specification, AMS 3801.

3.2 Construction and Properties:

- 3.2.1 Yarn: Yarn used in weaving the cloth shall be a low modulus meta-aramid with a carbonization (char) temperature not lower than 355°C (670°F).

- 3.2.1.1 Denier and Filament Count: The yarn shall be 200 denier \pm 15 and shall consist of 100 filaments \pm 10.

- 3.2.1.2 Ply: The yarn shall be 1 ply.

- 3.2.1.3 Twist: The final ply of yarn shall be twisted 4.0 to 4.4 turns per in. (25 mm).

3.2.2 Cloth:

- 3.2.2.1 Weave: Shall be 2-up, 2-down right-hand twill.

SAE Technical Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

AMS documents are protected under United States and international copyright laws. Reproduction of these documents by any means is strictly prohibited without the written consent of the publisher.