

AEROSPACE MATERIAL SPECIFICATION



AMS 3801/2A

Issued APR 1984
Revised JUL 1990
Reaffirmed JAN 2001

Superseding AMS 3801/2

Cloth, Parachute, Meta-Aramid, Low Modulus 6.5(220) Weight, Special Weave

1. SCOPE:

1.1 Form:

This specification covers one weight and one weave of low-modulus meta-aramid cloth.

1.2 Application:

Primarily for use in construction of parachutes.

1.3 Classification:

6.5 ounces per square yard (220 g/m²) low-modulus meta-aramid cloth with special weave.

2. APPLICABLE DOCUMENTS:

See AMS-3801.

3. TECHNICAL REQUIREMENTS:

3.1 Basic Specification:

The complete requirements for procuring the cloth described herein shall consist of this document and the latest issue of the basic specification, AMS-3801.

3.2 Construction and Properties:

3.2.1 Yarn: Yarn used in weaving the cloth shall be a low-modulus meta-aramid with a carbonization (char) temperature not lower than 355°C (671°F).

3.2.1.1 Denier and Filament Count: The yarn shall be 200 denier ± 15 and shall consist of 100 filaments ± 10.

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright 2001 Society of Automotive Engineers, Inc.
All rights reserved.

Printed in U.S.A.

QUESTIONS REGARDING THIS DOCUMENT:
TO PLACE A DOCUMENT ORDER:
SAE WEB ADDRESS:

(724) 772-7161
(724) 776-4970
<http://www.sae.org>

FAX: (724) 776-0243
FAX: (724) 776-0790

3.2.1.2 Ply: The yarn shall be 2 ply.

3.2.1.3 Twist: The final ply of yarn shall be twisted 2.5 to 2.8 turns per inch (25.4 mm).

3.2.2 Cloth:

3.2.2.1 Weave: Shall be as shown in Figure 1.

3.2.2.2 Color: Shall be Sage Green 1565 as shown in FED-STD-595. The color shall be obtained by the use of melt spun solution dyed yarn.

3.2.2.3 pH: Shall be 5.0 to 8.0, incl, determined on the water extract of the finished cloth.

3.2.2.4 Width: The width, inclusive of selvage, shall be as ordered.

3.2.2.5 Weight: Shall not exceed 6.5 ounces per square yard (220 g/m²).

3.2.2.6 Breaking Strength: Breaking strength of the unaged cloth shall be not less than 265 pounds force per inch (46,409 N/m) in both warp and fill directions. Breaking strength after heat aging shall be not less than 85% of the unaged values in both the warp and fill directions.

3.2.2.7 Elongation: Shall be not less than 25% in the warp and fill directions.

3.2.2.8 Tearing Strength: Shall be not less than 20 pounds force (89 N) in warp and fill directions.

3.2.2.9 Thickness: Shall not exceed 0.020 inch (0.51 mm).

3.2.2.10 Air Permeability: Shall be 50 - 80 cubic feet per minute for each square foot (15.5 - 24.5 m³/minute for each m²) of surface tested.

3.2.2.11 Count: Warp ends shall be not less than 63 per inch (25.4 mm). Filling picks shall be not less than 48 per inch (25.4 mm).

3.3 Length and Put-up:

The cloth shall be put up in rolls in accordance with PPP-P-1133. Each roll shall contain not less than 80 yards (73 m) nor more than 200 yards (183 m). Each roll of 100 yards (91 m) or less shall contain not more than 2 pieces and each roll over 100 yards (91 m) shall contain not more than 3 pieces. Each piece shall contain not less than 40 yards (37 m).

4. QUALITY ASSURANCE PROVISIONS:

See AMS-3801.

5. PREPARATION FOR DELIVERY:

See AMS-3801.

6. ACKNOWLEDGMENT:

See AMS-3801.

7. REJECTIONS:

See AMS-3801.

8. NOTES:

See AMS-3801.

SAENORM.COM : Click to view the full PDF of ams3801_2a

PREPARED UNDER THE JURISDICTION OF AMS COMMITTEE "P"