



AEROSPACE MATERIAL

AMS 3812

Society of Automotive Engineers, Inc. SPECIFICATION

400 COMMONWEALTH DRIVE, WARRENDALE, PA. 15096

Issued 4-15-78
Revised

RODS, GLASS FIBER/POLYESTER RESIN, COATED Pultrusion

1. SCOPE:

- 1.1 Form: This specification covers coated round rods manufactured by the pultrusion process from glass fiber roving and a weather-resistant polyester resin binder.
- 1.2 Application: Primarily for nonconductive tension elements in antenna supports where superior long-term weather resistance is required.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications (AMS) shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

- 2.1 SAE Publications: Available from Society of Automotive Engineers, Inc., 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

AMS 2350 - Standards and Test Methods

- 2.2 ASTM Publications: Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

ASTM D149 - Dielectric Breakdown Voltage and Dielectric Strength of Electrical Insulating Materials at Commercial Power Frequencies

ASTM D638 - Tensile Properties of Plastics

ASTM D695 - Compressive Properties of Rigid Plastics

ASTM D785 - Rockwell Hardness of Plastics and Electrical Insulating Materials

ASTM D790 - Flexural Properties of Plastics

ASTM D792 - Specific Gravity and Density of Plastics by Displacement

ASTM D2289 - Tensile Properties of Plastics at High Speeds

ASTM D2584 - Ignition Loss of Cured Reinforced Resins

ASTM D2648 - Measuring Time-to-Failure by Rupture of Plastics Under Tension in Various Environments

- 2.3 Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

2.3.1 Military Specifications:

MIL-R-60346 - Roving, Glass, Fibrous (For Filament Winding Applications)

2.3.2 Military Standards:

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes

MIL-STD-794 - Parts and Equipment, Procedures for Packaging and Packing of

SAE Technical Board rules provide that: "All technical reports, including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no agreement to adhere to any SAE standard recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its matter. Prospective users of the report are responsible for protecting themselves against infringement of patents."

3. TECHNICAL REQUIREMENTS:

3.1 Material: Shall be rods of circular cross section, manufactured by the pultrusion process from the necessary number of unidirectional, continuous, glass fiber rovings and a high-quality, weather-resistant, thermosetting polyester resin binder. The rods shall be coated for enhanced weatherability and resistance to handling damage.

3.1.1 Roving: Shall conform to MIL-R-60346, Type I, Class 2, and shall be free of splices.

3.1.2 Resin Binder: Shall be a high-quality, weather-resistant, thermosetting polyester, cross-linked with styrene. The resin formulation may contain a catalyst, a die lubricant, and additives for enhanced weather resistance, flame retardance, and anti-tracking qualities, but it shall not contain a wetting agent or a coupling agent, and shall be free of grease, oil, dirt, and other foreign matter.

3.1.3 Coating: Shall be primarily organic but may contain inorganic ingredients. It shall be applied uniformly over the cylindrical surfaces of the rods to a thickness of 0.010 in. \pm 0.005 (0.25 mm \pm 0.13).

3.1.3.1 The surfaces of coated rods shall be smooth, nonporous, and free of cracks. The coating shall not contain scratches, gouges, or other handling damage. Scuff marks and occasional blisters not exceeding one in any 5 ft (1.5 m), pits, or other manufacturing imperfections will be acceptable provided that they neither penetrate to the substrate nor protrude above the surface by more than 3% of the finished rod diameter.

3.1.3.2 The coating shall be flexible and well-adhered to the substrate, determined in accordance with 4.5.1 and 4.5.2.

3.2 Fabrication:

3.2.1 Pultrusion: Pultrusion of the rods shall be performed in accordance with best practices of the pultrusion industry.

3.2.2 Coiling: Coiling of rods (See 5.2.1), shall not be attempted until the rods have cooled to below 100° F (38° C). The coil diameter shall be not less than 300 times the rod diameter, unless rods have passed the coiled storage test in accordance with 4.5.11 utilizing a smaller coil diameter.

3.2.2.1 Rods furnished in straight lengths (See 5.2.1) shall not be cut from coils.

3.2.3 Post Curing: When specified by purchaser, straight rods not exceeding 10 ft (3 m) in length shall be post-cured for not less than 15 hr at 275° F \pm 10 (135° C \pm 5). The rods shall be fully supported during post curing to avoid warping.

3.3 Properties: The product shall conform to the following requirements; tests shall be performed on the product supplied and in accordance with specified test methods, insofar as practicable:

3.3.1 Tensile Strength, min	100,000 psi (690 MPa)	4.5.3
3.3.2 Stress-Rupture Strength, min	70,000 psi (483 MPa)	4.5.4
3.3.3 Flexural Strength, min		4.5.5
At 68° - 86° F (20° - 30° C)	100,000 psi (690 MPa)	
At -70° F \pm 5 (-57° C \pm 3)	90,000 psi (621 MPa)	

3.3.4	Vibration Fatigue Strength At 70 000 psi (483 MPa)	Pass	4.5.6
3.3.5	Dielectric Strength, min Dry	100 V per mil (3.99 MV/m)	4.5.7
	Wet	40 V per mil (1.57 MV/m)	
3.3.6	Fiber Content	Qualification Value $\pm 3\%$	4.5.8
3.3.7	Hardness, Rockwell E	Qualification Value ± 10	4.5.9
3.3.8	Transverse Tensile Strength	Qualification Value $\pm 20\%$	4.5.10
3.3.9	Density	Qualification Value $\pm 10\%$	ASTM D792

3.4 Quality: The product shall be uniform in quality and condition, smooth, and free from foreign materials and from internal and external imperfections detrimental to fabrication, appearance, or performance of parts.

3.5 Tolerances: Unless otherwise specified, the following tolerances shall apply:

3.5.1 Diameter: $\pm 3\%$ of nominal.

3.5.2 Length:

TABLE I

Nominal Length, Feet	Tolerance, Feet
Up to 10, incl	+0.10, -0
Over 10 to 50, incl	+0.25, -0
Over 50	+1.0, -0

TABLE I (SI)

Nominal Length, Metres	Tolerance, Metres
Up to 3, incl	+0.03, -0
Over 3 to 15, incl	+0.08, -0
Over 15	+0.3, -0

3.5.3 Straightness: The departure from straightness for rods furnished in straight lengths shall not exceed ± 0.04 in. per ft (3.3 mm per m) of length.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection: The vendor of rods shall supply all samples and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.6. Purchaser reserves the right to perform such confirmatory testing as he deems necessary to ensure that the rods conform to the requirements of this specification.

4.2 Classification of Tests:

- 4.2.1 **Acceptance Tests:** Tests to determine conformance to material (3.1), tensile strength (3.3.1), fiber content (3.3.6), hardness (3.3.7), transverse tensile strength (3.3.8), density (3.3.9), quality (3.4), and tolerance (3.5) requirements are classified as acceptance tests.
- 4.2.2 **Periodic Tests:** Tests to determine conformance to flexural strength (3.3.3) requirements are classified as periodic tests.
- 4.2.3 **Qualification Tests:** Tests to determine conformance to all technical requirements of this specification are classified as qualification tests except that the coiled storage test (4.5.11) is not required unless rod is to be supplied in coil diameters less than 300 times the rod diameter.
 - 4.2.3.1 For direct U.S. Military procurement, substantiating test data and, when requested, qualification test material shall be submitted to the cognizant qualification agency as directed by the procuring activity, the contracting officer, or the request for procurement.

4.3 Sampling:

- 4.3.1 **Acceptance Tests:** Shall be in accordance with Single Sampling for Normal Inspection, General Inspection Level II, with an Acceptable Quality Level (AQL) of 2.5 specified in MIL-STD-105, as shown in Table II. Sufficient test material shall be taken from inspection units selected at random from each production lot to perform all required tests and to allow for invalid tests. The number of specimens for each test shall be as specified in the applicable test procedure or, if not specified therein, not less than three.
 - 4.3.1.1 **Lot:** Shall be all rod produced from the same batches of ingredients, using the same processing conditions on the same machine, in a period not longer than 24 hr, and submitted for vendor's inspection at one time.
 - 4.3.1.2 **Inspection Unit:** Shall be each coil or 1000 ft (300 m) of rod, whichever is smaller, using both ends of each coil.

TABLE II

Number of Inspection Units in the Lot	Number of Inspection Units from Which Samples are to be Taken	Number of Nonconforming Samples to	
		Accept	Reject
1 - 50	8(4.3.1.2.1)	0	1
51 - 90	13	1	2
91 - 150	20	1	2
151 - 280	32	2	3
281 - 500	50	3	4

- 4.3.1.2.1 If the number of inspection units to be sampled equals or exceeds the lot size, inspect each unit.
- 4.3.1.3 **Reduced Inspection:** After 10 consecutive lots meet Table II requirements, inspection sampling may be reduced for the product of that machine to Special Inspection Level S-1, MIL-STD-105, wherein the Single Sample Size is 3 and the Acceptance Number is 0. Should any rejections occur, sampling shall be returned to that of Table II for at least 10 consecutive satisfactory production lots.

4.3.2 Periodic Tests: The frequency and sampling plan for periodic tests shall be as agreed upon by purchaser and vendor.

4.3.3 Qualification Tests: Shall be as agreed upon by purchaser and vendor.

4.4 Approval:

4.4.1 Sample rod shall be approved by purchaser before rod for production use is supplied, unless such approval be waived. Results of tests on production rod shall be essentially equivalent to those on the approved sample.

4.4.2 Vendor shall use ingredients, manufacturing procedures, processes, and methods of inspection on production rod which are essentially the same as those used on the approved sample rod. If any change is necessary in ingredients, in type of processing, or in manufacturing procedures, vendor shall submit for reapproval a statement of the proposed changes in material and processing and, when requested, sample rod. Production rod made to the revised procedure shall not be shipped prior to receipt of reapproval.

4.5 Test Methods:

4.5.1 Coating Flexibility: Shall be determined in accordance with ASTM D2289 using a specimen of full-diameter rod having length not exceeding 50 times the rod diameter. The specimen shall be subjected to an axial stress of 70,000 psi (483 MPa) using a testing speed which attains the required tensile load in not more than one second. Any loading method which meets this requirement may be used, including high-speed testing machines and drop weights. The specimen shall be examined, using magnification not over 10X, not less than 12 hr after the load is removed. Hairline cracks in the coating in a direction transverse to the rod axis or other evidence of coating damage are not acceptable.

4.5.2 Coating Adhesion: Shall be determined using a specimen of full-diameter rod. A transverse saw cut shall be made on the surface of the specimen to a depth of 1/4 to 1/3 of the rod diameter. Using the point of a sharp instrument, such as a penknife, or surgical blade, at the edges of the saw cut, attempt to pry off the coating. If a single piece of coating having a surface area greater than 1/8 in. (3 mm) square can be flaked off cleanly from the substrate, the rod is not acceptable.

4.5.3 Tensile Strength: Shall be determined in accordance with ASTM D638. The specimen shall be a full-diameter rod having length not less than 100 times the rod diameter, to which high-performance end fittings or grips have been attached. The specimen shall be loaded to a tensile stress of 100,000 psi (690 MPa) and the load maintained for not less than one min. without visible or audible evidence of incipient failure. A mechanical failure of the specimen initiating in an end fitting or grip prior to completion of the one-min. interval shall constitute an invalid test. In case of dispute between purchaser and vendor, results obtained using end fittings or grips conforming to the vendor's specifications shall govern.

4.5.4 Stress-Rupture Strength: Stressed exposure to simulated weather conditions shall be determined in accordance with ASTM D2648 and as follows:

4.5.4.1 The specimen shall be a full-diameter rod having length not less than 50 times the rod diameter, to which suitable end fittings or grips have been attached. The specimen, not including the end fittings or grips, shall be exposed for not less than 240 hr in an environmental chamber maintained at $160^{\circ}\text{F} \pm 5$ ($71^{\circ}\text{C} \pm 3$) and saturated humidity conditions, while under a constant load sufficient to produce an initial tensile stress of 70,000 psi (483 MPa). The rod shall exhibit no structural damage, deterioration, or other evidence of incipient failure. A mechanical failure of the specimen initiating in an end fitting or grip prior to completion of the 240 hr interval shall constitute an invalid test. In case of dispute between purchaser and vendor, results obtained using end fittings or grips conforming to the vendor's specifications shall govern.

- 4.5.5 Flexural Strength: Shall be determined in accordance with ASTM D790 using specimens of full-diameter rod, three-point loading, and a span-to-diameter ratio of 40.
- 4.5.6 Vibration Fatigue Strength: Shall be determined using a full-diameter rod having length not less than 300 times the rod diameter subjected to forced, transverse vibration at a resonance frequency between 45 and 90 Hz while under an axial tensile stress of 70,000 psi (483 MPa). The double amplitude of vibration at an anti-node point shall be not less than twice the rod diameter. Specimens shall exhibit no evidence of damage after 100,000,000 cycles.
- 4.5.7 Dielectric Strength: Shall be determined in accordance with ASTM D149, short time test, using disk specimens having length approximately equal to the rod diameter or 0.50 in. (12.7 mm). Tests shall be performed with the specimens under oil, using a voltage rise of 500 V/sec at a frequency of 60 Hertz. Dry specimens shall be conditioned at 77° F ± 9 (25° C ± 5) and relative humidity of 50% ± 5 for not less than 24 hr prior to testing. Wet specimens shall be tested immediately after immersion in boiling distilled water for not less than 2 hours.
- 4.5.7.1 Disk specimens shall be cut from full-diameter rod using a water-cooled, diamond cut-off saw, or equivalent, to obtain faces which are smooth and parallel, perpendicular to the rod axis, and not frayed at the edges. The water shall be blotted from the disks carefully, immediately after cutting.
- 4.5.8 Fiber Content: Shall be calculated by subtracting the resin content of a rod sample from 100%. The resin content shall be determined in accordance with ASTM D2584.
- 4.5.9 Hardness: Shall be determined in accordance with ASTM D785, Procedure A, on the faces of disk specimens prepared as in 4.5.7.1.
- 4.5.10 Transverse Tensile Strength: Shall be determined using a disk specimen having a thickness approximately equal to one-half the rod diameter, prepared in accordance with 4.5.7.1. The specimen shall be mounted on edge in a compression tool (See ASTM D695) in a testing machine, and loaded diametrically to failure in compression. The transverse tensile strength shall be calculated with the equation:

$$T = \frac{2P}{\pi td}$$

where T = transverse tensile strength, psi (MPa)

P = maximum applied load indicated by testing machine, lbf (MN)

t = thickness of specimen, in. (m)

d = rod diameter, in. (m)

- 4.5.11 Coiled Storage: Shall be determined using a coil consisting of not less than three full turns of finished rod packaged for shipment in the manner used by the vendor (See 5.2.2). The packaged coil shall be exposed for not less than 72 hr to a temperature not lower than 200° F (95° C) in a circulating-air chamber while suspended by wires from the ceiling of the chamber so that no part of the package contacts the ceiling, floor, or walls of the chamber. Inspection of the coil immediately following the exposure shall reveal no localized buckles or other structural damage in the rod which cause permanent distortion of the rod shape.

4.6 Reports:

- 4.6.1 The vendor of rod shall furnish with each shipment three copies of a report showing the results of tests to determine conformance to the acceptance test requirements and stating that the rod conforms to the other technical requirements of this specification. This report shall include the purchase order number, AMS 3812, vendor's product identification, size, lot number, and quantity.