

Submitted for recognition as an American National Standard

**CORD, CORELESS, PARA-ARAMID
Intermediate Modulus
1500 lb (6670 N), 200 ft per lb (135 m/kg)**

1. SCOPE:

- 1.1 Form: This specification covers one strength and weight of braided para-aramid cord.
- 1.2 Application: Primarily for use in cargo type parachutes.
- 1.3 Classification: The minimum breaking strength is 1500 lb (6670 N) and the minimum weight is 200 ft per lb (135 m/kg).

2. APPLICABLE DOCUMENTS: See AMS 3814.

3. TECHNICAL REQUIREMENTS:

3.1 Basic Specification: The complete requirements for procuring the cord described herein shall consist of this document and the latest issue of the basic specification, AMS 3814.

3.2 Properties: Cord shall conform to the following requirements:

- | | |
|--|--------------------------|
| 3.2.1 Breaking Strength, min | 1500 lb (6670 N) |
| 3.2.2 Weight, min | 200 ft per lb (135 m/kg) |
| 3.2.3 Number of Carriers | 16 |
| 3.2.4 Distance between Carrier Run-Offs, min | 25 ft (7.6 m) |
| 3.2.5 Ends per Carrier | 1 |

SAE Technical Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

AMS documents are protected under United States and international copyright laws. Reproduction of these documents by any means is strictly prohibited without the written consent of the publisher.