

AEROSPACE MATERIAL SPECIFICATION

Submitted for recognition as an American National Standard



AMS 3829B

Issued APR 1982
Revised OCT 1993
Reaffirmed SEP 1998

Superseding AMS 3829A

Cloth, Type "E"-Glass, Style 7781 Fabric Solution-Addition-Type PMR-15 Polyimide Resin Impregnated

1. SCOPE:

1.1 Form:

This specification covers one type of glass cloth impregnated with a heat-reactive, thermosetting, solution-addition-type PMR-15 polyimide resin system, supplied in the form of continuous rolls of full width cloth or slit tape.

1.2 Applications:

This cloth has been used typically for structural laminates requiring high strength and heat resistance for long-term service up to 290 °C (554 °F) and short-time service up to 315 °C (599 °F), but usage is not limited to such applications.

1.3 Safety-Hazardous Materials:

While the materials, methods, applications, and processes described or referenced in this specification may involve the use of hazardous materials, this specification does not address the hazards which may be involved in such use. It is the sole responsibility of the user to ensure familiarity with the safe and proper use of any hazardous materials and to take necessary precautionary measures to ensure the health and safety of all personnel involved.

2. APPLICABLE DOCUMENTS:

The following publications form a part of this specification to the extent specified herein. The latest issue of SAE publications shall apply. The applicable issue of other publications shall be the issue in effect on the date of the purchase order.

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright 1998 Society of Automotive Engineers, Inc.
All rights reserved.

Printed in U.S.A.

QUESTIONS REGARDING THIS DOCUMENT:
TO PLACE A DOCUMENT ORDER:
SAE WEB ADDRESS:

(724) 772-7154
(724) 776-4970
<http://www.sae.org>

FAX: (724) 776-0243
FAX: (724) 776-0790

2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

AMS 2825 Material Safety Data Sheets

AMS 3824 Cloth, Type "E" Glass, Finished for Resin Laminates

2.2 ASTM Publications:

Available from ASTM, 100 Barr Harbor Drive, West Conshohocken, PA 19428-2959.

ASTM D 638 Tensile Properties of Plastics

ASTM D 638M Tensile Properties of Plastics (Metric)

ASTM D 790 Flexural Properties of Unreinforced and Reinforced Plastics and Electrical Insulating Materials

ASTM D 790M Flexural Properties of Unreinforced and Reinforced Plastics and Electrical Insulating Materials (Metric)

ASTM D 792 Specific Gravity (Relative Density) and Density of Plastics by Displacement

ASTM D 2344 Apparent Interlaminar Shear Strength of Parallel Fiber Composites by Short Beam Method

ASTM D 2734 Void Content of Reinforced Plastics

2.3 U.S. Government Publications:

Available from DODSSP, Subscription Services Desk, Building 4D, 700 Robbins Avenue, Philadelphia, PA 19111-5094.

MIL-STD-2073-1 DOD Materiel, Procedures for Development and Application of Packaging Requirements

3. TECHNICAL REQUIREMENTS:

3.1 Material:

Shall be the reinforcement specified in 3.1.1, impregnated with the resin system specified in 3.1.2, supplied as rolls of full width impregnated cloth or as slit tape, as ordered, and in a condition suitable for in situ polymerization by vacuum/autoclave processing at 290 °C (554 °F) under 100 psi (689 kPa) pressure.

3.1.1 Reinforcement: Shall be AMS 3824 Type "E" Glass cloth, Style 7781, treated with a suitable finish to produce the required performance characteristics with the resin system specified in 3.1.2.

3.1.2 Resin: Shall be a heat-reactive, thermosetting monomeric reactants solution-addition-type PMR-15 polyimide resin system resulting in a prepolymer polyimide resin system with a 1500 formula molecular weight.

3.2 Storage Life:

Cloth shall have a storage life of not less than three months from the date of impregnation when stored or shipped in a barrier container and maintained at not warmer than 7 °C (45 °F).

3.3 Working Life:

Cloth shall meet the requirements of 3.4 and 3.5 when tested, after warming to room temperature, at any time up to five days after removal from storage at not warmer than 7 °C (45 °F).

3.4 Properties:

Cloth shall conform to the following requirements:

3.4.1 Uncured Impregnated Cloth: Shall have the following properties, determined on the product supplied, sampled in accordance with 4.3.1 after warming to above the dew point, and tested in accordance with 4.5.2:

3.4.1.1 Volatile Content: 9% ± 2

3.4.1.2 Resin Content by weight: 38% ± 3

3.4.2 Cured Laminates: Shall have the properties shown in Table 1, determined on specimens cut from a test laminate prepared as in 4.5.1. Specimens for elevated temperature tests shall be tested after exposure for 30 minutes ± 1 at the test temperature. Property values specified in 3.4.2.1 through 3.4.2.4 are the minimum averages for five determinations for each test; no individual value shall be less than 90% of the minimum average value specified.

TABLE 1 - Properties of Cured Laminates

Paragraph	Property	Requirement (See 8.2)	Test Method
3.4.2.1	Tensile Strength, minimum average At 25 °C ± 5 (77 °F ± 9) At 288 °C ± 5 (550 °F ± 9)	55.0 ksi (379 MPa) 50.0 ksi (345 MPa)	ASTM D 638 or ASTM D 638M Type 1 Specimen
3.4.2.2	Flexural Strength, minimum average At 25 °C ± 5 (77 °F ± 9) At 288 °C ± 5 (550 °F ± 9)	65.0 ksi (448 MPa) 50.0 ksi (345 MPa)	ASTM D 790 or ASTM D 790M
3.4.2.3	Flexural Strength, minimum average At 25 °C ± 5 (77 °F ± 9) At 288 °C ± 5 (550 °F ± 9)	3.3 Msi (22.8 GPa) 3.0 Msi (20.7 GPa)	ASTM D 790 or ASTM D 790M
3.4.2.4	Short-Beam Shear Strength, minimum average At 25 °C ± 5 (77 °F ± 9) At 288 °C ± 5 (550 °F ± 9)	6000 psi (41.4 MPa) 3300 psi (22.8 MPa)	ASTM D 2344
3.4.2.5	Specific Gravity At 23/23 °C (73/73 °F)	±0.10 Preproduction	ASTM D 792 Value
3.4.2.6	Void Content, maximum	3.0%	ASTM D 2734 Method A

3.5 Quality:

Cloth, as received by purchaser, shall be uniform in quality and condition, clean, and free from foreign materials and from imperfections detrimental to usage of the cloth.

3.6 Tolerances:

Width shall not vary more than +1/2 inch (+12.7 mm), -0 from the width ordered.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection:

The manufacturer of impregnated cloth shall supply all samples for required tests and shall be responsible for performing all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the cloth conforms to the requirements of this specification.

4.2 Classification of Tests:

4.2.1 Acceptance Tests: Tests for requirements shown in Table 2 are acceptance tests and shall be performed to represent each lot.

TABLE 2 - Acceptance Tests

Requirement	Paragraph Reference
Volatile Content, uncured	3.4.1.1
Resin Content, uncured	3.4.1.2
Flexural Strength	3.4.2.2
Flexural Modulus	3.4.2.3
Short-Beam Shear Strength	3.4.2.4
Specific Gravity, cured	3.4.2.5
Void Content, cured	3.4.2.6

4.2.2 Preproduction Tests: Tests for all technical requirements are preproduction tests and shall be performed prior to or on the initial shipment of impregnated cloth to a purchaser, when a change in ingredients and/or processing requires reapproval as in 4.4.2, and when purchaser deems confirmatory testing to be required.

4.2.2.1 For direct U.S. Military procurement, substantiating test data and, when requested, preproduction test material shall be submitted to the cognizant agency as directed by the procuring activity, contracting officer, or request for procurement.

4.3 Sampling and Testing:

Shall be as follows:

4.3.1 For Acceptance Tests: Each lot of impregnated cloth shall be sampled at random on sampling schedule shown in Table 3, using the number of specimens specified therein for each requirement. Samples for the panels required for testing the cured product shall be taken in approximately equal amounts from three locations in the lot, selected randomly. There shall be not more than 500 yards (457 m) of cloth, full width, represented in any one test panel; lots of greater quantity shall require one panel for each 500 yards (457 m) or portion thereof.

TABLE 3 - Acceptance Test Sampling

Requirement	Sampling	Minimum Number of Specimens
Volatile Content, uncured	Every Roll	2
Resin Content, uncured	Lot Basis	2
Flexural Strength	Lot Basis	5
Flexural Modulus	Lot Basis	5
Short-Beam Shear Strength	Lot Basis	5
Specific Gravity, cured	Lot Basis	2 from each test laminate
Void Content, cured	Lot Basis	2 from each test laminate

- 4.3.1.1 A lot shall be all cloth treated at one time without significant changes in treater setting using a single batch of resin and reinforcement and presented for manufacturer's inspection at one time. A lot shall not exceed 2000 yards (1829 m) of full width product.
- 4.3.1.2 When a statistical sampling plan has been agreed upon by purchaser and manufacturer, sampling shall be in accordance with such plan in lieu of sampling as in 4.3.1 and the report of 4.6 shall state that such plan was used.
- 4.3.2 For Preproduction Tests: As agreed upon by purchaser and manufacturer.
- 4.4 Approval:
- 4.4.1 Sample cloth shall be approved by purchaser before cloth for production use is supplied, unless such approval be waived by purchaser. Results of tests on production cloth shall be essentially equivalent to those on the approved sample.
- 4.4.2 Manufacturer shall use ingredients, manufacturing procedures, processes, and methods of inspection on production cloth which are essentially the same as those used on the approved sample cloth. If necessary to make any change in ingredients, in type of equipment for processing, or in manufacturing procedures, manufacturer shall submit for reapproval a statement of the proposed changes in ingredients and/or processing and, when requested, sample cloth. Production cloth made by the revised procedure shall not be shipped prior to receipt of reapproval.
- 4.5 Test Methods:
- 4.5.1 Specimen Preparation: Each roll to be sampled shall be allowed to warm above the dew point before opening the sealed package for sampling. Immediately after sampling, the roll shall be resealed and returned to storage at not higher than 7 °C (45 °F).
- 4.5.1.1 Tests of Uncured Product: Specimens shall be cut from test cloth and tested immediately as specified in the applicable test procedure.

4.5.1.2 Preparation of Test Laminate Panels:

4.5.1.2.1 Laminate panels from which all specimens are cut shall be composed of 14 plies, all face up, in makeup with ply orientation at 0 to 90 degrees. Laminate panel dimensions shall be sufficient to yield all specimens required for tests.

4.5.1.2.2 All test laminate panels shall be fabricated by vacuum bag/autoclave method under process parameters of 100 psi (689 kPa) and 288 °C (550 °F). Each test laminate shall be subjected to a postcure of 12 hours ± 0.25 at 315 °C ± 3 (599 °F ± 5) in an air environment prior to any specimen preparation or test.

4.5.2 Volatile and Uncured Resin Contents: Shall be determined as follows:

4.5.2.1 Cut a single-ply specimen of impregnated cloth nominally 4 inches (102 mm) square and weigh. Record weight as W_1 . Place the specimen in an oven preset to, and maintained at, 165 °C (329 °F) and heat at 165 °C ± 3 (329 °F ± 5) for five to seven minutes. Remove specimen from oven, cool, and reweigh. Record weight as W_2 .

4.5.2.2 Place the specimen on which volatile content was determined in a muffle furnace preset to, and maintained at, 565 °C (1049 °F); hold at 565 °C ± 5 (1049 °F ± 9) for not less than 30 minutes. Remove specimen from furnace, cool, and reweigh. Record weight as W_3 .

4.5.2.3 Calculate volatile content and resin content using Equation 1 and Equation 2, respectively.

$$\text{Volatile Content, \%} = \frac{W_1 - W_2}{W_1} \times 100 \quad (\text{Eq. 1})$$

$$\text{Resin Solids Content, \%} = \frac{W_2 - W_3}{W_2} \times 100 \quad (\text{Eq. 2})$$

4.6 Reports:

The supplier of impregnated cloth shall furnish with each shipment a report showing the results of tests to determine conformance to the acceptance test requirements and stating that the cloth conforms to the other technical requirements. This report shall include the purchase order number, lot number, AMS 3829B, manufacturer's material designation, cure cycle for each test panel and panel parameters, roll numbers, and quantity.

4.6.1 The supplier of impregnated cloth product shall furnish with each lot a statement that the product provided is "E" glass cloth impregnated with the PMR-15 resin binder system.

4.6.2 The supplier of impregnated cloth shall furnish with each lot a statement that purity of monomers and solvent used conformed to the following requirements:

4,43 - Methylenedianiline (MDA) - % MDA - 95% minimum
Melting Point - 90 °C (190 °F) minimum
Aniline Impurity - 0.1% maximum

Dimethyl Ester of 3,33 - Benzophenonetetracarboxylic Acid (BTDE) -
% Dimethyl ester of BTDE as measured

Monomethyl Ester of 5 - Norbornene - 2,3 - Dicarboxylic Acid (N,E)
Melting Point - 100 °C (212 °F) minimum

Anhydrous Methyl Alcohol - % Methyl Alcohol - 99.8% minimum
Acidity (Acetic Acid) - 0.003 % by weight, maximum

Alkalinity (Ammonium Hydroxide) - 0.0003 % by weight, maximum

Acetone - 0.003 % by weight, maximum

4.6.3 A material safety data sheet conforming to AMS 2825, or equivalent, shall be supplied to each purchaser prior to, or concurrent with, the report of preproduction test results, or, if preproduction testing be waived by purchaser, concurrent with the first shipment of cloth for production use. Each request for modification of formulation shall be accompanied by a revised data sheet for the proposed formulation.

4.7 Resampling and Retesting:

If any specimen used in the above tests fails to meet the specified requirements, disposition of the cloth may be based on the results of testing three additional specimens for each original nonconforming specimen. These specimens shall be cut from additional or newly-prepared panels using the same procedures and curing cycles as used on the original panels. Failure of any retest specimen to meet the specified requirements shall be cause for rejection of the cloth represented. Results of all tests shall be reported.

5. PREPARATION FOR DELIVERY:

5.1 Packaging and Identification:

5.1.1 A lot of cloth may be packaged in small quantities and delivered under the basic lot approval provided lot identification is maintained.

5.1.2 Impregnated cloth shall be shipped in rolls with ID not less than 3 inches (76 mm).

5.1.3 Cloth shall be interleaved with a nonadhering, colored separator to provide an outer wrapping with not less than a 2-inch (51-mm) overlap.