

Submitted for recognition as an American National Standard

CLOTH, NYLON, METALLIZED
Untreated

1. SCOPE:

1.1 Form: This specification covers one type of metallized nylon cloth.

1.2 Application: Primarily for use in aerial tow targets.

1.3 Classification: Untreated metallized nylon cloth.

2. APPLICABLE DOCUMENTS: See AMS 3848.

3. TECHNICAL REQUIREMENTS:

3.1 Basic Specification: The complete requirements for procuring the metallized cloth described herein shall consist of this document and the latest issue of the basic specification, AMS 3848.

3.2 Properties: Shall conform to the requirements of Table I, Table II, and the following, determined in accordance with test methods specified in the basic specification:

3.2.1 Air Permeability: Shall not change more than +15%.

3.2.2 Thickness: Shall not change more than +10%.

3.2.3 Shrinkage: Shall not shrink more than 2% in the warp direction nor more than 1% in the filling direction.

3.2.4 Electrical Conductivity: The metallized cloth shall show resistance not greater than 10 ohms per square.

SAE Technical Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

AMS documents are protected under United States and international copyright laws. Reproduction of these documents by any means is strictly prohibited without the written consent of the publisher.

4. QUALITY ASSURANCE PROVISIONS: See AMS 3848.
5. PREPARATION FOR DELIVERY: See AMS 3848.
6. ACKNOWLEDGMENT: See AMS 3848.
7. REJECTIONS: See AMS 3848.
8. NOTES: See AMS 3848.

TABLE I

BASE CLOTH REQUIREMENTS

Property	Requirement
Thread Count per in. (25.4 mm)	
Warp	40
Filling	22
Ply	
Warp	Singles
Filling	2
Twist, turns per in. (25.4 mm), min	
Warp	6
Filling	
Singles	3
Ply	6
Width (as specified)	36-1/2 in. + 1 or 72 in. + 3 (912 mm \pm 25 or 1800 mm \pm 75)
Thickness, max	0.0170 in. (0.425 mm)
Weight, max	3.25 oz per sq yd (110 g/m ²)
Breaking Strength, min	
Warp	100 lb per in. (17,500 N/m)
Filling	125 lb per in. (21,900 N/m)
Tearing Strength, min	
Warp	8 lb (35 N)
Filling	8 lb (35 N)
Air Permeability at 5 in. (125 mm) water pressure differential	3850 to 4000 cu ft/min. per sq ft (1155 to 1200 m ³ /min. per m ²)