



AEROSPACE MATERIAL SPECIFICATION

AMS 3894/1

Society of Automotive Engineers, Inc.
TWO PENNSYLVANIA PLAZA, NEW YORK, N.Y. 10001

Issued 11-15-72
Revised

GRAPHITE FIBER TAPE AND SHEET

Epoxy Resin Impregnated

G 110,000 (758) Tensile, 27,000,000 (186) Modulus, 350 (177)

1. SCOPE:

- 1.1 **Form:** This specification covers one type of epoxy-resin-impregnated graphite fibers in the form of tape and sheet.
- 1.2 **Application:** Primarily for use in structural composites requiring high modulus of elasticity in tension at temperatures up to 350 F (177 C).
- 1.3 **Classification:** G 110,000 psi (758 MPa) tensile strength, 27,000,000 psi (186 GPa) tensile modulus graphite fiber impregnated with epoxy resin for service at temperatures up to 350 F (177 C).

2. APPLICABLE DOCUMENTS:

Shall be as shown in AMS 3894.

3. TECHNICAL REQUIREMENTS:

- 3.1 **Basic Specification:** The complete requirements for procuring the product described herein shall consist of this document and the latest issue of the basic specification, AMS 3894.
- 3.2 **Material:** The product shall be AMS 3892/2 high modulus graphite fibers impregnated with epoxy resin formulated to meet the requirements specified herein.
- 3.2.1 **Storage Life:** The product shall meet the requirements of this specification when tested at any time up to 3 months from the date of receipt by the purchaser provided it has been stored at a maximum temperature of 0 F (-18C) in the original containers.
- 3.2.2 **Working Life:** The product shall meet the requirements of this specification when tested after exposure at a relative humidity not higher than 70% and at room temperature for a continuous period of up to 14 days.
- 3.3 **Properties of Uncured Impregnated Product:** The properties of the uncured product shall be as specified below. Tests shall be performed on the product after warming to above the dew point prior to sampling and in accordance with the test methods listed in the basic specification.

- | | |
|---|------------------------------|
| 3.3.1 Volatile Content, % by weight, max | 2 |
| Test temperature: | 250 F + 10 (121.1 C + 5.6) |
| Test time: | 60 min. ± 5 |
| 3.3.2 Total Nonfiber Content, % by weight | 42 ± 3 |
| 3.3.3 Resin Flow, % by weight | 10 - 30 |
| 3.3.4 Gel Time, min. | Qualification
Value ± 20% |
| 3.3.5 Tack | Shall adhere for
30 min. |

SAE Technical Board rules provide that: "All technical reports, including standards, approvals, and practices recommended, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."

- 3.4 Properties of Cured Laminate: The properties of cured product shall be determined on specimens cut from a test panel prepared as specified in the basic specification and tested in accordance with the methods specified therein.
- 3.4.1 Mechanical Properties: Shall be as specified in Table I.
- 3.4.2 Density: Shall be determined on the test laminate used to determine mechanical properties; values for each test laminate shall be reported. Fiber density and cured resin density shall also be reported.
- 3.4.3 Void Content: Shall not be greater than 3 %
4. QUALITY ASSURANCE PROVISIONS: See AMS 3894.
5. PREPARATION FOR DELIVERY: Shall be in accordance with AMS 3894 and the following:
- 5.1 Exterior package marking shall indicate storage temperature of "0 F (-18 C) maximum".
6. ACKNOWLEDGMENT: A vendor shall mention this specification number in all quotations and when acknowledging purchase orders.
7. REJECTIONS: Material not conforming to this specification or to authorized modifications will be subject to rejection.
8. NOTES: None.

SAENORM.COM : Click to view the full PDF of AMS 3894/1