

AEROSPACE
MATERIAL
SPECIFICATION

AMS 3898/2A
Superseding AMS 3898/2

Issued 6-15-75
Revised 1-1-85

INTERLEAF CARRIER MATERIAL, COMPOSITE TAPE
Polyethylene Film, Unperforated
0.0018 in. (0.046 mm)

1. SCOPE:

1.1 Form: This specification covers one type of polyethylene film in the form of rolls of sheeting or reels of unperforated tape of the width specified.

2. APPLICABLE DOCUMENTS: See AMS 3898.

3. TECHNICAL REQUIREMENTS:

3.1 Basic Specification: The complete requirements for procuring the product described herein shall consist of this document and the latest issue of the basic specification, AMS 3898.

3.2 Material: The carrier shall be polyethylene film.

3.2.1 Thickness: Shall be 0.0018 in. \pm 0.0003 (0.046 mm \pm 0.008).

3.2.2 Width: Shall be as ordered.

3.3 Properties: Shall be as follows:

3.3.1 Tensile Strength, min 25 lb per in. of width
(350 N/m of width)

3.3.2 Tear Strength, min 0.5 oz
(140 mN)

4. QUALITY ASSURANCE PROVISIONS: See AMS 3898.

5. PREPARATION FOR DELIVERY: See AMS 3898.

6. ACKNOWLEDGMENT: See AMS 3898.

SAE Technical Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

AMS documents are protected under United States and international copyright laws. Reproduction of these documents by any means is strictly prohibited without the written consent of the publisher.