



AEROSPACE MATERIAL SPECIFICATION	AMS3898™/8	REV. A
	Issued 1984-04 Revised 1994-02 Reaffirmed 2022-04 Superseding AMS3898/8	
Interleaf Carrier Material, Composite Tape/Broadgoods Kraft, Differentially Coated Paper, Unperforated 0.0038 inch ± 0.0004 (0.097 mm ± 0.010)		

RATIONALE

AMS3898/8A has been reaffirmed to comply with the SAE Five-Year Review policy.

1. SCOPE:

1.1 Form:

This specification covers a kraft paper, coated on both sides and with different release characteristics on each side (i.e., differentially coated), supplied in the form of rolls of sheeting or reels of unperforated tape of the width specified.

2. APPLICABLE DOCUMENTS:

See AMS 3898.

3. TECHNICAL REQUIREMENTS:

3.1 Basic Specification:

The complete requirements for procuring the product described herein shall consist of this document and the latest issue of the basic specification, AMS 3898.

3.2 Material:

(R) The carrier material shall be a latex-saturated kraft paper with a heat-cured silicone emulsion coating on each side. The coating on one side shall provide a controlled release from composite prepreg materials while the other side shall provide an easy release from these same composite prepreg materials, with no transfer of coating to the composite prepreg surface.

3.2.1 Thickness: Shall be 0.0038 inch ± 0.0004 (0.097 mm ± 0.010).

3.2.2 Width: Shall be as ordered.

SAE Executive Standards Committee Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2022 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
http://www.sae.org

SAE WEB ADDRESS:

For more information on this standard, visit
<https://www.sae.org/standards/content/AMS3898/8A/>