

CARBON FIBER TAPE AND SHEET
Polysulfone Resin Impregnated
C PS 170,000 (1170) Tensile, 16,000,000 (110) Modulus, 120 (250)

THIS REVISION CONTAINS ONLY EDITORIAL CHANGES.

1. SCOPE:

1.1 Form: This specification covers one type of thermoplastic, polysulfone resin-impregnated carbon fibers in the form of tape or sheet.

1.2 Application: Primarily for use in structural composites requiring high strength up to 120°C (250°F).

1.3 Classification: C 170,000 psi (1170 MPa) tensile strength, 16,000,000 psi (110 GPa) tensile modulus carbon fiber impregnated with polysulfone resin for service up to 120°C (250°F).

2. APPLICABLE DOCUMENTS: See AMS 3899.

3. TECHNICAL REQUIREMENTS:

3.1 Basic Specification: The complete requirements for producing the product described herein shall consist of this document and the latest issue of the basic specification, AMS 3899.

3.2 Material: The product shall be AMS 3892/1 high-tensile-strength carbon fibers impregnated with heat-reactive, thermoplastic, polysulfone resin formulated to meet the requirements specified herein.

3.2.1 Storage Life: The product shall meet the requirements of this specification when tested at any time up to one year from date of receipt by purchaser, provided it has been stored at room temperature in the original containers.

SAE Technical Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

AMS documents are protected under United States and international copyright laws. Reproduction of these documents by any means is strictly prohibited without the written consent of the publisher.

3.3 Properties: The product shall conform to the following requirements:

3.3.1 Resin Impregnated Fiber Tape and Sheet: Shall be as specified below; tests shall be performed on the as-supplied product and in accordance with test methods listed in the basic specification, AMS 3899.

3.3.1.1 Volatile Content by Weight, max: 5%

Test temperature: $260^{\circ}\text{C} + 5$ ($500^{\circ}\text{F} + 10$)

Test time: 30 min. \pm 5

3.3.1.2 Total Resin Solids Content by Weight: $34\% \pm 3$

3.3.1.3 Resin Flow by Weight, max: 4.0%

3.3.2 Molded Laminates: Shall be determined on specimens cut from a test panel prepared as specified in the basic specification and tested in accordance with the test methods specified therein.

3.3.2.1 Mechanical Properties: Shall be as specified in Table I.

3.3.2.2 Density: Shall be determined on each test panel used to determine mechanical properties; values shall be reported. Fiber density and resin density shall also be reported.

3.3.2.3 Void Content: Shall be not greater than 4%.

4. QUALITY ASSURANCE PROVISIONS: See AMS 3899.

5. PREPARATION FOR DELIVERY: See AMS 3899.

6. ACKNOWLEDGMENT: See AMS 3899.

7. REJECTIONS: See AMS 3899.

8. NOTES: See AMS 3899.