



400 Commonwealth Drive, Warrendale, PA 15096-0001

AEROSPACE MATERIAL SPECIFICATION



AMS 3901/5B

Issued 1 JUN 1974
Revised 1 OCT 1992
Superseding AMS 3901/5A

Submitted for recognition as an American National Standard

**ROVING, ORGANIC FIBER (PARA-ARAMID), HIGH MODULUS
OY 450 (3103)/23.0 Tensile Strength, 17.5 (121)/780 Tensile Modulus
7100 Denier, 0.6% Finish**

1. SCOPE:

1.1 Form:

This specification covers one type of organic fiber in the form of roving. The product shall be formed as five ends of 1420 denier yarn (AMS 3901/4) collected into an approximately parallel arrangement without twist.

1.2 Classification:

Organic 7100 denier roving with 450 ksi (3103 MPa) or 23.0 g/d tensile strength and 17.5 Msi (121 GPa) or 780 g/d tensile modulus for use in filament winding requiring high tensile strength and high modulus of elasticity in tension.

2. APPLICABLE DOCUMENTS:

See AMS 3901.

3. TECHNICAL REQUIREMENTS:

3.1 Basic Specification:

The complete requirements for procuring the organic roving described herein shall consist of this document and the latest issue of the basic specification.

3.2 Properties:

Shall be as shown in Table 1; no individual package, based on the average of five determinations, shall have less than 90% of the lot minimum values specified in 3.2.1 and 3.2.2.

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

AMS 3901/5B

SAE

AMS 3901/5B

TABLE 1 - Properties

Paragraph	Requirement	Requirement Dry Twisted Roving	Requirement Impregnated Strand	Test Method
3.2.1	Tensile Strength, minimum	21 g/d	450 ksi (3103 MPa)	4.5.1 or 4.5.2 of AMS 3901
3.2.2	Modulus of Elasticity, minimum	740 g/d	17.5 Msi (121 GPa)	4.5.1 or 4.5.3 of AMS 3901
3.2.3	Denier (R)	7100 ± 325	7100 ± 325	4.5.4 of AMS 3901
3.2.4	Fiber Finish, by weight	0.6% ± 0.6	0.6% ± 0.6	4.5.5 of AMS 3901
3.2.5	Fiber Density	0.052 pound mass per cubic inch ± 0.001 (1.44 grams/cm ³ ± 0.03)	0.052 pound mass per cubic inch ± 0.001 (1.44 grams/cm ³ ± 0.03)	
3.2.6	Catenary	1 inch per 50 feet (25.4 mm/15m)	1 inch per 50 feet (25.4 mm/15m)	4.5.6 of AMS 3901

3.3 Splicing:

The number of spliced ends within a ball of roving shall not exceed two times the roving weight of the ball in pounds (four times the roving weight of the ball in kilograms). There shall be no more than one spliced end in the same perpendicular plane for roving. Distance between splices shall not be less than 200 yards (183 m).

4. QUALITY ASSURANCE PROVISIONS:

See AMS 3901.

5. PREPARATION FOR DELIVERY:

See AMS 3901.

6. ACKNOWLEDGMENT:

See AMS 3901.

7. REJECTIONS:

See AMS 3901.