



# AEROSPACE MATERIAL SPECIFICATION

Society of Automotive Engineers, Inc.  
400 COMMONWEALTH DRIVE, WARRENDALE, PA. 15096

## AMS 3906/4

Issued 6-15-75  
Revised

### GLASS NON-WOVEN FIBER TAPE AND FLAT SHEET Epoxy Resin Impregnated, For Hand and Machine Layup GL-III-26 - 300 (149)

#### 1. SCOPE:

- 1.1 Form: This specification covers one type of epoxy-resin-impregnated, non-woven, glass fiber in the form of tape for hand or machine layup and of flat sheet.
- 1.2 Application: Primarily for use in structural composites requiring high strength at temperatures up to 300<sup>o</sup>F (149<sup>o</sup>C).
- 1.3 Classification: GL-III-26-300 (149), non-woven "S" glass fiber impregnated with epoxy resin for service at temperatures from -67<sup>o</sup> to 300<sup>o</sup>F (-55<sup>o</sup> to 149<sup>o</sup>C).

2. APPLICABLE DOCUMENTS: Shall be as shown in AMS 3906.

#### 3. TECHNICAL REQUIREMENTS:

- 3.1 Basic Specification: The complete requirements for procuring the product described herein shall consist of this document and the latest issue of the basic specification, AMS 3906.
- 3.2 Product: Shall be a non-woven, high tensile strength, "S" glass fiber meeting the requirements of MIL-R-60346 Type III, impregnated with epoxy resin formulated to meet the requirements specified herein.
- 3.2.1 Storage Life: The product shall meet the requirements of this specification when tested at any time up to 12 months from the date of receipt of the product by the purchaser provided it has been stored in the original sealed container at a maximum temperature of 40<sup>o</sup>F (4<sup>o</sup>C).
- 3.2.2 Working Life: The product shall meet the requirements of this specification when tested after exposure to a relative humidity not higher than 70% and a temperature not higher than 80<sup>o</sup>F (27<sup>o</sup>C) for a continuous period of not less than 1 month.
- 3.3 Properties of Uncured Product: Shall be as follows; tests shall be performed on the product as-received, after warming to above the dew point prior to sampling, in accordance with test methods specified in the basic specification.

- 3.3.1 Volatile Content by weight, max 2%  
Test Temperature: 325<sup>o</sup>F ± 10 (162.8<sup>o</sup>C ± 5.6)  
Test Time: 15 min. + 1
- 3.3.2 Total nonfiber content by weight 26% ± 3
- 3.3.3 Resin Flow by weight 9% ± 6  
Test Temperature: 325<sup>o</sup>F ± 10 (162.8<sup>o</sup>C ± 5.6)

SAE Technical Board rules provide that: "All technical reports, including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against infringement of patents."

- 3.3.4 Gel Time 3 min.  $\pm 2$   
Test Temperature:  $325^{\circ}\text{F} \pm 10$  ( $162.8^{\circ}\text{C} \pm 5.6$ )
- 3.3.5 Tack Shall adhere for at least 30 min.
- 3.3.6 Total weight per unit area shall be  $336 \text{ g/sq yd} \pm 21$  ( $402 \text{ g/m}^2 \pm 25$ ).
- 3.3.7 Ply thickness, uncured shall be  $0.009 \text{ in.} \pm 0.002$  ( $0.23 \text{ mm} \pm 0.05$ ).
- 3.4 Properties of Cured Laminate: Shall be as follows, determined on specimens cut from a test panel prepared and tested as specified in the basic specification.
- 3.4.1 Mechanical Properties: Shall be as specified in Table I.
- 3.4.2 Density: Shall be determined on the test laminate used to determine mechanical properties; values for each test laminate shall be reported. Cured resin density shall also be reported.
- 3.4.3 Void Content: Shall be not greater than 4%.
- 3.4.4 Fiber Volume: Shall be determined on the test laminate used to determine mechanical properties; values for each laminate shall be reported. The fiber density to be used shall be  $2.485 \text{ g/cm}^3$ .
4. QUALITY ASSURANCE PROVISIONS: See AMS 3906.
5. PREPARATION FOR DELIVERY: Shall be in accordance with AMS 3906 and the following:
- 5.1 Exterior package marking shall indicate storage temperature of  $40^{\circ}\text{F}$  ( $4^{\circ}\text{C}$ ) maximum.
6. ACKNOWLEDGMENT: A vendor shall mention this specification number in all quotations and when acknowledging purchase orders.
7. REJECTIONS: Material not conforming to this specification or to authorized modifications will be subject to rejection.
8. NOTES: None.