

CLOTH, PARACHUTE, ARAMID
2.0 oz per sq yd (68 g/m²), 230 lb per in. (40,275 N/m)
and 220 lb per in. (38,525 N/m)

1. SCOPE:

1.1 Form: This specification covers one weight and strength of intermediate modulus aramid cloth.

1.2 Application: Primarily for use in construction of parachutes.

1.3 Classification: 2.0 oz per sq yd (68 g/m²) cloth with breaking strength not lower than 230 lb per in. (40,275 N/m) in the warp direction and 220 lb per in. (38,525 N/m) in the filling direction.

2. APPLICABLE DOCUMENTS: See AMS 3909.

3. TECHNICAL REQUIREMENTS:

3.1 Basic Specification: The complete requirements for procuring the cloth described herein shall consist of this document and the latest issue of the basic specification, AMS 3909.

3.3 Properties: Shall conform to the requirements of Table I and the following:

3.2.1 Weave: Shall be a plain weave.

3.2.2 Color: Shall be as specified by purchaser.

3.2.3 Width: Shall be 36.5 in. \pm 0.5 (925 mm \pm 12).

3.2.4 Age: Shall be not more than 2 yr from date of manufacture of the yarn to date of delivery of the cloth.

4. QUALITY ASSURANCE PROVISIONS: See AMS 3909.

5. PREPARATION FOR DELIVERY: See AMS 3909.

6. ACKNOWLEDGMENT: See AMS 3909.

SAE Technical Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

AMS documents are protected under United States and international copyright laws. Reproduction of these documents by any means is strictly prohibited without the written consent of the publisher.