

**AEROSPACE
MATERIAL
SPECIFICATION**

Submitted for recognition as an American National Standard

SAE AMS 4001F

Issued 10-1-43
Revised 10-1-86

Superseding AMS 4001E

ALUMINUM SHEET AND PLATE
0.12 Cu (1100-0)
Annealed

UNS A91100

1. SCOPE:

1.1 Form: This specification covers aluminum in the form of sheet and plate.

1.2 Application: Primarily for severely formed parts and for parts requiring welding.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

2.1 SAE Publications: Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

AMS 2202 - Tolerances, Aluminum Alloy and Magnesium Alloy Sheet and Plate

MAM 2202 - Tolerances, Metric, Aluminum Alloy and Magnesium Alloy Sheet and Plate

AMS 2350 - Standards and Test Methods

AMS 2355 - Quality Assurance Sampling and Testing of Aluminum Alloys and Magnesium Alloys, Wrought Products (Except Forging Stock) and Flash Welded Rings

MAM 2355 - Quality Assurance Sampling and Testing of Aluminum Alloys and Magnesium Alloys, Wrought Products (Except Forging Stock) and Flash Welded Rings, Metric (SI) Units

2.2 U.S. Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

SAE Technical Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

AMS documents are protected under United States and international copyright laws. Reproduction of these documents by any means is strictly prohibited without the written consent of the publisher.

2.2.1 Military Standards:

MIL-STD-649 - Aluminum and Magnesium Products, Preparation for Shipment and Storage

3. TECHNICAL REQUIREMENTS:

3.1 Composition: Shall conform to the following percentages by weight, determined in accordance with AMS 2355 or MAM 2355:

	min	max
Aluminum	99.00	--
Copper	0.05	0.20
Iron + Silicon	--	0.95
Zinc	--	0.10
Manganese	--	0.05
Other Impurities, each	--	0.05
Other Impurities, total	--	0.15

3.2 Condition: Annealed.

3.3 Properties: The product shall conform to the following requirements, determined in accordance with AMS 2355 or MAM 2355:

3.3.1 Tensile Properties: Shall be as shown in Table I and 3.3.1.1.

TABLE I

Nominal Thickness Inches	Tensile Strength psi	Yield Strength at 0.2% Offset psi, min	Elongation in 2 in. or 4D %, min
0.006 to 0.019, incl	11,000 - 15,500	3,500	15
Over 0.019 to 0.031, incl	11,000 - 15,500	3,500	20
Over 0.031 to 0.050, incl	11,000 - 15,500	3,500	25
Over 0.050 to 0.249, incl	11,000 - 15,500	3,500	30
Over 0.249 to 3.000, incl	11,000 - 15,500	3,500	28

TABLE I (SI)

Nominal Thickness Millimetres	Tensile Strength MPa	Yield Strength at 0.2% Offset psi, min	Elongation in 50 mm or 4D %, min
0.15 to 0.48, incl	75 - 105	25	15
Over 0.48 to 0.78, incl	75 - 105	25	20
Over 0.78 to 1.25, incl	75 - 105	25	25
Over 1.25 to 6.25, incl	75 - 105	25	30
Over 6.25 to 75.00, incl	75 - 105	25	28

- 3.3.1.1 Tensile property requirements for plate over 3.000 in. (75.00 mm) in nominal thickness shall be as agreed upon by purchaser and vendor.
- 3.3.2 Bending: Product 0.249 in. (6.25 mm) and under in nominal thickness shall withstand, without cracking, bending at room temperature flat on itself with axis of bend parallel to the direction of rolling.
- 3.3.2.1 Bending requirements for plate over 0.249 in. (6.25 mm) in nominal thickness shall be as agreed upon by purchaser and vendor.
- 3.4 Quality: The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the product.
- 3.5 Tolerances: Shall conform to all applicable requirements of AMS 2202 or MAM 2202.
4. QUALITY ASSURANCE PROVISIONS:
- 4.1 Responsibility for Inspection: The vendor of the product shall supply all \emptyset samples for vendor's tests and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.4. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to the requirements of this specification.
- 4.2 Classification of Tests:
- 4.2.1 Acceptance Tests: Tests to determine conformance to requirements for \emptyset composition (3.1), tensile properties (3.3.1), and tolerances (3.5) are classified as acceptance tests and shall be performed on each lot.
- 4.2.2 Periodic Tests: Tests to determine conformance to requirements for \emptyset bending (3.3.2) are classified as periodic tests and shall be performed at a frequency selected by the vendor unless frequency of testing is specified by purchaser.
- 4.3 Sampling: Shall be in accordance with AMS 2355 or MAM 2355.
- 4.4 Reports:
- 4.4.1 The vendor of the product shall furnish with each shipment a report stating that the product conforms to the chemical composition and other technical requirements of this specification. This report shall include the purchase order number, AMS 4001F, size, and quantity.

4.4.2 The vendor of finished or semi-finished parts shall furnish with each shipment a report showing the purchase order number, AMS 4001F, contractor or other direct supplier of material, part number, and quantity. When material for making parts are produced or purchased by the parts vendor, that vendor shall inspect each lot of material to determine conformance to the requirements of this specification and shall include in the report either a statement that the material conforms or copies of laboratory reports showing the results of tests to determine conformance.

4.5 Resampling and Retesting: Shall be in accordance with AMS 2355 or MAM 2355.

5. PREPARATION FOR DELIVERY:

5.1 Identification: Each sheet and plate shall be marked on one face, in the respective location indicated below, with the alloy number and temper, AMS 4001 or applicable Federal specification designation, manufacturer's identification, and nominal thickness. The characters shall be of such size as to be legible, shall be applied using a suitable marking fluid, and shall be sufficiently stable to withstand normal handling. The markings shall have no deleterious effect on the product or its performance.

5.1.1 Flat Sheet and Plate Under 6 In. (150 mm) Wide: Shall be marked in one or more lengthwise rows of characters recurring at intervals not greater than 3 ft (900 mm).

5.1.2 Flat Sheet and Plate 0.375 In. (9.50 mm) and Under Thick, 6 - 60 In. (150 - 1500 mm), Incl, Wide, and 36 - 200 In. (900 - 5000 mm), Incl, Long: Shall be marked in lengthwise rows of characters recurring at intervals not greater than 3 ft (900 mm), the rows being spaced approximately 6 in. (150 mm) on centers across the width and staggered. Every third row shall show the manufacturer's identification and nominal thickness. The other rows shall show the alloy number and temper and AMS 4001 or applicable Federal specification designation.

5.1.3 Flat Sheet and Plate Over 0.375 In. (9.50 mm) Thick, or Over 60 In. (1500 mm) Wide, or Over 200 In. (5000 mm) Long: Shall be marked as in 5.1.2 or, at vendor's discretion, shall be marked in one or two rows of characters recurring at intervals not greater than 3 ft (900 mm) and running around the periphery of the piece. If one row is used, it shall show all information of 5.1. If two rows are used, one row shall show the alloy number and temper and AMS 4001 or applicable Federal specification designation; the second row shall show the manufacturer's identification and nominal thickness.

5.1.3.1 If peripheral marking is applied to the full piece as produced but partial sheets or plates are supplied, an arrow shall also be applied near one corner indicating the direction of rolling.