

AEROSPACE  
MATERIAL  
SPECIFICATION

AMS 4006F

Superseding AMS 4006E

Issued 11-1-41  
Revised 1-1-83

UNS A93003

ALUMINUM ALLOY SHEET AND PLATE  
1.25Mn - 0.12Cu (3003-0)  
Annealed

1. SCOPE:

1.1 Form: This specification covers an aluminum alloy in the form of sheet and plate.

1.2 Application: Primarily for parts fabricated by spinning or severe forming where good weldability is required.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications (AMS) shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

2.1 SAE Publications: Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

AMS 2202 - Tolerances, Aluminum Alloy and Magnesium Alloy Sheet and Plate

AMS 2350 - Standards and Test Methods

AMS 2355 - Quality Assurance Sampling and Testing of Aluminum-Base and Magnesium-Base Alloys, Wrought Products (Except Forgings and Forging Stock) and Flash Welded Rings

2.2 U.S. Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

2.2.1 Military Specifications:

MIL-H-6088 - Heat Treatment of Aluminum Alloys

2.2.2 Military Standards:

MIL-STD-649 - Aluminum and Magnesium Products, Preparation for Shipment and Storage

SAE Technical Board rules provide that: "All technical reports, including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade or their use by governmental agencies is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."

# AMS 4006F

## 3. TECHNICAL REQUIREMENTS:

3.1 Composition: Shall conform to the following percentages by weight, determined in accordance with AMS 2355:

	min	max
Manganese	1.0	1.5
Copper	0.05	0.20
Iron	--	0.7
Silicon	--	0.6
Zinc	--	0.10
Other Impurities, each	--	0.05
Other Impurities, total	--	0.15
Aluminum	remainder	

3.2 Condition: Annealed in accordance with MIL-H-6088.

Ø

3.3 Properties: The product shall conform to the following requirements, determined in accordance with AMS 2355:

3.3.1 Tensile Properties: Shall be as specified in Table I and 3.3.1.1.

TABLE I

Nominal Thickness Inches	Tensile Strength psi	Elongation in 2 in. or 4D %, min
0.006 to 0.007, incl	14,000 - 19,000	14
Over 0.007 to 0.012, incl	14,000 - 19,000	18
Over 0.012 to 0.031, incl	14,000 - 19,000	20
Over 0.031 to 0.050, incl	14,000 - 19,000	23
Over 0.050 to 0.249, incl	14,000 - 19,000	25
Over 0.249 to 3.000, incl	14,000 - 19,000	23

TABLE I (SI)

Nominal Thickness Millimetres	Tensile Strength MPa	Elongation in 50 mm or 4D %, min
0.15 to 0.18, incl	95 - 130	14
Over 0.18 to 0.30, incl	95 - 130	18
Over 0.30 to 0.75, incl	95 - 130	20
Over 0.75 to 1.25, incl	95 - 130	23
Over 1.25 to 6.25, incl	95 - 130	25
Over 6.25 to 75.00, incl	95 - 130	23

- 3.3.1.1 Tensile properties of plate over 3.000 in. (75.00 mm) in nominal thickness shall be as agreed upon by purchaser and vendor.
- 3.3.2 Bending: Product 0.249 in. (6.25 mm) and under in nominal thickness shall withstand, without cracking, bending at room temperature flat on itself with axis of bend parallel to the direction of rolling.
- 3.3.2.1 Bending requirements for plate over 0.249 in. (6.25 mm) in nominal thickness shall be as agreed upon by purchaser and vendor.
- 3.4 Quality: The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from internal and external imperfections detrimental to usage of the product.
- 3.5 Tolerances: Unless otherwise specified, tolerances shall conform to all applicable requirements of AMS 2202.
4. QUALITY ASSURANCE PROVISIONS:
- 4.1 Responsibility for Inspection: The vendor of the product shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.4. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to the requirements of this specification.
- 4.2 Classification of Tests:
- 4.2.1 Acceptance Tests: Tests to determine conformance to requirements for composition (3.1), tensile properties (3.3.1), and tolerances (3.5) are classified as acceptance tests and shall be performed on each lot.
- 4.2.2 Periodic Tests: Tests to determine conformance to requirements for bending (3.3.2) are classified as periodic tests and shall be performed at a frequency selected by the vendor unless frequency of testing is specified by purchaser.
- 4.3 Sampling: Shall be in accordance with AMS 2355.
- 4.4 Reports:
- 4.4.1 The vendor of the product shall furnish with each shipment three copies of a report stating that the product conforms to the chemical composition and other technical requirements of this specification. This report shall include the purchase order number, AMS 4006F, size, and quantity.

# AMS 4006F

4.4.2 The vendor of finished or semi-finished parts shall furnish with each shipment three copies of a report showing the purchase order number, AMS 4006F, contractor or other direct supplier of material, part number, and quantity. When material for making parts is produced or purchased by the parts vendor, that vendor shall inspect each lot of material to determine conformance to the requirements of this specification and shall include in the report either a statement that the material conforms or copies of laboratory reports showing the results of tests to determine conformance.

4.5 Resampling and Retesting: Shall be in accordance with AMS 2355.

## 5. PREPARATION FOR DELIVERY:

5.1 Identification: Each sheet and plate shall be marked on one face, in the respective location indicated below, with the alloy number and temper, AMS 4006 or applicable Federal or Military specification designation, manufacturer's identification, and nominal thickness. The characters shall be of such size as to be legible, shall be applied using a suitable marking fluid, and shall be sufficiently stable to withstand normal handling. The markings shall have no deleterious effect on the product or its performance.

5.1.1 Flat Sheet and Plate Under 6 In. (150 mm) Wide: Shall be marked in one or more lengthwise rows of characters recurring at intervals not greater than 3 ft (900 mm).

5.1.2 Flat Sheet and Plate 0.375 In. (9.50 mm) and Under Thick, 6 - 60 In. (150 - 1500 mm), Incl, Wide, and 36 - 200 In. (900 - 5000 mm), Incl, Long: Shall be marked in lengthwise rows of characters recurring at intervals not greater than 3 ft (900 mm), the rows being spaced approximately 6 in. (150 mm) on centers across the width and staggered. Every third row shall show the manufacturer's identification and nominal thickness. The other rows shall show the alloy number and temper and AMS 4006 or applicable Federal or Military specification designation.

5.1.3 Flat Sheet and Plate over 0.375 In. (9.50 mm) Thick, or Over 60 In. (1500 mm) Wide, or Over 200 In. (5000 mm) Long: Shall be marked as in 5.1.2 or, at vendor's discretion, shall be marked in one or two rows of characters recurring at intervals not greater than 3 ft (900 mm) and running around the periphery of the piece. If one row is used, it shall show all information of 5.1. If two rows are used, one row shall show the alloy number and temper and AMS 4006 or applicable Federal or Military specification designation; the second row shall show the manufacturer's identification and nominal thickness.

5.1.3.1 If peripheral marking is applied to the full piece as produced but partial sheets or plates are supplied, an arrow shall also be applied near one corner indicating the direction of rolling.