

AEROSPACE MATERIAL SPECIFICATION

Issued NOV 1941
Revised FEB 2001

Superseding AMS 4008H

Aluminum Alloy, Sheet and Plate
1.25Mn - 0.12Cu (3003-H14)
Strain Hardened

UNS A93003

1. SCOPE:

1.1 Form:

This specification covers an aluminum alloy in the form of sheet and plate.

1.2 Application:

These products have been used typically for parts requiring moderately severe forming or spinning, but usage is not limited to such applications.

2. APPLICABLE DOCUMENTS:

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been canceled and no superseding document has been specified, the last published issue of that document shall apply.

2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

AMS 2355 Quality Assurance Sampling and Testing, Aluminum Alloys and Magnesium Alloys, Wrought Products, Except Forging Stock, and Rolled, Forged, or Flash Welded Rings
MAM 2355 Quality Assurance Sampling and Testing, Aluminum Alloys and Magnesium Alloys, Wrought Products, Except Forging Stock, and Rolled, Forged, or Flash Welded Rings, Metric (SI) Units

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright 2001 Society of Automotive Engineers, Inc.
All rights reserved.

Printed in U.S.A.

QUESTIONS REGARDING THIS DOCUMENT:
TO PLACE A DOCUMENT ORDER:
SAE WEB ADDRESS:

(724) 772-7161
(724) 776-4970
<http://www.sae.org>

FAX: (724) 776-0243
FAX: (724) 776-0790

2.2 ASTM Publications:

Available from ASTM, 100 Barr Harbor Drive, West Conshohocken, PA 19428-2959.

ASTM B 660 Packaging/Packing of Aluminum and Magnesium Products
 ASTM B 666/B 666M Identification Marking of Aluminum and Magnesium Products

2.3 ANSI Publications:

Available from ANSI, 11 West 42nd Street, New York, NY 10036-8002.

ANSI H35.2 Dimensional Tolerances for Aluminum Mill Products
 ANSI H35.2M Dimensional Tolerances for Aluminum Mill Products (Metric)

3. TECHNICAL REQUIREMENTS:

3.1 Composition:

Shall conform to the percentages by weight shown in Table 1, determined in accordance with AMS 2355 or MAM 2355.

TABLE 1 - Composition

Element	min	max
Silicon	--	0.6
Iron	--	0.7
Copper	0.05	0.20
Manganese	1.0	1.50
Zinc	--	0.10
Other Elements, each	--	0.05
Other Elements, total	--	0.15
Aluminum	remainder	

3.2 Condition:

Strain hardened to the H14 condition.

3.3 Properties:

The product shall conform to the following requirements, determined in accordance with AMS 2355 or MAM 2355 on the mill produced size.

3.3.1 Tensile Properties: Shall be as specified in Table 2.

TABLE 2A - Tensile Properties, Inch/Pound Units

Nominal Thickness Inch	Tensile Strength ksi	Yield Strength at 0.2% Offset ksi, min	Elongation in 2 Inches or 4D %, min
0.009 to 0.012, incl	20.0 to 26.0	17.0	1
Over 0.012 to 0.019, incl	20.0 to 26.0	17.0	2
Over 0.019 to 0.031, incl	20.0 to 26.0	17.0	3
Over 0.031 to 0.050, incl	20.0 to 26.0	17.0	4
Over 0.050 to 0.113, incl	20.0 to 26.0	17.0	5
Over 0.113 to 0.161, incl	20.0 to 26.0	17.0	6
Over 0.161 to 0.249, incl	20.0 to 26.0	17.0	7
Over 0.249 to 0.499, incl	20.0 to 26.0	17.0	8
Over 0.499 to 1.000, incl	20.0 to 26.0	17.0	10

TABLE 2B - Tensile Properties, SI Units

Nominal Thickness Millimeters	Tensile Strength MPa	Yield Strength at 0.2% Offset MPa, min	Elongation in 50.8 mm or 4D %, min
0.23 to 0.30, incl	138 to 179	117	1
Over 0.30 to 0.48, incl	138 to 179	117	2
Over 0.48 to 0.79, incl	138 to 179	117	3
Over 0.79 to 1.27, incl	138 to 179	117	4
Over 1.27 to 2.87, incl	138 to 179	117	5
Over 2.87 to 4.09, incl	138 to 179	117	6
Over 4.09 to 6.32, incl	138 to 179	117	7
Over 6.32 to 12.67, incl	138 to 179	117	8
Over 12.67 to 25.40, incl	138 to 179	117	10

- 3.3.2 Bending: Product shall withstand, without cracking, bending at room temperature through an angle of 180 degrees around a diameter equal to the bend factor shown in Table 3 times the nominal thickness of the product with axis of bend parallel to the direction of rolling.

TABLE 3 - Bending Parameters

Nominal Thickness Inch	Nominal Thickness Millimeters	Bend Factor
0.009 to 0.113, incl	0.23 to 2.87, incl	0
Over 0.113 to 0.249, incl	Over 2.87 to 6.32, incl	2

3.4 Quality:

The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the product.

3.5 Tolerances:

Shall conform to all applicable requirements of ANSI H35.2 or ANSI H35.2M.

4. QUALITY ASSURANCE PROVISIONS:**4.1 Responsibility for Inspection:**

The vendor of the product shall supply all samples for vendor's tests and shall be responsible for the performance of all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to the specified requirements.

4.2 Classification of Tests:

4.2.1 Acceptance Tests: Composition (3.1), tensile properties (3.3.1), and tolerances (3.5) are acceptance tests and, except for composition, shall be performed on each lot.

4.2.2 Periodic Tests: Bending (3.3.2) is a periodic test and shall be performed at a frequency selected by the vendor unless frequency of testing is specified by purchaser.

4.3 Sampling and Testing:

Shall be in accordance with AMS 2355 or MAM 2355.

4.4 Reports:

The vendor of the product shall furnish with each shipment a report stating that the product conforms to the chemical composition and tolerances, and showing the numerical results of tests on each inspection lot to determine conformance to the other acceptance test requirements. This report shall include the purchase order number, inspection lot number(s), AMS 4008J, size, and quantity. The report shall also identify the producer, the product form, and size of the mill product.

4.5 Resampling and Retesting:

Shall be in accordance with AMS 2355 or MAM 2355.

5. PREPARATION FOR DELIVERY:**5.1 Identification:**

Shall be in accordance with ASTM B 666/B 666M.