

Submitted for recognition as an American National Standard

**ALUMINUM SHEET, LAMINATED
Edge Bonded**

1. SCOPE:

1.1 Form: This specification covers an aluminum or aluminum alloy in the form of sheet, laminated and edge bonded.

1.2 Application: Primarily for shims of special shapes in which thickness is to be adjusted by removal of laminations as required.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

2.1 SAE Publications: Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

AMS 2350 - Standards and Test Methods

AMS 2355 - Quality Assurance Sampling and Testing of Aluminum Alloys and Magnesium Alloys, Wrought Products (Except Forging Stock) and Flash Welded Rings

MAM 2355 - Quality Assurance Sampling and Testing of Aluminum Alloys and Magnesium Alloys, Wrought Products (Except Forging Stock) and Flash Welded Rings

AMS 4041 - Aluminum Alloy Sheet and Plate, Alclad, 4.4Cu - 1.5Mg - 0.60Mn (Alclad 2024 and 1-1/2% Alclad 2024-T3 Flat Sheet; 1-1/2% Alclad 2024-T351 Plate)

2.2 U.S. Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

SAE Technical Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

2.2.1 Military Standards:

MIL-STD-649 - Aluminum and Magnesium Products, Preparation for Shipment and Storage

3. TECHNICAL REQUIREMENTS:

3.1 Composition:

3.1.1 Laminations: Shall be 1100, 1145, 3003, or 5052 aluminum alloy foil. The choice of alloy shall be at the discretion of the producer.

3.1.2 Solid Base: Shall be AMS 4041 aluminum alloy sheet.

3.1.3 Adhesive: Shall be a composition which will meet the fabrication and quality requirements of 3.2 and 3.3.

3.2 Fabrication:

3.2.1 Sheet shall be fabricated from hard or extra-hard laminations, in combination with a solid base when required, pre-cut to the desired shape; stacked to the desired thickness, and bonded on the outside edge with adhesive such that individual laminations may be peeled for adjustment of shim thickness.

3.2.1.1 Laminations shall be bonded together in such a manner that normal handling shall not cause separation.

3.2.2 Laminations shall be 0.003 in. \pm 0.0003 (0.08 mm \pm 0.008) thick unless 0.002 in. \pm 0.0002 (0.05 mm \pm 0.005) laminations are specified or required to produce the nominal laminate thickness.

3.2.3 Sizes: The product shall be of the following thicknesses and combinations of laminations and solid base:

Nominal Thickness of Shim Stock		All Laminated	Half Solid, Half Laminated	Three-Quarters Solid, One-Quarter Laminated
Inch	mm			
0.006	0.15	X		
0.008	0.20	X		
0.010	0.25	X		
0.016	0.40	X		
0.020	0.50	X		
0.032	0.80	X		
0.047	1.18	X		
0.062	1.55	X	X	
0.094	2.35	X	X	
0.125	3.00	X	X	X
0.190	4.75	X	X	X

3.3 Quality: Sheet, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the sheet.

3.4 Tolerances: Shall be as specified in Table I.

TABLE I

Nominal Total Thickness Inch	Tolerance, Inch	
	plus	minus
Up to 0.008, incl	0.001	0.0005
Over 0.008 to 0.010, incl	0.0015	0.0005
Over 0.010 to 0.016, incl	0.0015	0.001
Over 0.016 to 0.021, incl	0.002	0.001
Over 0.021 to 0.033, incl	0.003	0.002
Over 0.033 to 0.048, incl	0.005	0.002
Over 0.048 to 0.063, incl	0.006	0.002
Over 0.063 to 0.080, incl	0.007	0.002
Over 0.080 to 0.094, incl	0.009	0.003
Over 0.094 to 0.109, incl	0.010	0.003
Over 0.109 to 0.125, incl	0.012	0.003
Over 0.125 to 0.156, incl	0.015	0.003
Over 0.156 to 0.187, incl	0.018	0.003
Over 0.187 to 0.190, incl	0.018	0.005

TABLE I (SI)

Nominal Total Thickness Millimetres	Tolerance, Millimetre	
	plus	minus
Up to 0.20, incl	0.03	0.012
Over 0.20 to 0.25, incl	0.038	0.012
Over 0.25 to 0.40, incl	0.038	0.02
Over 0.40 to 0.52, incl	0.05	0.02
Over 0.52 to 0.82, incl	0.08	0.05
Over 0.82 to 1.20, incl	0.12	0.05
Over 1.20 to 1.60, incl	0.15	0.05
Over 1.60 to 2.00, incl	0.18	0.05
Over 2.00 to 2.35, incl	0.22	0.08
Over 2.35 to 2.75, incl	0.25	0.08
Over 2.75 to 3.00, incl	0.30	0.08
Over 3.00 to 3.90, incl	0.38	0.08
Over 3.90 to 4.70, incl	0.45	0.08
Over 4.70 to 4.75, incl	0.45	0.12

4. QUALITY ASSURANCE PROVISIONS:

- 4.1 Responsibility for Inspection: The vendor of sheet shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.4. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the sheet conforms to the requirements of this specification.
- 4.2 Classification of Tests: Tests to determine conformance to all technical requirements of this specification are classified as acceptance tests and shall be performed on each lot.
- 4.3 Sampling: Shall be in accordance with AMS 2355 or MAM 2355.
- 4.4 Reports:
- 4.4.1 The vendor of sheet shall furnish with each shipment a report stating that the sheet conforms to the chemical composition and other technical requirements of this specification. This report shall include the purchase order number, AMS 4012E, shim stock thickness, foil thickness, percentage of total thickness which is laminated, size, and quantity.
- 4.4.2 The vendor of finished or semi-finished parts shall furnish with each shipment a report showing the purchase order number, AMS 4012E, contractor or other direct supplier of sheet, part number, and quantity. When sheet for making parts is produced or purchased by the parts vendor that vendor shall inspect each lot of sheet to determine conformance to the requirements of this specification and shall include in the report either a statement that the sheet conforms or copies of laboratory reports showing the results of tests to determine conformance.
- 4.5 Resampling and Retesting: Shall be in accordance with AMS 2355 or MAM 2355.
5. PREPARATION FOR DELIVERY:
- 5.1 Identification: Each sheet shall be marked near one end with AMS 4012E, manufacturer's identification, nominal thickness, thickness of each lamination, and percentage of total thickness which is laminated.
- 5.2 Packaging:
- 5.2.1 Sheet shall be prepared for shipment in accordance with commercial practice and in compliance with applicable rules and regulations pertaining to the handling, packaging, and transportation of the sheet to ensure carrier acceptance and safe delivery. Packaging shall conform to carrier rules and regulations applicable to the mode of transportation.
- 5.2.2 For direct U.S. Military procurement, packaging shall be in accordance with MIL-STD-649, Level A or Level C, as specified in the request for procurement. Commercial packaging as in 5.2.1 will be acceptable if it meets the requirements of Level C.
6. ACKNOWLEDGMENT: A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.