



<b>AEROSPACE MATERIAL SPECIFICATION</b>	<b>AMS4015™</b>	<b>REV. N</b>
	Issued 1939-12 Reaffirmed 2017-11 Revised 2023-06  Superseding AMS4015M	
Aluminum Alloy, Sheet and Plate 2.5Mg - 0.25Cr (5052-O) Annealed (Composition similar to UNS A95052)		

### RATIONALE

AMS4015N results from a Five-Year Review and update of this specification with changes to update wording to prohibit unauthorized exceptions (see 3.3.1.1, 3.6, and 8.3) and Applicable Documents (see Section 2), and to relocate Definitions (see 2.4).

#### 1. SCOPE

##### 1.1 Form

This specification covers an aluminum alloy in the form of sheet and plate 0.006 to 3.000 inches (0.15 to 76.20 mm), inclusive, in nominal thickness (see 8.5).

##### 1.2 Application

These products have been used typically for formed parts requiring moderate strength and good corrosion resistance and where welding may be required in fabrication, but usage is not limited to such applications.

#### 2. APPLICABLE DOCUMENTS

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

##### 2.1 SAE Publications

Available from SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001, Tel: 877-606-7323 (inside USA and Canada) or +1 724-776-4970 (outside USA), [www.sae.org](http://www.sae.org).

AMS2355 Quality Assurance, Sampling and Testing, Aluminum Alloys and Magnesium Alloy, Wrought Products (Except Forging Stock), and Rolled, Forged, or Flash Welded Rings

AMS2772 Heat Treatment of Aluminum Alloy Raw Materials

AS7766 Terms Used in Aerospace Metals Specifications

SAE Executive Standards Committee Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2023 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

**TO PLACE A DOCUMENT ORDER:** Tel: 877-606-7323 (inside USA and Canada)  
Tel: +1 724-776-4970 (outside USA)  
Fax: 724-776-0790  
Email: [CustomerService@sae.org](mailto:CustomerService@sae.org)  
<http://www.sae.org>

SAE WEB ADDRESS:

For more information on this standard, visit  
<https://www.sae.org/standards/content/AMS4015N/>

## 2.2 ASTM Publications

Available from ASTM International, 100 Barr Harbor Drive, P.O. Box C700, West Conshohocken, PA 19428-2959, Tel: 610-832-9585, [www.astm.org](http://www.astm.org).

ASTM B660 Packaging/Packing of Aluminum and Magnesium Products

ASTM B666/B666M Identification Marking of Aluminum and Magnesium Products

## 2.3 ANSI Accredited Publications

Copies of these documents are available online at <https://webstore.ansi.org/>.

ANSI H35.2 Dimensional Tolerances for Aluminum Mill Products

ANSI H35.2M Dimensional Tolerances for Aluminum Mill Products (Metric)

## 2.4 Definitions

Terms used in AMS are defined in AS7766.

## 3. TECHNICAL REQUIREMENTS

### 3.1 Composition

Shall conform to the percentages by weight shown in Table 1, determined in accordance with AMS2355.

**Table 1 - Composition**

Element	Min	Max
Silicon	--	0.25
Iron	--	0.40
Copper	--	0.10
Manganese	--	0.10
Magnesium	2.2	2.8
Chromium	0.15	0.35
Zinc	--	0.10
Other Elements, each	--	0.05
Other Elements, total	--	0.15
Aluminum	remainder	

### 3.2 Condition

Annealed in accordance with AMS2772.

### 3.3 Properties

The product shall conform to the following requirements, determined in accordance with AMS2355 on the mill produced size.

## 3.3.1 Tensile Properties

Shall be as specified in Table 2.

**Table 2A - Tensile properties, inch/pound units**

Nominal Thickness Inches	Tensile Strength ksi	Yield Strength at 0.2% Offset ksi, Min	Elongation in 2 Inches or 4D %, Min
0.006 to 0.007, incl	25.0 to 31.0	9.5	--
Over 0.007 to 0.012, incl	25.0 to 31.0	9.5	14
Over 0.012 to 0.019, incl	25.0 to 31.0	9.5	15
Over 0.019 to 0.031, incl	25.0 to 31.0	9.5	16
Over 0.031 to 0.050, incl	25.0 to 31.0	9.5	18
Over 0.050 to 0.113, incl	25.0 to 31.0	9.5	19
Over 0.113 to 0.249, incl	25.0 to 31.0	9.5	20
Over 0.249 to 3.000, incl	25.0 to 31.0	9.5	18

**Table 2B - Tensile properties, SI units**

Nominal Thickness Millimeters	Tensile Strength MPa	Yield Strength at 0.2% Offset MPa, Min	Elongation in 50.8 mm or 4D %, Min
0.15 to 0.18, incl	172 to 214	65.5	--
Over 0.18 to 0.30, incl	172 to 214	65.5	14
Over 0.30 to 0.48, incl	172 to 214	65.5	15
Over 0.48 to 0.79, incl	172 to 214	65.5	16
Over 0.79 to 1.27, incl	172 to 214	65.5	18
Over 1.27 to 2.87, incl	172 to 214	65.5	19
Over 2.87 to 6.32, incl	172 to 214	65.5	20
Over 6.32 to 76.20, incl	172 to 214	65.5	18

3.3.1.1 Tensile property requirements for sheet and plate outside the thickness range of 1.1 shall be as agreed upon by the purchaser and producer and reported per 4.4.1 (see 8.5).

## 3.3.2 Bending

Product 0.249 inch (6.32 mm) and under in nominal thickness shall withstand, without cracking, bending at room temperature flat on itself with axis of bend parallel to the direction of rolling.

## 3.4 Quality

The product, as received by the purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the product.

## 3.5 Tolerances

Shall conform to all applicable requirements of ANSI H35.2 or ANSI H35.2M.

## 3.6 Exceptions

Any exceptions shall be authorized by the purchaser and reported as in 4.4.1.

#### 4. QUALITY ASSURANCE PROVISIONS

##### 4.1 Responsibility for Inspection

The producer of the product shall supply all samples for the producer's tests and shall be responsible for the performance of all required tests. The purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to the specified requirements.

##### 4.2 Classification of Tests

###### 4.2.1 Acceptance Tests

Composition (see 3.1), tensile properties (see 3.3.1), and tolerances (see 3.5) are acceptance tests and, except for composition, shall be performed on each lot.

###### 4.2.2 Periodic Tests

Bending (see 3.3.2) is a periodic test and shall be performed at a frequency selected by the producer unless frequency of testing is specified by the purchaser.

##### 4.3 Sampling and Testing

Shall be in accordance with AMS2355.

##### 4.4 Reports

The producer of the product shall furnish with each shipment a report stating that the product conforms to the composition and tolerances and showing the numerical results of tests on each inspection lot to determine conformance to the other acceptance test requirements. This report shall include the purchase order number, inspection lot number(s), AMS4015N, size, and quantity. The report shall also identify the producer, the product form, and size from the mill.

4.4.1 When material produced to this specification is beyond the sizes allowed in the scope of tables, or other exceptions are taken to the technical requirements listed in Section 3 (see 5.1.1), the report shall contain a statement "This material is certified as AMS4015N(EXC) because of the following exceptions:" and the specific exceptions shall be listed.

##### 4.5 Resampling and Retesting

Shall be in accordance with AMS2355.

#### 5. PREPARATION FOR DELIVERY

##### 5.1 Identification

Shall be in accordance with ASTM B666/B666M.

5.1.1 When technical exceptions are taken (see 4.4.1), the material shall be marked with AMS4015(EXC).

##### 5.2 Packaging

5.2.1 Flat sheet, plate, and circles 12 inches (305 mm) and over in nominal diameter shall be coated, prior to shipment, with a light corrosion-inhibiting oil.

5.2.2 The product shall be prepared for shipment in accordance with ASTM B660 and in compliance with applicable rules and regulations pertaining to the handling, packaging, and transportation of the product to ensure carrier acceptance with safe delivery.