



AEROSPACE MATERIAL SPECIFICATION

Society of Automotive Engineers, Inc.
400 COMMONWEALTH DRIVE, WARRENDALE, PA. 15096

AMS 4017G

Superseding AMS 4017F

Issued 1-1-42
Revised 1-15-78

ALUMINUM ALLOY SHEET AND PLATE 2.5Mg - 0.25Cr (5052-H34)

1. SCOPE:

- 1.1 Form: This specification covers an aluminum alloy in the form of sheet and plate.
- 1.2 Application: Primarily for parts requiring moderate forming and where good welding characteristics and resistance to corrosion are important.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications (AMS) shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

- 2.1 SAE Publications: Available from Society of Automotive Engineers, Inc., 400 Commonwealth Drive, Warrendale, PA 15096.
 - 2.1.1 Aerospace Material Specifications:
 - AMS 2202 - Tolerances, Aluminum-Base and Magnesium-Base Alloy Sheet and Plate
 - AMS 2350 - Standards and Test Methods
 - AMS 2355 - Quality Assurance Sampling and Testing of Aluminum-Base and Magnesium-Base Alloys, Wrought Products (Except Forgings and Forging Stock) and Flash Welded Rings

2.2 Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

- 2.2.1 Military Standards:
 - MIL-STD-649 - Aluminum and Magnesium Products, Preparation for Shipment and Storage

3. TECHNICAL REQUIREMENTS:

3.1 Composition: Shall conform to the following percentages by weight, determined in accordance with AMS 2355:

	min	max
∅ Magnesium	2.2	2.8
Chromium	0.15	0.35
Iron	--	0.40
Silicon	--	0.25
Zinc	--	0.10
Manganese	--	0.10
Copper	--	0.10
Other Impurities, each	--	0.05
Other Impurities, total	--	0.15
Aluminum	remainder	

SAE Technical Board rules provide that: "All technical reports, including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against infringement of patents."

3.2 Condition: Strain hardened, half-hard, and stabilized.

3.3 Properties: The product shall conform to the following requirements, determined in accordance with AMS 2355:

3.3.1 Tensile Properties: Shall be as specified in Table I and 3.3.1.1.

TABLE I

Nominal Thickness Inch	Tensile Strength psi	Elongation in 2 in. or 4 D %, min
0.009 to 0.019, incl	34,000 - 41,000	3
Over 0.019 to 0.050, incl	34,000 - 41,000	4
Over 0.050 to 0.113, incl	34,000 - 41,000	6
Over 0.113 to 0.249, incl	34,000 - 41,000	7
Over 0.249 to 1.000, incl	34,000 - 41,000	10

TABLE I (SI)

Nominal Thickness Millimetres	Tensile Strength MPa	Elongation in 50 mm or 4D %, min
0.23 to 0.48, incl	234 - 283	3
Over 0.48 to 1.27, incl	234 - 283	4
Over 1.27 to 2.87, incl	234 - 283	6
Over 2.87 to 6.32, incl	234 - 283	7
Over 6.32 to 25.40, incl	234 - 283	10

3.3.1.1 Tensile property requirements for product less than 0.009 in. (0.23 mm) or over 1.000 in. (25.40 mm) in nominal thickness shall be as agreed upon by purchaser and vendor.

3.3.2 Bending: Product 0.249 in. (6.32 mm) and under in nominal thickness shall withstand without cracking, bending at room temperature through an angle of 180 deg around a diameter equal to the bend factor times the nominal thickness of the product with axis of bend parallel to the direction of rolling.

∅	Nominal Thickness		Bend Factor
	Inch	(Millimetres)	
	Up to 0.019, incl	(Up to 0.48, incl)	1
	Over 0.019 to 0.050, incl	(Over 0.48 to 1.27, incl)	2
	Over 0.050 to 0.113, incl	(Over 1.27 to 2.87, incl)	3
	Over 0.113 to 0.249, incl	(Over 2.87 to 6.32, incl)	4

3.3.2.1 Bending requirements for plate over 0.249 in (6.32 mm) in nominal thickness shall be as agreed upon by purchaser and vendor.

3.4 Quality: The product, as received by purchaser, shall be in uniform in quality and condition, sound, and free from foreign materials and from internal and external imperfections detrimental to usage of the product.

3.5 Tolerances: Unless otherwise specified, tolerances shall conform to all applicable requirements of AMS 2202.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection: The vendor of the product shall supply all samples and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.4. Purchaser reserves the right to perform such confirmatory testing as he deems necessary to ensure that the product conforms to the requirements of this specification.

4.2 Classification of Tests:

4.2.1 Acceptance Tests: Tests to determine conformance to composition (3.1), tensile property (3.3.1) and tolerance (3.5) requirements are classified as acceptance tests.

4.2.2 Periodic Tests: Tests to determine conformance to bending (3.3.2) requirements are classified as periodic tests.

4.3 Sampling: Shall be in accordance with AMS 2355. Frequency and extent of sampling shall be as agreed upon by purchaser and vendor.

4.4 Reports:

4.4.1 The vendor of the product shall furnish with each shipment three copies of a report stating that the product conforms to the chemical composition, showing the results of tests to determine conformance to the tensile property requirements, and stating that the product conforms to the other technical requirements of this specification. This report shall include the purchase order number, material specification number and its revision letter, size, and quantity.

4.4.2 The vendor of finished or semi-finished parts shall furnish with each shipment three copies of a report showing the purchase order number, material specification number and its revision letter, contractor or other direct supplier of material, part number, and quantity. When material for making parts is produced or purchased by the parts vendor, that vendor shall inspect each lot of material to determine conformance to the requirements of this specification, and shall include in the report a statement that the material conforms, or shall include copies of laboratory reports showing the results of tests to determine conformance.

4.5 Resampling and Retesting: Shall be in accordance with AMS 2355.

5. PREPARATION FOR DELIVERY:

5.1 Identification: Each sheet and plate shall be marked on one face, in the respective location indicated below, with the alloy number and temper, AMS 4017 or applicable Federal or Military specification designation, manufacturer's identification, and nominal thickness. The characters shall be of such size as to be clearly legible, shall be applied using a suitable marking fluid, and shall be sufficiently stable to withstand normal handling. The markings shall have no deleterious effect on the product or its performance.

5.1.1 Flat Sheet and Plate Under 6 In. (152 mm) Wide: Shall be marked in one or more lengthwise rows of characters recurring at intervals not greater than 3 ft (914 mm).

- 5.1.2 Flat Sheet and Plate 0.375 In. (9.52 mm) and Under, Thick, 6 - 60 In. (152 - 1524 mm), Incl, Wide and 36 - 200 In. (914 - 5080 mm), Incl, Long: Shall be marked in lengthwise rows of characters recurring at intervals not greater than 3 ft (914 mm), the rows being spaced approximately 6 in. (152 mm) on centers across the width and staggered. Every third row shall show the manufacturer's identification and nominal thickness. The other rows shall show the alloy number and temper and AMS 4017 or applicable Federal or Military specification designation.
- 5.1.3 Flat Sheet and Plate Over 0.375 In. (9.52 mm) Thick, Over 60 In. (1524 mm) Wide, or Over 200 In. (5080 mm) Long: Shall be marked as in 5.1.2 or, at vendor's discretion, shall be marked in one or two rows of characters recurring at intervals not greater than 3 ft (914 mm) and running around the periphery of the piece. If one row is used, it shall show all information of 5.1. If two rows are used, one row shall show the alloy number and temper and AMS 4017 or applicable Federal or Military specification designation; the second row shall show the manufacturer's identification and nominal thickness.
- 5.1.3.1 If peripheral marking is applied to the full piece as produced but partial sheets or plates are supplied, an arrow shall also be applied near one corner indicating the direction of rolling.
- 5.1.4 Coiled Sheet: Shall be marked near both the outside and inside ends of the coil; the markings shall be applied as in 5.1 or shall appear on a durable tag or label attached to the coil and marked with the information of 5.1. When the inside end of the coil is inaccessible, as when the sheet is wound on cores, the tag or label may be attached to the core.
- 5.1.5 Circles: Shall be marked with the information of 5.1 if the circle is 24 in. (610 mm) or more in nominal diameter. Circles less than 24 in. (610 mm) in nominal diameter shall be identified as agreed upon by purchaser and vendor.
- 5.2 Protective Treatment: Flat sheet, plate, and circles 12 in. (305 mm) or more in nominal diameter shall be protected during shipment and storage by inter-leaving with suitable paper sheets. Circles less than 12 in. (305 mm) in nominal diameter shall be protected as agreed upon by purchaser and vendor.
- 5.3 Packaging:
- 5.3.1 The product shall be prepared for shipment in accordance with commercial practice and in compliance with applicable rules and regulations pertaining to the handling, packaging, and transportation of the product to ensure carrier acceptance and safe delivery. Packaging shall conform to carrier rules and regulations applicable to the mode of transportation.
- 5.3.2 For direct U. S. Military procurement, packaging shall be in accordance with MIL-STD-649, Level A or Level C, as specified in the request for procurement. Commercial packaging as in 5.3.1 will be acceptable if it meets the requirements of Level C.
6. ACKNOWLEDGMENT: A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.
7. REJECTIONS: Material not conforming to this specification or to authorized modifications will be subject to rejection.
8. NOTES:
- 8.1 Marginal Indicia: The phi (ϕ) symbol is used to indicate technical changes from the previous issue of this specification.