



AEROSPACE MATERIAL SPECIFICATION

Society of Automotive Engineers, Inc.
TWO PENNSYLVANIA PLAZA, NEW YORK, N. Y. 1000

AMS 4023D

Superseding AMS 4023C

Issued 10-1-51

Revised 11-1-68

ALUMINUM ALLOY SHEET AND PLATE, ALCLAD

1.0Mg - 0.60Si - 0.30Cu - 0.25Cr (Alclad 6061; -T6 Sheet, -T651 Plate)

1. **ACKNOWLEDGMENT:** A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.
2. **APPLICATION:** Primarily for formed, medium strength, structural parts not requiring heat treatment and which are required to exhibit maximum corrosion resistance and to approximate the color and appearance of other clad aluminum alloy parts.
3. **COMPOSITION:**

	Core (6061)		Cladding (7072)	
	min	max	min	max
Magnesium	0.8	1.2	Zinc	0.8 - 1.3
Silicon	0.40	0.8	Silicon + Iron	-- 0.7
Copper	0.15	0.40	Magnesium	-- 0.10
Chromium	0.15	0.35	Copper	-- 0.10
Iron	--	0.7	Manganese	-- 0.10
Zinc	--	0.25	Other Impurities, each	-- 0.05
Manganese	--	0.15	Other Impurities, total	-- 0.15
Titanium	--	0.15	Aluminum	remainder
Other Impurities, each	--	0.05		
Other Impurities, total	--	0.15		
Aluminum	remainder			

4. **CONDITION:**
 - 4.1 **Sheet:** Solution and precipitation heat treated.
 - 4.2 **Plate:** Solution heat treated, stretched to produce a nominal permanent set of 2% but not less than \emptyset 1-1/2% nor more than 3%, and precipitation heat treated.
 - \emptyset 4.2.1 Plate shall receive no further straightening operations after stretching.
5. **TECHNICAL REQUIREMENTS:** The product shall conform to the following requirements; tensile \emptyset properties shall be determined in accordance with the latest issue of AMS 2355.
 - 5.1 **Cladding Thickness:** After rolling, the average cladding thickness per side shall be not less than 4% of the total composite thickness. Routine measurements are not required.

SAE Technical Board rules provide that: "All technical reports, including standards and practices recommended, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."

5.2 Tensile Properties:

Nominal Thickness Inches	Tensile Strength psi, min	Yield Strength at 0.2% Offset or at Extension Indicated (E = 9,900,000)		Elongation % in 2 in. or 4D, min
		psi, min	Extension Under Load in. in 2 in.	
0.010 to 0.020, incl	38,000	32,000	0.0105	8
Over 0.020 to 0.499, incl	38,000	32,000	0.0105	10
Over 0.499 to 1.000, incl	42,000	35,000	0.0111	9
Over 1.000 to 2.000, incl	42,000	35,000	0.0111	8
Over 2.000 to 4.000, incl	42,000	35,000	0.0111	6
Over 4.000 to 5.000, incl	40,000	35,000	0.0111	6

5.2.1 Tensile properties of plate over 5.000 in. in thickness shall be as agreed upon by purchaser and vendor.

5.2.2 When a dispute occurs between purchaser and vendor over the yield strength values, yield strength determined by the offset method shall apply.

5.3 Bending: Material shall be capable of withstanding, without cracking, bending at room temperature through an angle of 180 deg around a diameter equal to the bend factor times the nominal thickness of the material, with axis of bend parallel to direction of rolling.

Nominal Thickness Inch	Bend Factor
0.010 to 0.036, incl	3
Over 0.036 to 0.064, incl	4
Over 0.064 to 0.128, incl	5
Over 0.128 to 0.249, incl	6
Over 0.249 to 0.499, incl	10

6. QUALITY: Material shall be uniform in quality and condition, clean, sound, and free from foreign materials and from internal and external imperfections detrimental to fabrication or to performance of parts.

7. TOLERANCES: Unless otherwise specified, tolerances shall conform to all applicable requirements of the latest issue of AMS 2202.

8. REPORTS:

8.1 Unless otherwise specified, the vendor of the product shall furnish with each shipment three copies of a report stating that the product conforms to the chemical composition and technical requirements of this specification. This report shall include the purchase order number, material specification number and its revision letter, thickness, size, and quantity.

8.2 Unless otherwise specified, the vendor of finished or semi-finished parts shall furnish with each shipment three copies of a report showing the purchase order number, material specification number and its revision letter, contractor or other direct supplier of material, part number, and quantity. When material for making parts is produced or purchased by the parts vendor, that vendor shall inspect each lot of material to determine conformance to the requirements of this specification, and shall include in the report a statement that the material conforms, or shall include copies of laboratory reports showing the results of tests to determine conformance.

9. IDENTIFICATION: Unless otherwise specified, each sheet and plate shall be marked on one face, in the respective location indicated below, with the alloy number and temper, AMS 4023 or applicable Federal or Military specification designation, manufacturer's identification, and nominal thickness in inches. The characters shall be of such size as to be clearly legible, shall be applied using a suitable marking fluid, and shall be sufficiently stable to withstand normal handling.