

AEROSPACE MATERIAL SPECIFICATION

Issued	1951-10
Revised	1977-01
Noncurrent	1984-04
Reaf. Noncur.	2009-06
Superseding AMS 4023D	

Aluminum Alloy Sheet and Plate, Alclad
1.0Mg - 0.60Si - 0.28Cu - 0.20Cr (Alclad 6061; -T6 Sheet, -T651 Plate)

NONCURRENCY NOTICE

This specification has been declared "NONCURRENT" by the Aerospace Materials Division, SAE, as of April 1984. It is recommended that this specification not be specified for new designs.

"NONCURRENT" specifications are available from SAE upon request.

SAENORM.COM : Click to view the full PDF of ams4023e

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2009 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
http://www.sae.org

SAE WEB ADDRESS:

SAE values your input. To provide feedback
on this Technical Report, please visit
<http://www.sae.org/technical/standards/AMS4023E>

1. SCOPE:

- 1.1 Form: This specification covers an aluminum alloy in the form of sheet and plate.
- 1.2 Application: Primarily for formed, medium-strength, structural parts not requiring heat treatment and which are required to exhibit maximum corrosion resistance and to approximate the color and appearance of other clad aluminum alloy parts.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications (AMS) shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

2.1 SAE Publications: Available from Society of Automotive Engineers, Inc., 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

AMS 2202 - Tolerances, Aluminum-Base and Magnesium-Base Alloy Sheet and Plate
 AMS 2350 - Standards and Test Methods
 AMS 2355 - Quality Assurance Sampling and Testing of Aluminum-Base and Magnesium-Base Alloys, Wrought Products (Except Forgings and Forging Stock) and Flash Welded Rings

2.2 Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

2.2.1 Military Specifications:

MIL-H-6088 - Heat Treatment of Aluminum Alloys

2.2.2 Military Standards:

MIL-STD-649 - Aluminum and Magnesium Products, Preparation for Shipment and Storage

3. TECHNICAL REQUIREMENTS:

3.1 Composition: Shall conform to the following percentages by weight, determined in accordance with
 ∅ AMS 2355:

	Core (6061)		Cladding (7072)	
	min	max	min	max
Magnesium	0.8	1.2	Zinc	0.8 - 1.3
Silicon	0.40	0.8	Silicon + Iron	-- 0.7
Copper	0.15	0.40	Magnesium	-- 0.10
Chromium	0.04	0.35	Copper	-- 0.10
Iron	--	0.7	Manganese	-- 0.10
Zinc	--	0.25	Other Impurities, each	-- 0.05
Manganese	--	0.15	Other Impurities, total	-- 0.15
Titanium	--	0.15	Aluminum	remainder
Other Impurities, each	--	0.05		
Other Impurities, total	--	0.15		
Aluminum	remainder			

- 3.1 Composition: Shall conform to the following percentages by weight, determined in accordance with
 ∅ AMS 2355:

	Core (6061)		Cladding (7072)	
	min	max	min	max
Magnesium	0.8	1.2	Zinc	0.8 - 1.3
Silicon	0.40	0.8	Silicon + Iron	-- 0.7
Copper	0.15	0.40	Magnesium	-- 0.10
Chromium	0.04	0.35	Copper	-- 0.10
Iron	--	0.7	Manganese	-- 0.10
Zinc	--	0.25	Other Impurities, each	-- 0.05
Manganese	--	0.15	Other Impurities, total	-- 0.15
Titanium	--	0.15	Aluminum	remainder
Other Impurities, each	--	0.05		
Other Impurities, total	--	0.15		
Aluminum		remainder		

- 3.2 Condition:

- ∅ 3.2.1 Sheet: Solution and precipitation heat treated in accordance with MIL-H-6088.
- 3.2.2 Plate: Solution heat treated, stretched to produce a nominal permanent set of 2% but not less than
 ∅ 1-1/2% nor more than 3%, and precipitation heat treated. Heat treatments shall be performed in accordance with MIL-H-6088.
- 3.2.2.1 Plate shall receive no further straightening operations after stretching.

- 3.3 Properties: The product shall conform to the following requirements, determined in accordance with AMS 2355:

- 3.3.1 Tensile Properties: Shall be as specified in Table I and 3.3.1.1.

TABLE I

Nominal Thickness Inches	Tensile Strength psi, min	Yield Strength at 0.2% Offset psi, min	Elongation in 2 in. or 4D %, min
0.010 to 0.020, incl	38,000	32,000	8
Over 0.020 to 0.499, incl	38,000	32,000	10
Over 0.499 to 1.000, incl	42,000	35,000	9
Over 1.000 to 2.000, incl	42,000	35,000	8
Over 2.000 to 4.000, incl	42,000	35,000	6
Over 4.000 to 5.000, incl	40,000	35,000	6

TABLE I (SI)

Nominal Thickness Millimetres	Tensile Strength MPa, min	Yield Strength at 0.2% Offset MPa, min	Elongation in 50.8 mm or 4D %, min
0.25 to 0.51, incl	262	221	8
Over 0.51 to 12.67, incl	262	221	10
Over 12.67 to 25.40, incl	290	241	9
Over 25.40 to 50.80, incl	290	241	8
Over 50.80 to 101.60, incl	290	241	6
Over 101.60 to 127.00, incl	276	241	6

3.3.1.1 Tensile properties of plate over 5.000 in. (127.00 mm) in nominal thickness shall be as agreed upon by purchaser and vendor.

3.3.2 Bending: Product 0.010 - 0.499 in. (0.25 - 12.67 mm), incl, in nominal thickness shall withstand, without cracking, bending at room temperature through an angle of 180 deg (3.14 rad) around a diameter equal to the bend factor times the nominal thickness of the product with axis of bend parallel to the direction of rolling.

Nominal Thickness		Bend Factor
Inch	(Millimetres)	
0.010 to 0.036, incl	(0.25 to 0.91, incl)	3
Over 0.036 to 0.064, incl	(Over 0.91 to 1.63, incl)	4
Over 0.064 to 0.128, incl	(Over 1.63 to 3.25, incl)	5
Over 0.128 to 0.249, incl	(Over 3.25 to 6.32, incl)	6
Over 0.249 to 0.499, incl	(Over 6.32 to 12.67, incl)	10

3.3.2.1 Bending requirements for plate over 0.499 in. (12.67 mm) in nominal thickness shall be as agreed upon by purchaser and vendor.

3.3.3 Cladding Thickness: After rolling, the average cladding thickness per side shall be not less than 4% of the total composite thickness.

3.4 Quality: The product, as received by the purchaser shall be uniform in quality and condition, sound, and free from foreign materials and from internal and external imperfections detrimental to usage of the product.

3.5 Tolerances: Unless otherwise specified, tolerances shall conform to all applicable requirements of AMS 2202.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection: The vendor of the product shall supply all samples and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.4. Purchaser reserves the right to perform such confirmatory testing as he deems necessary to ensure that the product conforms to the requirements of this specification.

4.2 Classification of Tests:

4.2.1 Acceptance Tests: Tests to determine conformance to composition (3.1), tensile properties (3.3.1), and tolerance (3.5) requirements are classified as acceptance tests.

4.2.2 Periodic Tests: Tests to determine conformance to bending (3.3.2) and cladding thickness (3.3.3) requirements are classified as periodic tests.

4.3 Sampling: Shall be in accordance with AMS 2355. Frequency of sampling for periodic tests shall be as agreed upon by purchaser and vendor.

4.4 Reports:

4.4.1 The vendor of the product shall furnish with each shipment three copies of a report stating that the product conforms to the chemical composition and other technical requirements of this specification. This report shall include the purchase order number, material specification number and its revision letter, size, and quantity.