



AEROSPACE MATERIAL SPECIFICATION

Society of Automotive Engineers, Inc.
TWO PENNSYLVANIA PLAZA, NEW YORK, N.Y. 1000

AMS 4029E

Superseding AMS 4029D

Issued	8-15-58
Revised	5-1-69

ALUMINUM ALLOY SHEET AND PLATE

4.5Cu - 0.85Si - 0.80Mn - 0.50Mg (2014; -T6 Sheet, -T651 Plate)

1. **ACKNOWLEDGMENT:** A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.
2. **APPLICATION:** Primarily for structural parts of good strength. Certain design and processing procedures may cause this material to be susceptible to stress corrosion cracking; ARP 823 recommends practices to minimize such conditions.
3. **COMPOSITION:**

	min	max
Copper	3.9	5.0
Silicon	0.50	1.2
Manganese	0.40	1.2
Magnesium	0.20	0.8
Iron	--	0.7
Zinc	--	0.25
Titanium	--	0.15
Chromium	--	0.10
Other Impurities, each	--	0.05
Other Impurities, total	--	0.15
Aluminum	remainder	

4. **CONDITION:**

4.1 **Sheet:** Solution and precipitation heat treated.

4.2 **Plate:** Solution heat treated, stretched to produce a nominal permanent set of 2% but not less than 1-1/2% nor more than 3%, and precipitation heat treated.

4.2.1 Plate shall receive no further straightening operations after stretching.

5. **TECHNICAL REQUIREMENTS:** The product shall conform to the following requirements; tensile properties shall be determined in accordance with the latest issue of AMS 2355.

SAE Technical Board rules provide that: "All technical reports, including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against infringement of patents."

5.1 Tensile Properties:

Nominal Thickness Inches	Tensile Strength psi, min	Yield Strength at 0.2% Offset or at Extension Indicated (E = 10,500,000)		Elongation % in 2 in. or 4D min
		psi, min	Extension Under Load in. in 2 in.	
0.020 to 0.039, incl	64,000	57,000	0.0149	6
Over 0.039 to 0.249, incl	66,000	58,000	0.0150	7
Over 0.249 to 0.499, incl	67,000	59,000	0.0152	7
Over 0.499 to 1.000, incl	67,000	59,000	0.0152	6
Over 1.000 to 2.000, incl	67,000	59,000	0.0152	4
Over 2.000 to 2.500, incl	65,000	58,000	0.0150	2
Over 2.500 to 3.000, incl	63,000	57,000	0.0149	2
Over 3.000 to 4.000, incl	59,000	55,000	0.0145	1

5.1.1 Tensile properties of plate thicker than 4.000 in. shall be as agreed upon by purchaser and vendor.

5.1.2 When a dispute occurs between purchaser and vendor over the yield strength values, yield strength determined by the offset method shall apply.

5.2 Bending: Material shall be capable of withstanding, without cracking, bending at room temperature through an angle of 180 deg around a diameter equal to the bend factor times the nominal thickness of material with axis of bend parallel to direction of rolling.

Nominal Thickness Inch.	Bend Factor
0.020 to 0.039, incl	5
Over 0.039 to 0.050, incl	6
Over 0.050 to 0.124, incl	8
Over 0.124 to 0.249, incl	10
Over 0.249 to 0.499, incl	12

6. QUALITY: Material shall be uniform in quality and condition, clean, sound, and free from foreign materials and from internal and external imperfections detrimental to fabrication or to performance of parts.

7. TOLERANCES: Unless otherwise specified, tolerances shall conform to all applicable requirements of the latest issue of AMS 2202. Flatness tolerances for plate over 6.000 in. thick shall be as agreed upon by purchaser and vendor.

8. REPORTS:

8.1 Unless otherwise specified, the vendor of the product shall furnish with each shipment three copies of a report stating that the product conforms to the chemical composition and technical requirements of this specification. This report shall include the purchase order number, material specification number and its revision letter, thickness, size, and quantity.

8.2 Unless otherwise specified, the vendor of finished or semi-finished parts shall furnish with each shipment three copies of a report showing the purchase order number, material specification number and its revision letter, contractor or other direct supplier of material, part number, and quantity. When material for making parts is produced or purchased by the parts vendor, that vendor shall inspect each lot of material to determine conformance to the requirements of this specification, and shall include in the report a statement that the material conforms, or shall include copies of laboratory reports showing the results of tests to determine conformance.